



Standard Test Methods for Polymer Content of Styrene Monomer and AMS (α -Methylstyrene)¹

This standard is issued under the fixed designation D 2121; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 These test methods cover the determination of the polymer content of styrene monomer and AMS (α -Methylstyrene). It should be noted, however, that dimers and trimers are not measured by these test methods.

1.2 *Test Method A*, which is based on the use of a spectrophotometer or photometer, is intended for the quantitative determination of the polymer content of styrene monomer or AMS in concentrations up to 15 mg/kg. Samples containing more than 15 mg/kg of polymer must be suitably diluted before measurement.

1.3 *Test Method B* is a rapid visual procedure that is intended for the approximate evaluation of polymer to a maximum concentration of 1.0 weight %. Samples having a polymer content of 1.0 weight % or greater should be suitably diluted prior to measurement.

1.4 In determining the conformance of the test results using this method to applicable specifications, results shall be rounded off in accordance with the rounding-off method of Practice E 29.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 8.

2. Referenced Documents

2.1 *ASTM Standards*:²

D 2827 Specification for Styrene Monomer

¹ These test methods are under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and are the direct responsibility of Subcommittee D16.07 on Styrene, Ethylbenzene and C9 and C10 Aromatic Hydrocarbons.

Current edition approved Jan. 1, 2007. Published January 2007. Originally approved in 1962. Last previous edition approved in 2000 as D 2121 – 00.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 3437 Practice for Sampling and Handling Liquid Cyclic Products

D 6809 Guide for Quality Control and Quality Assurance Procedures for Aromatic Hydrocarbons and Related Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 *Other Document*:

OSHA Regulations, 29 CFR, paragraphs 1910.1000 and 1910.1200³

TEST METHOD A—DETERMINATION OF POLYMER IN STYRENE MONOMER OR α -METHYLSTYRENE PHOTOMETER METHOD

3. Summary of Test Method

3.1 This test method utilizes the fact that polymers present in the monomers are insoluble in methanol. The polymer content of styrene monomer or AMS is determined by measurement of the degree of turbidity produced by the addition of dry methanol to the styrene or AMS sample.

4. Significance and Use

4.1 This test method can be used for determining polymer concentrations in styrene monomer or AMS.

4.2 This test method will not detect dimers and trimers.

4.3 This test method can be used for plant control and for specification analysis.

5. Interferences

5.1 Small changes in turbidity may occur with time. It is, therefore, important that the absorbance of calibration mixtures and samples be determined after standing the same length of time.

5.2 Hexane is used for two reasons:

5.2.1 To block out any color in the styrene or AMS, and

5.2.2 To indicate dissolved water in the styrene or AMS.

6. Apparatus

6.1 *Pipets*, 10 and 15-mL.

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

*A Summary of Changes section appears at the end of this standard.

6.2 *Bottles or Flasks*, of suitable size equipped with glass stoppers.

6.3 *Spectrophotometer or Photometer Cells*, with 50 to 150-mm light path.

6.4 *Spectrophotometer or Photometer*, capable of absorbance measurements in wavelength region of 420 nm and sensitive to 1 mg polymer/kg monomer.

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Hexane*, dry.

7.3 *Methanol*, dry.

7.4 *Polystyrene*:

7.4.1 Prepare polystyrene as follows: wash 50 mL of styrene monomer twice with equal volumes of 1 *N* NaOH solution and twice with equal volumes of water. After the second water wash, filter the styrene through two layers of rapid filtering ready folded filter paper. Pour about 20 mL of this styrene monomer into a test tube and heat in an oven at 100°C for 24 h to promote polymerization. At the end of this time, remove the polystyrene from the test tube by breaking the tube and discarding all glass. Grind the polymer plug to a fine powder in an agate mortar.

7.4.2 Commercially available high-purity polystyrene pellets can be used; however, high-molecular weight polystyrene (>150 000 molecular weight) should be specified.

7.5 *Styrene Monomer*, conforming to Specification **D 2827**.

7.6 *Toluene*, dry.

8. Hazards

8.1 Styrene monomer is flammable and polymerizes exothermically on contact with peroxides, mineral acids and aluminum chloride.

8.2 Styrene monomer both in liquid and vapor state, when in sufficient concentrations, acts as an irritant to the eyes and respiratory tract.

8.3 Consult current **OSHA regulations**, local regulations, and suppliers' Material Safety Data Sheets for all materials used in these test methods.

9. Sampling and Handling

9.1 Sample the material in accordance with Practice **D 3437**.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

10. Calibration

10.1 *Apparatus*—Prepare and operate the spectrophotometer or photometer in accordance with the manufacturer's instructions.

10.2 *Reference Standards and Blanks*:

10.2.1 Dissolve 0.0905 g of polystyrene in 1000 mL of toluene measured at 25°C, which is equivalent to 100 mg/kg of polymer in monomer. This serves as the standard for polymer in styrene and polymer in AMS.

10.2.2 Make standard solutions containing 1, 3, 6, 9, 12, and 15 mg/kg of styrene polymer by diluting 1, 3, 6, 9, 12, and 15 mL of the 100 mg/kg standard solution to 100 mL with toluene in a volumetric flask at 25°C.

10.3 *Calibration Curves and Tables*:

10.3.1 Into each of a series of bottles equipped with glass stoppers pipet 15 mL of dry methanol and 10 mL of a polymer standard and mix thoroughly. Into another series of bottles pipet 15 mL of hexane and 10 mL of each polymer standard and mix thoroughly. Other volumes may be used, depending on the capacity of the spectrophotometer cell as long as the 3:2 proportion is maintained.

10.3.2 Allow the solutions to stand in the stoppered bottles for 15 min ± 1 min (**Note 1**). At the end of this time, pour the solutions into the spectrophotometer cells and measure the absorbance of each at a wavelength of 420 nm using the hexane/polymer standard as the blank (**Note 2**).

NOTE 1—Small changes in turbidity may occur with time. It is, therefore, important that the absorbance of calibration mixtures and samples be determined after standing the same length of time.

NOTE 2—The hexane is used for two reasons: (1) to blank out any color in the styrene, and (2) to indicate dissolved water in the styrene.

10.3.3 Prepare a calibration curve by plotting the absorbance against the milligrams per kilogram of polymer.

11. Procedure

11.1 Pipet 15 mL of hexane into a bottle equipped with a glass stopper.

11.2 Into a second bottle, pipet 15 mL of dry methanol.

11.3 Add 10 mL of styrene monomer or AMS to each bottle and mix thoroughly.

11.4 Proceed as described in **10.3.2** using the hexane mixture as the blank.

12. Calculation

12.1 Read the milligrams per kilogram of polymer directly from the calibration curve.

NOTE 3—Milligrams per kilogram can be converted to weight percent by dividing by 10 000.

13. Report

13.1 Report the polymer content of the sample as milligrams of polymer per kilogram of monomer to the nearest mg/kg. For results less than 1 mg/kg, report </mg/kg.