



# Standard Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials<sup>1</sup>

This standard is issued under the fixed designation G154; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This practice is limited to the basic principles for operating a fluorescent UV lamp and water apparatus; on its own, it does not deliver a specific result.

1.2 It is intended to be used in conjunction with a practice or method that defines specific exposure conditions for an application along with a means to evaluate changes in material properties. This practice is intended to reproduce the weathering effects that occur when materials are exposed to sunlight (either direct or through window glass) and moisture as rain or dew in actual usage. This practice is limited to the procedures for obtaining, measuring, and controlling conditions of exposure.

NOTE 1—Practice **G151** describes general procedures to be used when exposing nonmetallic materials in accelerated test devices that use laboratory light sources.

NOTE 2—A number of exposure procedures are listed in an appendix; however, this practice does not specify the exposure conditions best suited for the material to be tested.

1.3 Test specimens are exposed to fluorescent UV light under controlled environmental conditions. Different types of fluorescent UV lamp sources are described.

NOTE 3—In this standard, the terms *UV light* and *UV radiation* are used interchangeably.

1.4 Specimen preparation and evaluation of the results are covered in ASTM methods or specifications for specific materials. General guidance is given in Practice **G151** and ISO 4892-1.

NOTE 4—General information about methods for determining the change in properties after exposure and reporting these results is described in ISO 4582 and Practice **D5870**.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee **G03** on Weathering and Durability and is the direct responsibility of Subcommittee **G03.03** on Simulated and Controlled Exposure Tests.

Current edition approved March 1, 2016. Published September 2016. Originally approved in 1997. Last previous edition approved in 2012 as G154 – 12a. DOI: 10.1520/G0154-16.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.7 This standard is technically similar to ISO 4892-3 and ISO 16474-3.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

**D5870** Practice for Calculating Property Retention Index of Plastics

**D6631** Guide for Committee D01 for Conducting an Inter-laboratory Study for the Purpose of Determining the Precision of a Test Method

**G113** Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

**G151** Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

**G177** Tables for Reference Solar Ultraviolet Spectral Distributions: Hemispherical on 37° Tilted Surface

### 2.2 ISO Standards:<sup>3</sup>

**ISO 4582** Plastics—Determination of the Changes of Colour and Variations in Properties After Exposure to Daylight Under Glass, Natural Weathering or Artificial Light

**ISO 4892-1** Plastics—Methods of Exposure to Laboratory Light Sources—Part 1, Guidance

**ISO 4892-3** Plastics—Methods of Exposure to Laboratory Light Sources—Part 3, Fluorescent UV lamps

**ISO 16474-3** Paints and Varnishes—Methods of Exposure to Laboratory Light Sources—Part 3: Fluorescent UV Lamps

## 3. Terminology

3.1 *Definitions*—The definitions given in Terminology **G113** are applicable to this practice.

3.2 *Definitions of Terms Specific to This Standard*—As used

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

in this practice, the term *sunlight* is identical to the terms *daylight* and *solar irradiance, global* as they are defined in Terminology **G113**.

3.2.1 *Fluorescent Ultraviolet (UV) lamp Apparatus*—an apparatus specifically designed for performing artificial accelerated weathering and irradiation tests using fluorescent UV lamps as the light source and including a means to expose the test specimens to moisture and controlled temperature.

#### 4. Summary of Practice

4.1 Specimens are exposed to repetitive cycles of light and moisture under controlled environmental conditions.

4.1.1 Moisture is usually produced by condensation of water vapor onto the test specimen or by spraying the specimens with demineralized/deionized water.

4.2 The exposure condition may be varied by selection of:

4.2.1 The fluorescent lamp,

4.2.2 The lamp's irradiance level,

4.2.3 The type of moisture exposure,

4.2.4 The timing of the light, dark, and moisture periods, and

4.2.5 The temperature during each exposure condition.

#### 5. Significance and Use

5.1 The use of this apparatus is intended to induce property changes consistent with the end use conditions, including the effects of the UV portion of sunlight, moisture, and heat. Typically, these exposures would include moisture in the form of condensing humidity. Exposures are not intended to simulate the deterioration caused by localized weather phenomena, such as atmospheric pollution, biological attack, and saltwater exposure. Alternatively, the exposure may simulate the effects of sunlight through window glass. (**Warning**—Refer to Practice **G151** for full cautionary guidance applicable to all laboratory weathering devices.)

5.2 This practice provides general procedures for operating fluorescent UV lamp weathering devices that allow for a wide range of exposure conditions. Therefore, no reference shall be made to results from the use of this practice unless accompanied by a report detailing the specific operating conditions in conformance with Section **10**.

5.2.1 It is recommended that a similar material of known performance (a control) be exposed simultaneously with the test specimen to provide a standard for comparative purposes. Generally, two controls are recommended: one known to have poor durability and one known to have good durability. It is recommended that at least three replicates of each material evaluated be exposed in each test to allow for statistical evaluation of results.

5.2.2 Comparison of results obtained from specimens exposed in the same model of apparatus should not be made unless reproducibility has been established among devices for the material to be tested.

5.2.3 Comparison of results obtained from specimens exposed in different models of apparatus should not be made unless correlation has been established among devices for the material to be tested.

NOTE 5—See Guide **D6631** for guidance.

#### 6. Apparatus

6.1 *Laboratory Light Source*—The light source shall be one or more fluorescent UV lamps. A variety of fluorescent UV lamps can be used for this procedure. Differences in lamp intensity or spectrum may cause significant differences in test results.

6.1.1 Do not mix different types of lamps. Mixing different types of lamps in a fluorescent UV apparatus may produce major inconsistencies in the light falling on the samples, unless the apparatus has been specifically designed to ensure a uniform spectral distribution.

6.1.1.1 A detailed description of the type(s) of lamp(s) used shall be stated in the test report. The particular testing application determines which lamp is used. See **Appendix X1** for lamp application guidelines.

6.1.2 The apparatus should include an irradiance control system to monitor and control the irradiance. In apparatuses without irradiance control, the actual irradiance levels at the test specimen surface may vary due to the type of lamps, manufacturer of the lamps, age of the lamps, accumulation of dirt or other residue on the lamps, distance to the lamp array, air temperature within the chamber and ambient laboratory temperature.

NOTE 6—In general, in apparatuses without irradiance control, lamp output will decrease with increasing chamber or laboratory temperature, or both.

6.1.3 Fluorescent lamps age with extended use. Follow the apparatus manufacturer's instructions on the procedure necessary to maintain desired irradiance (**1, 2**).<sup>4</sup>

6.1.4 *Standard Fluorescent UV Lamps*—Fluorescent UV lamps are available with a choice of spectral power distributions that vary significantly. The more common are identified as UVA-340, UVA-351, and UVB-313. These numbers represent the characteristic nominal wavelength (in nm) of peak emission for each of these lamp types. The actual peak emissions are at 343 nm, 350 nm, and 313 nm, respectively.

6.1.4.1 *Spectral Power Distribution of UVA-340 Lamps for Daylight UV*—The spectral power distribution of UVA-340 fluorescent lamps shall comply with the requirements specified in **Table 1**.

NOTE 7—The main application for UVA-340 lamps is for simulation of the short and middle UV wavelength region of daylight.

6.1.4.2 *Spectral Power Distribution of UVA-351 Lamps for Daylight UV Behind Window Glass*—The spectral power distribution of UVA-351 lamp for Daylight UV behind Window Glass shall comply with the requirements specified in **Table 2**.

NOTE 8—The main application for UVA-351 lamps is for simulation of the short and middle UV wavelength region of daylight that has been filtered through window glass (**3**).

6.1.4.3 *Spectral Power Distribution of UVB-313 Lamps*—The spectral power distribution of UVB-313 fluorescent lamps shall comply with the requirements specified in **Table 3**.

<sup>4</sup> The boldface numbers in parentheses refer to a list of references at the end of this standard.

**TABLE 1 Relative Ultraviolet Spectral Power Distribution Specification for Fluorescent UVA-340 Lamps for Daylight UV<sup>A,B</sup>**

Spectral Bandpass Wavelength $\lambda$ in nm	Minimum Percent <sup>C</sup>	Benchmark Solar Radiation Percent <sup>D,E</sup>	Maximum Percent <sup>C</sup>
$\lambda < 290$			0.01
$290 \leq \lambda \leq 320$	5.9	5.8	9.3
$320 < \lambda \leq 360$	60.9	40.0	65.5
$360 < \lambda \leq 400$	26.5	54.2	32.8

<sup>A</sup> Data in **Table 1** are the irradiance in the given bandpass expressed as a percentage of the total irradiance from 290 to 400 nm. The manufacturer is responsible for determining conformance to **Table 1**. **Annex A1** states how to determine relative spectral irradiance.

<sup>B</sup> The data in **Table 1** are based on the rectangular integration of 65 spectral power distributions for fluorescent UV devices operating with UVA 340 lamps of various lots and ages. The spectral power distribution data is for lamps within the aging recommendations of the device manufacturer. The minimum and maximum data are at least the three sigma limits from the mean for all measurements.

<sup>C</sup> The minimum and maximum columns will not necessarily sum to 100 % because they represent the minimum and maximum for the data used. For any individual spectral power distribution, the calculated percentage for the bandpasses in **Table 1** will sum to 100 %. For any individual fluorescent UVA-340 lamp, the calculated percentage in each bandpass must fall within the minimum and maximum limits of **Table 1**. Test results can be expected to differ between exposures using devices with fluorescent UVA-340 lamps in which the spectral power distributions differ by as much as that allowed by the tolerances. Contact the manufacturer of the fluorescent UV devices for specific spectral power distribution data for the fluorescent UVA-340 lamp used.

<sup>D</sup> The benchmark solar radiation data is defined in **ASTM G177** and is for atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV. While this data is provided for comparison purposes only, it is desirable for the laboratory accelerated light source to provide a spectrum that is a close match to the benchmark solar spectrum.

<sup>E</sup> For the benchmark daylight spectrum, the UV irradiance (290 to 400 nm) is 9.8% and the visible irradiance (400 to 800 nm) is 90.2% expressed as a percentage of the total irradiance from 290 to 800 nm. Because the primary emission of fluorescent UV lamps is concentrated in the 290 to 400 nm bandpass, there are limited visible light emissions from fluorescent UV lamps.

**NOTE 9**—Fluorescent UVB lamps have the spectral distribution of radiation peaking near the 313-nm mercury line, and as such, are not recommended for sunlight simulation. They emit significant amounts of radiation below 295 nm, the nominal cut on wavelength of global solar radiation, that may result in aging processes not occurring outdoors. See **Table 3**.

**6.2 Test Chamber**—The design of the test chamber may vary, but it should be constructed from corrosion resistant material and, in addition to the light source, may provide for means of controlling temperature and relative humidity. When required, provision shall be made for the spraying of water on the test specimen for the formation of condensate on the exposed face of the specimen or for the immersion of the test specimen in water.

**6.2.1** The light source(s) shall be located with respect to the specimens such that the uniformity of irradiance at the specimen face complies with the requirements in **Practice G151**.

**6.2.2** Lamp replacement, lamp rotation, and specimen repositioning may be required to obtain uniform exposure of all specimens to UV radiation and temperature. Follow manufacturer's recommendation for lamp replacement and rotation.

**6.3 Calibration**—To ensure standardization and accuracy, the instruments associated with the exposure apparatus (for example, timers, thermometers, UV sensors, and radiometers) require periodic calibration to ensure repeatability of test results. Calibration schedule and procedure shall be in accor-

**TABLE 2 Relative Spectral Power Distribution Specification for Fluorescent UVA-351 Lamps for Daylight UV Behind Window Glass<sup>A,B</sup>**

Spectral Bandpass Wavelength $\lambda$ in nm	Minimum Percent <sup>C</sup>	Window Glass Filtered Daylight Percent <sup>D,E</sup>	Maximum Percent <sup>C</sup>
$\lambda < 300$		0.0	0.2
$300 \leq \lambda \leq 320$	1.1	$\leq 0.5$	3.3
$320 < \lambda \leq 360$	60.5	34.2	66.8
$360 < \lambda \leq 400$	30.0	65.3	38.0

<sup>A</sup> Data in **Table 2** are the irradiance in the given bandpass expressed as a percentage of the total irradiance from 300 to 400 nm. The manufacturer is responsible for determining conformance to **Table 1**. **Annex A1** states how to determine relative spectral irradiance.

<sup>B</sup> The data in **Table 2** are based on the rectangular integration of 21 spectral power distributions for fluorescent UV devices operating with UVA 351 lamps of various lots and ages. The spectral power distribution data is for lamps within the aging recommendations of the device manufacturer. The minimum and maximum data are at least the three sigma limits from the mean for all measurements.

<sup>C</sup> The minimum and maximum columns will not necessarily sum to 100 % because they represent the minimum and maximum for the data used. For any individual spectral power distribution, the calculated percentage for the bandpasses in **Table 2** will sum to 100 %. For any individual fluorescent UV device operating with UVA 351 lamps, the calculated percentage in each bandpass must fall within the minimum and maximum limits of **Table 2**. Test results can be expected to differ between exposures using fluorescent UV devices in which the spectral power distributions differ by as much as that allowed by the tolerances. Contact the manufacturer of the fluorescent UV devices for specific spectral power distribution data for the lamps used.

<sup>D</sup> The window glass filtered solar radiation data is for a solar spectrum with atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV (defined in **ASTM G177**) that has been filtered by window glass. The glass transmission is the average for a series of single strength window glasses tested as part of a research study for **ASTM Subcommittee G3.02 (3)**. While this data is provided for comparison purposes only, it is desirable for the laboratory accelerated light source to provide a spectrum that is a close match to this benchmark window glass filtered solar spectrum.

<sup>E</sup> For the benchmark window glass filtered solar spectrum, the UV irradiance (300 to 400 nm) is 8.2 % and the visible irradiance (400 to 800 nm) is 91.8 % expressed as a percentage of the total irradiance from 300 to 800 nm. Because the primary emission of fluorescent UV lamps is concentrated in the 290 to 400 nm bandpass, there are limited visible light emissions from fluorescent UV lamps.

dance with manufacturer's instructions. Calibration should be traceable to a national metrological institute (NMI).

**6.4 Radiometer**—The use of a radiometer to monitor and control the amount of radiant energy received at the sample is recommended. If a radiometer is used, it shall comply with the requirements in **Practice G151**.

**6.5 Thermometer**—Either insulated or un-insulated black or white panel thermometers may be used. The un-insulated thermometers may be made of either steel or aluminum. Thermometers shall conform to the descriptions found in **Practice G151**.

**NOTE 10**—Typically, these devices control by un-insulated black panel thermometer only.

**6.5.1** The thermometer shall be mounted on the specimen rack so that its surface is in the same relative position and subjected to the same influences as the test specimens.

**6.5.2** The apparatus may provide chamber air temperature control. Positioning and calibration of chamber air temperature sensors shall be in accordance with the descriptions found in **Practice G151**.