



AEROSPACE MATERIAL SPECIFICATION	AMS2175™	REV. A
	Issued 2003-07 Revised 2010-06 Reaffirmed 2018-08 Superseding AMS2175	
Castings, Classification and Inspection of		

RATIONALE

AMS2175A results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Purpose

This specification establishes nondestructive testing methods, sampling frequency, and acceptance criteria for the inspection of metal castings.

1.2 Application

This specification has been used typically for structural castings, but usage is not limited to such applications.

1.2.1 Casting Methods

This specification is intended to apply to all casting methods except high pressure die castings. See 8.2.

1.2.2 Casting Alloys

This specification is intended to apply to all casting alloys covered in Tables 6 through 14. Other alloys may be inspected to this standard as described in 3.4.3.2 using criteria specified by the cognizant engineering organization.

1.3 Classification

Castings that are inspected in accordance with this specification are designated by classes and applicable grades. The "Casting Class" governs the frequency of inspection (See 3.1 and 4.3), while the "Casting Grade" controls the acceptance criteria. See 3.1 and 3.4.

1.3.1 Classes

Class 1 - A casting, the single failure of which would endanger the lives of operating personnel, or cause the loss of a missile, aircraft, or other vehicle.

Class 2 - A casting, the single failure of which would result in a significant operational penalty. In the case of missiles, aircraft, and other vehicles, this includes loss of major components, unintentional release or inability to release armament stores, or failure of weapon installation components.

Class 3 - Castings not included in Class 1 or Class 2 and having a margin of safety of 200 percent or less.

Class 4 - Castings not included in Class 1 or Class 2 and having a margin of safety greater than 200 percent.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2018 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit
<http://standards.sae.org/AMS2175A>**

1.3.2 Grades

Castings, or sections of a casting, shall be of the following grades:

Grade A - The highest quality grade of casting, or area of a casting, with minimum allowable discontinuities and very difficult to produce except in local areas.

Grade B - The second highest quality grade of casting, or area of a casting, which allows slightly more discontinuities than Grade A, and difficult to produce, except in local areas.

Grade C - A high quality grade of casting, or area of a casting, that can be consistently produced.

Grade D - The lowest quality grade of a casting, or area of a casting, that is easily produced and is used primarily for low stress or noncritical areas adjacent to the higher graded areas.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 155	Reference Radiographs for Inspection of Aluminum and Magnesium Castings
ASTM E 186	Reference Radiographs for Heavy-Walled (2 to 4.5-in. (51 to 114-mm)) Steel Castings
ASTM E 192	Reference Radiographs of Investment Steel Castings for Aerospace Applications
ASTM E 272	Reference Radiographs of High-Strength Copper-Base and Nickel-Copper Alloy Castings
ASTM E 280	Reference Radiographs for Heavy-Walled (4.5 to 12-in. (114 to 305-mm)) Steel Castings
ASTM E 310	Reference Radiographs for Tin Bronze Castings
ASTM E 446	Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness
ASTM E 1255	Radioscopy
ASTM E 1320	Reference Radiographs for Titanium Castings
ASTM E 1417	Liquid Penetrant Testing
ASTM E 1444	Magnetic Particle Testing
ASTM E 1742	Radiographic Examination
ASTM E 2033	Computed Radiology (Photostimulable Luminescence Method)
ASTM E 2104	Radiographic Examination of Advanced Aero and Turbine Materials and Components
ASTM E 2422	Digital Reference Images for Inspection of Aluminum Castings

2.2 NAS Publications

Available from Aerospace Industries Association, 1000 Wilson Boulevard, Suite 1700, Arlington, VA 22209-3928, Tel: 703-358-1000, www.aia-aerospace.org.

NAS 410 Certification and Qualification of Nondestructive Test Personnel

3. TECHNICAL REQUIREMENTS

3.1 Classification of Castings

3.1.1 Determination of Classes and Grades

The cognizant engineering organization shall establish the class and grade(s) for each casting design in accordance with 1.3). If the grade of casting is not specified on the drawing or other contractual document, Grade C shall apply, except for Class 4 castings, where Grade D shall apply. Sections of a casting may be of varying grades depending on the applied stresses to that portion of the casting. Particular attention should be given to areas that contain, or will eventually contain, stress risers after machining (such as sharp internal corners, holes, or notches).

3.1.1.1 Class 1 Casting Requirements

All areas of Class 1 castings shall be of a quality equivalent to, or higher quality grade than, Grade C, except that all highly stressed areas of a Class 1 casting shall be of a quality equivalent to, or higher quality grade than, Grade B.

3.2 Inspection Sequence

It is the responsibility of the supplier to perform and comply with appropriate inspections as necessary and in the proper sequence during processing to assure freedom from harmful discontinuities in the final product. The intent of inspections during processing is to detect discontinuities that would be detrimental to the final product at the earliest stage in processing so as to minimize the cost of rejected or scrapped castings. The sequence for penetrant, magnetic particle, and radiographic inspections shall be as specified in ASTM E 1417, ASTM E 1444, and ASTM E 1742, respectively, or as otherwise specified by the cognizant engineering organization.

3.3 Personnel Qualification

Personnel performing penetrant, magnetic particle or radiographic inspections shall be qualified and certified in accordance with NAS 410 for the applicable method and technique.

3.4 Inspection Methods and Acceptance Criteria

3.4.1 Visual Inspection

Visual inspection shall be performed in areas with ambient lighting that is not less than 75 foot-candles.

3.4.1.1 Surface Characteristics

Castings shall be free of foreign materials, and shall not contain cracks, hot tears, cold shuts, and negative core seams (also called parting line below flush). In addition, castings shall conform to the criteria specified on the engineering drawing, specification, or agreed upon observational standards. See 8.3.

3.4.1.2 Surface Roughness

Surface roughness shall conform to the engineering drawing requirements. Surface roughness requirements specified on the engineering drawing (e.g., 63 Ra, 125 RMS, etc.) do not preclude the presence of acceptable liquid penetrant or magnetic particle indications. Visual and tactile comparison with commercially available observational standards may be used to determine conformance to surface roughness requirements.