



AEROSPACE MATERIAL SPECIFICATION	AMS2772™	REV. G
	Issued 1997-01 Revised 2016-04	
Superseding AMS2772F		
Heat Treatment of Aluminum Alloy Raw Materials		

RATIONALE

AMS2772G revises Equipment (4.3.1.1, 4.3.1.1.2), Uniformity of Quench (4.3.2.5, 4.3.2.5.2), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Purpose

This specification covers requirements and recommendations for the heat treatment of wrought aluminum alloy raw materials (see 8.2.1) by producers. It supersedes AMS-H-6088 and replaces MIL-H-6088.

1.1.1 Tempers

Aluminum alloy tempers are described in SAE AS1990 and ANSI H35.1.

1.1.2 Other Alloys

This specification may be used for alloys other than those specified herein providing temperatures, times, and quenchants are specified.

1.1.2.1 For those material specifications that specify proprietary heat treat and/or aging practices, all other requirements of AMS2772 apply.

1.1.3 Other Heat Treatment

1.1.3.1 Parts (See 8.2.2)

Made from wrought raw material shall be heat treated in accordance with AMS2770.

1.1.3.2 Castings and Parts Made from Castings

Are not covered by this specification; heat treatment of aluminum castings and parts made from such castings is covered by AMS2771.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2016 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2772G>**

1.1.3.3 Temper Conversion

Warehouses, distributors etc. shall conform to 3.8.

1.1.3.4 Procedure for Response-to-Heat-Treatment Tests

Shall conform to 3.9.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2750	Pyrometry
AMS2770	Heat Treatment of Wrought Aluminum Alloy Parts
AMS2771	Heat Treatment of Aluminum Alloy Castings
AMS-H-6088	Heat Treatment of Aluminum Alloys
ARP1962	Training and Approval of Heat-Treating Personnel
AS1990	Aluminum Alloy Tempers

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM STP15D	Manual on Presentation of Data and Control Chart Analysis
ASTM B557	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM B557M	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
ASTM B666/B666M	Identification Marking of Aluminum and Magnesium Products
ASTM G110	Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution

2.3 U.S. Government Publications

Copies of these documents are available online at <http://quicksearch.dla.mil>.

MIL-H-6088	Heat Treatment of Aluminum Alloys
MIL-STD-1537	Electrical Conductivity Test for Verification of Heat Treatment of Aluminum Alloys, Eddy Current Method

2.4 ANSI Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1 American National Standard Alloy and Temper Designation Systems for Aluminum

2.5 Battelle Publications

Available from Battelle, 505 King Ave, Columbus, OH 43201 or www.mmpds.org.

MMPDS Metallic Materials Properties Development and Standardization (MMPDS)

3. TECHNICAL REQUIREMENTS

3.1 Equipment Qualification

Before production heat treatment, each solution heat treating furnace/quench facility and each aging furnace shall be qualified by tensile and metallurgical testing (see 4.4) of heat treated samples representative of the most quench-sensitive (see 4.3.2.5.1) product to be heat treated. In addition, qualification of quench facilities shall include conformance to 4.3.

3.1.1 Sample Thickness

Tensile tests shall be representative of the thinnest and the thickest material to be heat treated; intermediate thickness samples shall be included when necessary to ensure proper production heat treatment. Thickness for metallurgical tests shall conform to 4.4.

3.1.2 Sample Locations

Samples shall be randomly positioned in simulated production loads except at least one of the tensile test samples shall be positioned at a location which exhibited a conductivity within 0.3% of the highest conductivity in a quench uniformity test.

3.1.3 Equipment Re-Qualification

Whenever any qualified equipment is changed or reworked, it shall be re-qualified unless it is known that the change or rework will not have a detrimental effect upon the properties of products. Re-qualification of quench facilities shall include conformance to 4.3.

3.2 Pyrometry

Shall conform to AMS2750 except (1) it is not applicable to furnaces used only for stress relieving or full annealing below 825 °F (441 °C), (2) recordings from instruments may be stored on magnetic or optical media providing a hard copy is producible on request, and (3) in continuous and semi-continuous furnaces, the requirements applicable to controls, instruments, and sensors in the working (soaking) zone shall also be applicable to the heating (heat-up) zone.

3.2.1 The temperature uniformity test requirements of AMS2750 shall be modified as follows:

3.2.1.1 Load Condition

Initial tests shall be performed with a typical load. Subsequent tests may be performed with any load or no load. Furnaces which have only been tested with a heavy load (in anticipation of only heat treating heavy loads) (see 8.2.9) shall not be used to heat treat light loads unless load sensors and recording instruments are employed to (1) preclude any portion of the load exceeding the maximum specified temperature on heat-up and (2) ensure soaking within the specified range for the required time.

3.2.1.2 Load Sensors

When all production loads are heavy (see 8.2.9) and a temperature uniformity test load is heavy, load sensors may be used in lieu of uniformity test sensors.