

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**SAE** AMS3568/2

REV. B

Issued 1983-07  
Revised 1993-07  
Reaffirmed 2006-01  
Stabilized 2011-08

Superseding AMS3568/2A

Foam, Polyether Urethane (EU) Elastomer, Shock Absorbing  
15 Pounds/Cubic Foot (240 kg/m<sup>3</sup>) Density

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS3568/2B>**

## 1. SCOPE:

This specification covers a chemically or mechanically expanded polyether urethane (EU) elastomeric foam material in the form of ready-to-use sheet.

### 1.1 Application:

See AMS 3568.

## 2. APPLICABLE DOCUMENTS:

See AMS 3568.

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Basic Specification:

The complete requirements for procuring the foam sheet described herein shall consist of this document and the latest issue of the basic specification, AMS 3568.

### 3.2 Material:

Shall be an elastomeric polyether urethane (EU) foam as specified in AMS 3568 formed by open or closed cells, with natural (cream) color.