



Designation: A510/A510M – 20

# Standard Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel<sup>1</sup>

This standard is issued under the fixed designation A510/A510M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification covers general requirements for carbon and alloy steel wire rods and uncoated coarse round wire in coils or straightened and cut lengths.

1.2 In case of conflict, the requirements in the purchase order, on the drawing, in the individual specification, and in this general specification shall prevail in the sequence named.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. Within the text, inch-pound units are shown in brackets.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A751 Test Methods and Practices for Chemical Analysis of Steel Products](#)

[A1040 Guide for Specifying Harmonized Standard Grade](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.03 on Steel Rod and Wire.

Current edition approved Nov. 15, 2020. Published January 2021. Originally approved in 1964. Last previous edition approved in 2018 as A510/A510M – 18. DOI: 10.1520/A0510\_A0510M-20.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Compositions for Wrought Carbon, Low-Alloy, and Alloy Steels](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E112 Test Methods for Determining Average Grain Size](#)

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *coarse round wire, n*—from 0.90 to 25 mm [0.035 to 0.999 in.] in diameter, inclusive, wire that is produced from hot-rolled wire rods or hot-rolled coiled bars by one or more cold reductions primarily for the purpose of obtaining a desired size with dimensional accuracy, surface finish, and mechanical properties; by varying the amount of cold reduction and other wire mill practices, including thermal treatment, a wide diversity of mechanical properties and finishes are made available.

3.1.1.1 *Discussion*—Coarse round wire is designated by Steel Wire Gauge numbers, common fractions, or decimal parts of an inch, or metric equivalents. The Steel Wire Gauge system is shown in [Table 1](#). Since the many gauge systems in use may cause confusion, the purchaser is encouraged to specify wire diameters in inches, decimal parts, or metric equivalents.

3.1.2 *straightened and cut wire, n*—wire that is produced from coils of wire by means of special machinery which straightens the wire and cuts it to a specified length.

3.1.2.1 *Discussion*—The straightening operation may alter the mechanical properties of the wire, especially the tensile strength. The straightening operation may also induce changes in the diameter of the wire. The extent of the changes in the properties of the wire after cold straightening depends upon the kind of wire and also on the normal variations in the adjustments of the straightening equipment. It is therefore not possible to forecast the properties of straightened and cut wire and each kind of wire needs individual consideration. In most cases, the end use of straightened and cut wire is not seriously influenced by these changes.

3.1.3 *wire rods, n*—rods that are hot rolled from billets to an approximate round cross section into coils of one continuous length; rods are intended primarily for the manufacture of wire.

3.1.3.1 *Discussion*—Common rod sizes from 5.5 to 19 mm [ $7/32$  to  $3/4$  in.] in diameter, inclusive, are designated in [Table 2](#).

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Steel Wire Gauge<sup>A</sup>**

Gauge No.	Decimal Equivalent, mm	Decimal Equivalent, in.	Gauge No.	Decimal Equivalent, mm	Decimal Equivalent, in.
7/0	12.45	0.490	9	3.76	0.148*
6/0	11.73	0.462*	9½	3.61	0.142
5/0	10.92	0.430*	10	3.43	0.135
4/0	10.01	0.394*	10½	3.25	0.128
3/0	9.19	0.362*	11	3.05	0.120*
2/0	8.41	0.331	11½	2.87	0.113
1/0	7.77	0.306	12	2.69	0.106*
1	7.19	0.283	12½	2.51	0.099
1½	6.91	0.272	13	2.34	0.092*
2	6.65	0.262*	13½	2.18	0.086
2½	6.43	0.253	14	2.03	0.080
3	6.20	0.244*	14½	1.93	0.076
3½	5.94	0.234	15	1.83	0.072
4	5.72	0.225*	15½	1.70	0.067
4½	5.49	0.216	16	1.57	0.062*
5	5.26	0.207	16½	1.47	0.058
5½	5.08	0.200	17	1.37	0.054
6	4.88	0.192	17½	1.30	0.051
6½	4.67	0.184	18	1.22	0.048*
7	4.50	0.177	18½	1.12	0.044
7½	4.32	0.170	19	1.04	0.041
8	4.11	0.162	19½	0.97	0.038
8½	3.94	0.155	20	0.89	0.035*

<sup>A</sup> The steel wire gauge outlined in this table has been taken from the original Washburn and Moen Gauge chart. In 20 gauge and coarser, inch sizes originally quoted to four decimal equivalent places have been rounded to three decimal places in accordance with rounding procedures of Practice E29. All rounded U.S. customary inch size values are indicated by an asterisk. SI unit decimal equivalents are converted from inch size decimal equivalents.

3.1.4 *direct-drawn wire, n*—wire that is produced from hot-rolled wire rods or hot-rolled coiled bars to finished wire through one or more cold reductions without annealing or patenting heat treatment.

#### 4. Ordering Information

4.1 Orders for hot-rolled wire rods under this specification should include the following information:

- 4.1.1 Quantity (mass or weight),
- 4.1.2 Name of material (wire rods),
- 4.1.3 Diameter (Section 3),
- 4.1.4 Chemical composition grade no. (Section 6),
- 4.1.5 Packaging (Section 15),
- 4.1.6 ASTM designation and date of issue, and
- 4.1.7 The purchaser shall have the option to specify additional requirements, including but not limited to:
  - 4.1.7.1 Requirements for certifications, heat analysis, or test reports (Sections 6 and 14),
  - 4.1.7.2 Mechanical property requirements (Sections 6 and 8),
  - 4.1.7.3 Freedom from welds (Section 10),
  - 4.1.7.4 Special packing, marking, and loading requirements (Section 15),
  - 4.1.7.5 Additional processing, if any, and
  - 4.1.7.6 Other special requirements, if any.

NOTE 1—A typical ordering description is as follows: 50 000 kg steel wire rods, 5.5 mm, grade G10100 in approximately 600 kg coils for metric orders to ASTM A510/A510M dated \_\_\_\_\_, or 100 000 lb wire rods, 7/32 in., grade 1010 in approximately 1000 lb coils to ASTM A510/A510M dated \_\_\_\_\_.

4.2 Orders for coarse round wire under this specification should include the following information:

- 4.2.1 Quantity (mass or weight),
- 4.2.2 Name of material (uncoated carbon steel wire or alloy steel wire),
- 4.2.3 Diameter (Section 3),
- 4.2.4 Length (straightened and cut only, Section 9)
- 4.2.5 Chemical composition (Section 6),
- 4.2.6 Packaging (Section 15),
- 4.2.7 ASTM designation and date of issue, and
- 4.2.8 The purchaser shall have the option to specify additional requirements, including but not limited to:
  - 4.2.8.1 Requirements for certifications, heat analysis, or test reports (Sections 6 and 14),
  - 4.2.8.2 Mechanical property requirements (Sections 6 and 8),
  - 4.2.8.3 Freedom from welds made prior to or during wire drawing, or marking of welds (Section 10),
  - 4.2.8.4 Special packing, marking, and loading requirements (Section 15),
  - 4.2.8.5 Additional processing, if any, and
  - 4.2.8.6 Other special requirements, if any.

NOTE 2—A typical ordering description is as follows: 15 000 kg uncoated carbon or alloy steel wire 3.8 mm in diameter, grade G10080 in 1000 kg coils on tubular carriers to ASTM A510/A510M dated \_\_\_\_\_, or 2500 pieces carbon or alloy steel wire, 9.5 mm diameter, straightened and cut, 0.76 m, grade G10500, in 25-piece bundles on pallets to ASTM A510/A510M dated \_\_\_\_\_.

For inch-pound units, a typical ordering description is as follows: 40 000 lb uncoated carbon or alloy steel wire, 0.148 in. (9 ga.) diameter,

**TABLE 2 Common Sizes of Wire Rods<sup>A</sup>**

SI Units			
Diameter, mm			
5.5		12.5	
6		13	
6.5		13.5	
7		14	
7.5		14.5	
8		15	
8.5		15.5	
9		16	
9.5		16.5	
10		17	
10.5		17.5	
11		18	
11.5		18.5	
12		19	
Inch-Pound Units			
Inch Fraction	Decimal Equivalent, in.	Inch Fraction	Decimal Equivalent, in.
7/32	0.219	31/64	0.484
15/64	0.234	1/2	0.500
1/4	0.250	33/64	0.516
17/64	0.266	17/32	0.531
9/32	0.281	35/64	0.547
19/64	0.297	9/16	0.562
5/16	0.312	37/64	0.578
21/64	0.328	19/32	0.594
11/32	0.344	39/64	0.609
23/64	0.359	5/8	0.625
3/8	0.375	41/64	0.641
25/64	0.391	21/32	0.656
13/32	0.406	43/64	0.672
27/64	0.422	11/16	0.688
7/16	0.438	45/64	0.703
29/64	0.453	23/32	0.719
15/32	0.469	47/64	0.734
		3/4	0.750

<sup>A</sup> Rounded off to three decimal places in decimal equivalents in accordance with procedures outlined in Practice E29.

**TABLE 3 Permissible Variations for Product Analysis of Carbon Steel**

Element	Limit, or Maximum of Specified Range, %	Tolerance	
		Over Maximum Limit, %	Under Minimum Limit, %
Carbon	0.25 and under	0.02	0.02
	over 0.25 to 0.55, incl	0.03	0.03
	over 0.55	0.04	0.04
Manganese	0.90 and under	0.03	0.03
	over 0.90 to 1.65, incl	0.06	0.06
Phosphorus	to 0.040, incl	0.008	...
Sulfur	to 0.060, incl	0.008	...
Silicon	0.35 and under	0.02	0.02
	over 0.35 to 0.60, incl	0.05	0.05
Copper <sup>A</sup>	under minimum only	...	0.02
Lead <sup>B</sup>	0.15 to 0.35, incl	0.03	0.03

<sup>A</sup> Product analysis permissible variations for copper apply only when the amount of copper is specified or required. Copper bearing steels typically specify 0.20 % min copper.

<sup>B</sup> Product analysis permissible variations for lead applies both over and under to a specified range of 0.15 to 0.35 %.

strengths within the allowable carbon range. The Mn, P, and S limits for carbon steel wire rods are normally specified according to Guide A1040.

**6.2 Boron Additions to Control Strain Aging Behavior—**Intentional additions of boron to low carbon steels for the purpose of controlling strain aging behavior during wire drawing is permissible only with the agreement of the purchaser. In such cases, the boron content shall be reported in either a material test report or certification.

**6.2.1** For steels that do not have intentional boron additions for hardenability or for control of strain aging behavior, the boron content will not normally exceed 0.0008 %.

**6.3 Heat Analysis (Formerly Ladle Analysis)—**An analysis of each heat shall be made to determine the percentage of the elements specified. The analysis shall be made from a test sample, preferably taken during the pouring of the heat. The chemical composition thus determined shall be reported, if required, to the purchaser, or his representative. Reporting of significant figures and rounding shall be in accordance with Test Methods, Practices, and Terminology A751.

**6.4 Product Analysis (Formerly Check Analysis)—**A product analysis may be made by the purchaser. The purpose of the product analysis is to verify that the chemical composition is within specified limits for each element, including applicable permissible variations in product analysis. The results of analyses taken from different pieces of a heat may differ within permissible limits from each other and from the heat analysis. Table 3 shows the permissible variations for product analysis of carbon steel. Table 4 shows the permissible variations for product analysis of alloy steel. The results of the product analysis obtained, except lead, shall not vary both above and below the permissible limits.

**6.4.1** Rimmed or capped steels are characterized by a lack of uniformity in their chemical composition, especially for the

grade 10080 in 500 lb coils on tubular carriers to ASTM A510/A510M dated \_\_\_\_\_, or

2500 pieces, carbon or alloy steel wire, 0.375 in. diameter, straightened and cut 29½ in., grade 1015, in 25 piece bundles on pallets to ASTM A510/A510M dated \_\_\_\_\_.

## 5. Manufacture

**5.1** The steel shall be made by any commercially accepted steel making process. The steel may be either ingot cast or strand cast.

## 6. Chemical Composition

**6.1** The chemical composition for steel under this specification shall conform to the requirements set forth in the purchase order. Chemical compositions are specified by ranges or limits for carbon and other elements. The grades commonly specified for carbon and alloy steel wire rods and coarse round wire are designated in Guide A1040. Other grades not designated in Guide A1040 may be specified.

**6.1.1** For wire rods intended for direct-drawn wire, it is common practice to specify a range of tensile strength. If chemistry ranges are also specified, due consideration should be taken to ensure that the producer can achieve the required