



AEROSPACE MATERIAL SPECIFICATION	AMS5528™	REV. J
	Issued	1953-12
	Revised	2019-04
Superseding AMS5528H		
Steel, Corrosion-Resistant, Sheet, Strip, and Plate 17Cr - 7.1Ni - 1.1Al Solution Heat Treated, Precipitation Hardenable (Composition similar to UNS S17700)		

RATIONALE

AMS5528J prohibits unauthorized exceptions (3.7), revises chemical analysis standards (3.1), solution heat treatment (3.3), properties (3.4.3), reports (4.4) and identification (5.1.1), and results from a Five-Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate 0.005 inch (0.13 mm) and above in nominal thickness (see 8.6).

1.2 Application

These products have been used typically for parts requiring corrosion resistance and high strength up to 600 °F (316 °C), and where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

- AMS2242 Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- AMS2248 Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2019 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS5528J>

AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications
AS4194	Sheet and Strip Surface Finish Nomenclature

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A370	Mechanical Testing of Steel Products
ASTM A480/A480M	Flat Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM A751	Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
ASTM E140	Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness
ASTM E290	Bend Test of Materials for Ductility

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.09
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	16.00	18.00
Nickel	6.50	7.75
Aluminum	0.75	1.50

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance in accordance with ASTM A480/A480M and AS4194 comparable to 3.2.1.1 and 3.2.1.2 as applicable.