



Designation: D6938 – 17a

Standard Test Methods for In-Place Density and Water Content of Soil and Soil-Aggregate by Nuclear Methods (Shallow Depth)¹

This standard is issued under the fixed designation D6938; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method describes the procedures for measuring in-place density and moisture of soil and soil-aggregate by use of nuclear equipment (hereafter referred to as “gauge”). The density of the material may be measured by direct transmission, backscatter, or backscatter/air-gap ratio methods. Measurements for water (moisture) content are taken at the surface in backscatter mode regardless of the mode being used for density.

1.1.1 For limitations see Section 5 on Interferences.

1.2 The total or wet density of soil and soil-aggregate is measured by the attenuation of gamma radiation where, in direct transmission, the source is placed at a known depth up to 300 mm (12 in.) and the detector(s) remains on the surface (some gauges may reverse this orientation); or in backscatter or backscatter/air-gap the source and detector(s) both remain on the surface.

1.2.1 The density of the test sample in mass per unit volume is calculated by comparing the detected rate of gamma radiation with previously established calibration data.

1.2.2 The dry density of the test sample is obtained by subtracting the water mass per unit volume from the test sample wet density (Section 11). Most gauges display this value directly.

1.3 The gauge is calibrated to read the water mass per unit volume of soil or soil-aggregate. When divided by the density of water and then multiplied by 100, the water mass per unit volume is equivalent to the volumetric water content. The water mass per unit volume is determined by the thermalizing or slowing of fast neutrons by hydrogen, a component of water. The neutron source and the thermal neutron detector are both located at the surface of the material being tested. The water content most prevalent in engineering and construction activities is known as the gravimetric water content, w , and is the

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.08 on Special and Construction Control Tests.

Current edition approved Nov. 1, 2017. Published December 2017. Originally approved in 2006. Last previous edition approved in 2017 as D6938–17. DOI: 10.1520/D6938-17A.

ratio of the mass of the water in pore spaces to the total mass of solids, expressed as a percentage.

1.4 Two alternative procedures are provided.

1.4.1 *Procedure A* describes the direct transmission method in which the probe extends through the base of the gauge into a pre-formed hole to a desired depth. The direct transmission is the preferred method.

1.4.2 *Procedure B* involves the use of a dedicated backscatter gauge or the probe in the backscatter position. This places the gamma and neutron sources and the detectors in the same plane.

1.4.3 Mark the test area to allow the placement of the gauge over the test site and to align the probe to the hole.

1.5 *SI Units*—The values stated in SI units are to be regarded as the standard. The values in inch-pound units (ft – lb units) are provided for information only.

1.6 All observed and calculated values shall conform to the guide for significant digits and rounding established in Practice D6026.

1.6.1 The procedures used to specify how data are collected, recorded, and calculated in this standard are regarded as the industry standard. In addition, they are representative of the significant digits that should generally be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user’s objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of this standard to consider significant digits used in analysis methods for engineering design.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

*A Summary of Changes section appears at the end of this standard

2. Referenced Documents

2.1 ASTM Standards:²

- D653** Terminology Relating to Soil, Rock, and Contained Fluids
- D698** Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft³ (600 kN-m/m³))
- D1556** Test Method for Density and Unit Weight of Soil in Place by Sand-Cone Method
- D1557** Test Methods for Laboratory Compaction Characteristics of Soil Using Modified Effort (56,000 ft-lbf/ft³ (2,700 kN-m/m³))
- D2167** Test Method for Density and Unit Weight of Soil in Place by the Rubber Balloon Method
- D2487** Practice for Classification of Soils for Engineering Purposes (Unified Soil Classification System)
- D2488** Practice for Description and Identification of Soils (Visual-Manual Procedures)
- D2216** Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass
- D2937** Test Method for Density of Soil in Place by the Drive-Cylinder Method
- D3740** Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction
- D4253** Test Methods for Maximum Index Density and Unit Weight of Soils Using a Vibratory Table
- D4254** Test Methods for Minimum Index Density and Unit Weight of Soils and Calculation of Relative Density
- D4643** Test Method for Determination of Water Content of Soil and Rock by Microwave Oven Heating
- D4718** Practice for Correction of Unit Weight and Water Content for Soils Containing Oversize Particles
- D4944** Test Method for Field Determination of Water (Moisture) Content of Soil by the Calcium Carbide Gas Pressure Tester
- D4959** Test Method for Determination of Water Content of Soil By Direct Heating
- D6026** Practice for Using Significant Digits in Geotechnical Data
- D7013** Guide for Nuclear Surface Moisture and Density Gauge Calibration Facility Setup
- D7759** Guide for Nuclear Surface Moisture and Density Gauge Calibration

3. Terminology

3.1 *Definitions*—See Terminology **D653** for general definitions.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *nuclear gauge*—a device containing one or more radioactive sources used to measure certain properties of soil and soil-aggregates.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.2 *gamma (radiation) source*—a sealed source of radioactive material that emits gamma radiation as it decays.

3.2.3 *neutron (radiation) source*—a sealed source of radioactive material that emits neutron radiation as it decays.

3.2.4 *Compton scattering*—the interaction between a gamma ray (photon) and an orbital electron where the gamma ray loses energy and rebounds in a different direction.

3.2.5 *detector*—a device to detect and measure radiation.

3.2.6 *gravimetric water content*—same as water content (as defined in Terminology **D653**), a nomenclature used in some scientific fields to differentiate it from volumetric water content.

3.2.7 *thermalization*—the process of “slowing down” fast neutrons by collisions with light-weight atoms, such as hydrogen.

3.2.8 *volumetric water content*—the volume of water as a percent of the total volume of soil or rock material.

3.2.9 *test count, n*—the measured output of a detector for a specific type of radiation for a given test.

3.2.10 *prepared blocks*—blocks prepared of soil, solid rock, concrete, and engineered materials, that have characteristics of various degrees of reproducible uniformity.

4. Significance and Use

4.1 The test method described is useful as a rapid, nondestructive technique for in-place measurements of wet density and water content of soil and soil-aggregate and the determination of dry density.

4.2 The test method is used for quality control and acceptance testing of compacted soil and soil-aggregate mixtures as used in construction and also for research and development. The nondestructive nature allows repetitive measurements at a single test location and statistical analysis of the results.

4.3 *Density*—The fundamental assumptions inherent in the methods are that Compton scattering is the dominant interaction and that the material is homogeneous.

4.4 *Water Content*—The fundamental assumptions inherent in the test method are that the hydrogen ions present in the soil or soil-aggregate are in the form of water as defined by the water content derived from Test Methods **D2216**, and that the material is homogeneous. (See **5.2**)

NOTE 1—The quality of the result produced by this standard test method is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice **D3740** are generally considered capable of competent and objective testing/sampling/inspection, and the like. Users of this standard are cautioned that compliance with Practice **D3740** does not in itself ensure reliable results. Reliable results depend on many factors; Practice **D3740** provides a means of evaluating some of those factors.

5. Interferences

5.1 *In-Place Density Interferences*

5.1.1 Measurements may be affected by the chemical composition of the material being tested.

5.1.2 Measurements may be affected by non-homogeneous soils and surface texture (see **10.2**). Excessive voids in the

prepared test surface beneath the gauge can cause density measurements that are lower than the actual soil density. Excessive use of fill material to compensate for these voids may likewise cause biased density measurements, or biased water content measurements, or both.

5.1.3 Measurements in the Backscatter Mode are influenced more by the density and water content of the material in proximity to the surface.

5.1.4 Measurements in the Direct Transmission mode are an average of the density from the bottom of the probe in the soil or soil aggregate back up to the surface of the gauge.

5.1.5 Gravel particles or large voids in the source-detector path may cause higher or lower density measurements. Where lack of uniformity in the soil due to layering, aggregate or voids is suspected, the test site should be excavated and visually examined to determine whether the test material is representative of the in situ material in general and whether an oversize correction is required in accordance with Practice **D4718**.

5.1.6 Oversize particles or large voids in the source-detector path may cause higher or lower density measurements. Where lack of uniformity in the soil due to layering, aggregate or voids is suspected, the test site should be excavated and visually examined to determine if the test material is representative of the in situ material in general and if an oversize correction is required in accordance with Practice **D4718**.

5.1.7 The measured volume is approximately 0.0028 m³ (0.10 ft³) for the Backscatter Mode and 0.0057 m³ (0.20 ft³) for the Direct Transmission Mode when the test depth is 150 mm (6 in.). The actual measured volume is indeterminate and varies with the apparatus and the density of the material.

5.1.8 Other radioactive sources must not be within 9 m (30 ft) of equipment in operation.

5.2 *In-Place Water (Moisture) Content Interferences*

5.2.1 The chemical composition of the material being tested can affect the measurement and adjustments may be necessary (see Section 10.6). Hydrogen in forms other than water and carbon will cause measurements in excess of the true value. Some chemical elements such as boron, chlorine, and cadmium will cause measurements lower than the true value.

5.2.2 The water content measured by this test method is not necessarily the average water content within the volume of the sample involved in the measurement. Since this measurement is by backscatter in all cases, the value is biased by the water content of the material closest to the surface. The volume of soil and soil-aggregate represented in the measurement is indeterminate and will vary with the water content of the material. In general, the greater the water content of the material, the smaller the volume involved in the measurement. Approximately 50 % of the typical measurement results from the water content of the upper 50 to 75 mm (2 to 3 in.).

5.2.3 Other neutron sources must not be within 9 m (30 ft) of equipment in operation.

6. Apparatus

6.1 *Nuclear Density / Moisture Gauge*—While exact details of construction of the apparatus may vary, the system shall consist of:

6.1.1 *Gamma Source*—A sealed source of high-energy gamma radiation such as cesium or radium.

6.1.2 *Gamma Detector*—Any type of gamma detector such as a Geiger-Mueller tube(s).

6.1.3 *Fast Neutron Source*—A sealed mixture of a radioactive material such as americium, radium and a target material such as beryllium, or a neutron emitter such as californium-252.

6.1.4 *Slow Neutron Detector*—Any type of slow neutron detector such as boron trifluoride or helium-3 proportional counter.

6.2 *Reference Standard*—A block of material used for checking instrument operation, correction of source decay, and to establish conditions for a reproducible reference count rate.

6.3 *Site Preparation Device*—A plate, straightedge, or other suitable leveling tool that may be used for planing the test site to the required smoothness, and in the Direct Transmission Method, guiding the drive pin to prepare a perpendicular hole.

6.4 *Drive Pin*—A pin of slightly larger diameter than the probe in the Direct Transmission Instrument used to prepare a hole in the test site for inserting the probe.

6.4.1 *Drive Pin Guide*—A fixture that keeps the drive pin perpendicular to the test site. Generally part of the site preparation device.

6.5 *Hammer*—Heavy enough to drive the pin to the required depth without undue distortion of the hole.

6.6 *Drive Pin Extractor*—A tool that may be used to remove the drive pin in a vertical direction so that the pin will not distort the hole in the extraction process.

6.7 *Slide Hammer*, with a drive pin attached, may also be used both to prepare a hole in the material to be tested and to extract the pin without distortion to the hole.

6.8 *Probe*, a slender, elongated device, part of the gauge, that is inserted into the soil under measurement by the gauge. This device may contain either a radioactive source, a radiation detection device, or both. Probes containing only a radioactive source are commonly referred to as “source rods.”

7. Hazards

7.1 These gauges utilize radioactive materials that may be hazardous to the health of the users unless proper precautions are taken. Users of these gauges must become familiar with applicable safety procedures and government regulations.

7.2 Effective user instructions, together with routine safety procedures and knowledge of and compliance with Regulatory Requirements, are a mandatory part of the operation and storage of these gauges.

8. Calibration

8.1 Gauge calibration shall be performed in accordance with Guides **D7013** and **D7759**.

9. Standardization

9.1 Nuclear moisture density gauges are subject to long-term aging of the radioactive sources, which may change the