



Designation: E1067/E1067M – 18

## Standard Practice for Acoustic Emission Examination of Fiberglass Reinforced Plastic Resin (FRP) Tanks/Vessels<sup>1</sup>

This standard is issued under the fixed designation E1067/E1067M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This practice covers acoustic emission (AE) examination or monitoring of fiberglass-reinforced plastic (FRP) tanks-vessels (equipment) under pressure or vacuum to determine structural integrity.

1.2 This practice is limited to tanks-vessels designed to operate at an internal pressure no greater than 1.73 MPa absolute [250 psia, 17.3 bar] above the static pressure due to the internal contents. It is also applicable for tanks-vessels designed for vacuum service with differential pressure levels between 0 and 0.10 MPa [0 and 14.5 psi, 1 bar].

1.3 This practice is limited to tanks-vessels with glass contents greater than 15 % by weight.

1.4 This practice applies to examinations of new and in-service equipment.

1.5 *Units*—The values stated in either SI units or inch-pound units are to be regarded as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.04 on Acoustic Emission Method.

Current edition approved Feb. 1, 2018. Published February 2018. Originally approved in 1985. Last previous edition approved in 2011 as E1067/E1067M – 11. DOI: 10.1520/E1067-18.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- D883 Terminology Relating to Plastics
- D5436 Specification for Cast Poly(Methyl Methacrylate) Plastic Rods, Tubes, and Shapes
- E543 Specification for Agencies Performing Nondestructive Testing
- E650 Guide for Mounting Piezoelectric Acoustic Emission Sensors
- E750 Practice for Characterizing Acoustic Emission Instrumentation
- E1106 Test Method for Primary Calibration of Acoustic Emission Sensors
- E1316 Terminology for Nondestructive Examinations
- E2075 Practice for Verifying the Consistency of AE-Sensor Response Using an Acrylic Rod
- E1781 Practice for Secondary Calibration of Acoustic Emission Sensors
- E2374 Guide for Acoustic Emission System Performance Verification

#### 2.2 ANSI/ASNT Standards:

- SNT-TC-1A Recommended Practice for Nondestructive Testing Personnel Qualification and Certification<sup>3</sup>
- ANSI/ASNT CP-189 Standard for Qualification and Certification of Nondestructive Testing Personnel<sup>3</sup>

#### 2.3 AIA Standard:

- NAS-410 Certification and Qualification of Nondestructive Personnel (Quality Assurance Committee)<sup>4</sup>

#### 2.4 ISO Standard:

- ISO 9712 Non-Destructive Testing—Qualification and Certification of NDT Personnel

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

<sup>4</sup> Available from Aerospace Industries Association of America, Inc. (AIA), 1000 Wilson Blvd., Suite 1700, Arlington, VA 22209-3928, <http://www.aia-aerospace.org>.

\*A Summary of Changes section appears at the end of this standard

### 3. Terminology

3.1 Complete definitions of terms related to plastics and acoustic emission will be found in Terminology [D883](#) and [E1316](#).

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *FRP*—fiberglass reinforced plastic, a glass-fiber polymer composite with certain mechanical properties superior to those of the base resin.

3.2.2 *operating pressure*—the pressure at the top of a vessel at which it normally operates. It shall not exceed the design pressure and it is usually kept at a suitable level below the setting of the pressure-relieving devices to prevent their frequent opening.

3.2.3 *pressure, design*—the pressure used in design to determine the required minimum thicknesses and minimum mechanical properties.

3.2.4 *processor*—a circuit that analyzes AE waveforms. (See Section [7](#) and [A1.8](#).)

3.2.5 *summing amplifier (summer, mixer)*—an operational amplifier that produces an output signal equal to a weighted sum of the input signals.

3.2.6 *zone*—the area surrounding a sensor from which AE can be detected by that sensor.

### 4. Summary of Practice

4.1 This practice consists of subjecting equipment to increasing pressure or vacuum while monitoring with sensors that are sensitive to acoustic emission (transient stress waves) caused by growing flaws. The instrumentation and techniques for sensing and analyzing AE data are described.

4.2 This practice provides guidelines to determine the location and severity of structural flaws in FRP equipment.

4.3 This practice provides guidelines for AE examination of FRP equipment within the pressure range stated in [1.2](#). Maximum test pressure (or vacuum) for an FRP vessel will be determined upon agreement among user, manufacturer, or test agency, or a combination thereof. Pressure vessels will normally be tested to  $1.1 \times$  operating pressure. Atmospheric storage vessels and vacuum vessels will normally be tested under maximum operating conditions. Vessels will normally be tested at ambient temperature. In the case of elevated operating temperature the test may be performed either at operating or ambient temperature. The test temperature must be below the glass transition temperature of the resin.

### 5. Significance and Use

5.1 The AE examination method detects damage in FRP equipment. The damage mechanisms that are detected in FRP are as follows: resin cracking, fiber debonding, fiber pullout, fiber breakage, delamination, and bond failure in assembled joints (for example, nozzles, manways, and so forth). Flaws in unstressed areas and flaws that are structurally insignificant will not generate AE.

5.2 This practice is convenient for on-line use under operating stress to determine structural integrity of in-service equipment usually with minimal process disruption.

5.3 Indications located with AE should be examined by other techniques; for example, visual, ultrasound, dye penetrant, and so forth, and may be repaired and tested as appropriate. Repair procedure recommendations are outside the scope of this practice.

### 6. Basis of Application

6.1 The following items are subject to contractual agreement between the parties using or referencing this practice:

#### 6.2 Personnel Qualification:

6.2.1 If specified in the contractual agreement, personnel performing examinations to this standard shall be qualified in accordance with a nationally or internationally recognized NDT personnel qualification practice or standard such as ANSI/ASNT-CP-189, SNT-TC-1A, NAS-410, ISO 9712, or a similar document and certified by the employer or certifying agency, as applicable. The practice or standard used and its applicable revision shall be identified in the contractual agreement between the using parties.

6.3 *Qualification of Nondestructive Agencies*—If specified in the contractual agreement, NDT agencies shall be qualified and evaluated as described in Practice [E543](#). The applicable edition of Practice [E543](#) shall be specified in the contractual agreement.

6.4 *Procedures and Techniques*—The procedures and techniques to be utilized shall be as specified in the contractual agreement.

6.5 *Surface Preparation*—The pre-examination surface preparation criteria shall be in accordance with [9.2](#) unless otherwise specified.

6.6 *Reporting Criteria/Acceptance Criteria*—Reporting criteria for the examination results shall be in accordance with Section [13](#) unless otherwise specified. Since acceptance criteria are not specified in this practice, they shall be specified in the contractual agreement.

### 7. Instrumentation

7.1 The AE instrumentation consists of sensors, signal processors, and recording equipment. Additional information on AE instrumentation can be found in Practice [E750](#).

7.2 Instrumentation shall be capable of recording AE hits, signal strength and hit duration and have sufficient channels to localize AE sources in real time. It may incorporate (as an option) peak-amplitude detection for each input channel or for groups of channels. Hit detection is required for each channel. An AE hit amplitude measurement is recommended for sensitivity verification (see [Annex A2](#)). Amplitude distributions are recommended for flaw characterization. It is preferred that AE instrumentation acquire and record duration hit and amplitude information on a per channel basis. The AE instrumentation is further described in [Annex A1](#).

7.3 Capability for measuring parameters such as time and pressure shall be provided. The pressure-vacuum in the vessel should be continuously monitored to an accuracy of  $\pm 2\%$  of the maximum test value.

7.4 *Lockouts and Guard Sensors*—These techniques shall not be used.

7.5 *Instrument Displays*— The instrumentation shall be capable of providing the following real time displays:

7.5.1 *Bar Chart by Channel of Cumulative Signal Strength*—Enables the examiner to identify which channel is recording the most data.

7.5.2 *Amplitude per Hit Versus Time*—Provides the examiner with early warning of an impending failure (see Reference (1)).

7.5.3 *Duration per Hit Versus Time*—Useful for identifying rubbing or sliding (see Reference (1)).

7.5.4 *Log Duration (or Counts) per Hit Versus Amplitude per Hit*—Helps the examiner determine the presence of false emission signals (see Reference (1)).

7.5.5 *Cumulative Signal Strength per Channel Versus Time*—Useful for identifying certain types of instrument malfunctions; for example, continuous electronic noise will produce a characteristically steady rise with time, unlike the stepwise rise associated with natural AE.

7.6 *Cumulative Amplitude Distribution*, or a tabular listing by channel number of total hits equal to and greater than defined amplitude values. Tabular amplitude values shall be in increments of not greater than 5 dB and shall be for at least a 35 dB range beginning at the threshold. These displays are used to provide warning of significant fiber breakage of the type that can lead to sudden structural failure. The displays also provide information about the micromechanisms giving rise to the emission and warn of potential instrument malfunction.

## 8. Examination Preparations

8.1 *Safety*—All plant safety requirements unique to the examination location shall be met.

8.1.1 Protective clothing and equipment that is normally required in the area in which the examination is being conducted shall be worn.

8.1.2 A fire permit may be needed to use the electronic instrumentation.

8.1.3 Precautions shall be taken to protect against the consequences of catastrophic failure when pressure testing, for example, flying debris and impact of escaping liquid. Pressurizing under pneumatic conditions is not recommended except when normal service loads include either a superposed gas pressure or gas pressure only. Care shall be taken to avoid overstressing the lower section of the vessel when liquid test loads are used to simulate operating gas pressures.

8.1.4 Special safety precautions shall be taken when pneumatic testing is required; for example, safety valves, and so forth.

8.2 *Vessel Conditioning*—The operating conditions for vessels that have been stressed previously shall be reduced prior to examining in accordance with the schedule shown in **Table 1**. **Table 1** is used as follows. The planned reduced pressure is expressed as a percentage of the maximum operating pressure or load in the vessel during the past year (the latter must be known in order to conduct the AE examination properly). Looking for this percentage in the first column of **Table 1**, the

**TABLE 1 Requirements for Reduced Operating Pressure-Load Immediately Prior to Examining**

% of Operating Pressure or Load, or Both	Time at Reduced Pressure or Load, or Both
10 or less	12 h
20	18 h
30	30 h
40	2 days
50	4 days
60	7 days

corresponding row in the second column shows the time that must be spent at the reduced pressure, to condition the vessel prior to making an AE test. When the percentage falls between two values in the first column, the higher value is used.

8.3 *Vessel Stressing*—Arrangements should be made to stress the vessel as prescribed in 4.3. The stress rate shall be sufficient to expedite the examination with minimum extraneous noise. Holding stress levels is a key aspect of an acoustic emission examination. Accordingly, provision must be made for holding the pressure-load at designated check points.

8.3.1 *Atmospheric Tanks*—Process liquid is the preferred fill medium for atmospheric tanks. If water must replace the process liquid, the designer and user shall be in agreement on the procedure to achieve acceptable stress levels.

8.3.2 *Vacuum-Tank Stressing*—A controllable vacuum-pump system is required for vacuum tanks.

8.3.3 *Pressure-Vessel Stressing*—Water is the preferred medium for pressure tanks. Safe means for hydraulically increasing the pressure under controlled conditions shall be provided.

8.4 *Tank Support*—The tank shall be examined in its operating position and supported in a manner consistent with good installation practice. Flat-bottomed tanks examined in other than the intended location shall be mounted on a pad (for example, rubber on a concrete base or equivalent) to reduce structure-borne noise between the tank and base.

8.5 *Environmental*—The normal minimum acceptable vessel wall temperature is 4°C [40°F].

8.6 *Noise Reduction*—Noise sources in the examination frequency and amplitude range, such as rain, spargers, and foreign objects contacting the tank, must be minimized since they mask the AE signals emanating from the structure. The inlet should be at the lowest nozzle or as near to the bottom of the vessel as possible, that is, below the liquid level. Liquid falling, swirling, or splashing can invalidate data obtained during the filling phase. However, this needs to be addressed by appropriate data filtering, not by turning off data acquisition during the filling phase altogether.

8.7 *Power Supply*—A stable grounded power supply, meeting the specification of the instrumentation, is required at the examination site.

8.8 *Instrumentation Settings*—Settings will be determined as described in **Annex A2**.

## 9. Sensors

9.1 *Sensor Mounting*—Refer to Practice **E650** for additional information on sensor mounting. Location and spacing of the