



Designation: C927 – 80 (Reapproved 2019)^{ε1}

Standard Test Method for Lead and Cadmium Extracted from the Lip and Rim Area of Glass Tumblers Externally Decorated with Ceramic Glass Enamels¹

This standard is issued under the fixed designation C927; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Eq 1 and 2 were revised editorially in February 2019.

1. Scope

1.1 This test method covers the determination of lead and cadmium extracted by acetic acid from the lip and rim area of glassware used for drinking and which is exteriorly decorated with ceramic glass enamels. The procedure of extraction may be expected to accelerate the release of lead and cadmium from the decorated area and to serve, therefore, as a severe test that is unlikely to be matched under the actual conditions of usage of such glassware. This test method is specific for lead and cadmium.

NOTE 1—For additional information see Test Method C738.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.10 on Glass Decoration. It was developed jointly by ASTM Committee C-14 and C-21 on Ceramic Whitewares and Related Products, the Society of Glass Decorators A-20 Subcommittee on Ceramic Enamelled Decorated Glass Tumblers, and an Inter-agency Task Force consisting of FDA, EPA, and CPSC of the U.S. Government.

Current edition approved Feb. 1, 2019. Published February 2019. Originally approved in 1980. Last previous edition approved in 2014 as C927 – 80 (2014). DOI: 10.1520/C0927-80R19E01.

2. Referenced Documents

2.1 *ASTM Standards*:²

C738 Test Method for Lead and Cadmium Extracted from Glazed Ceramic Surfaces

3. Terminology

3.1 *Definitions*:

3.1.1 *ceramic glass decorations*—ceramic glass enamels fused to glassware at temperatures above 425°C (800°F) to produce a decoration.

3.1.2 *ceramic glass enamels (also ceramic enamels or glass enamels)*—predominately colored, silicate glass fluxes used to decorate glassware.

3.1.3 *lip and rim area*—that part of a drinking vessel which extends 20 mm below the rim on the outside of the specimen.

4. Summary of Test Method

4.1 Lead and cadmium are extracted from the lip and rim area of the article under test by leaching with a 4 % acetic acid solution at 20 to 24°C (68 to 75°F) for 24 h and are measured by atomic absorption spectrophotometry using specific hollow cathode or electrodeless discharge lamps for lead and cadmium respectively. Results are reported as micrograms per millilitre (ppm) extracted relative to the internal volume of the glass article.

5. Significance and Use

5.1 The heavy metals, lead and cadmium, are known to cause serious health effects in man if consumed in excess. It is, therefore, important to measure the amount that may be extracted from an area of the glass drinking vessel in contact

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

with the lip. Even though the amount of lead and cadmium extracted by this test method is in no way representative of the amount of the metals extracted by actual lip contact, the relative magnitude of metals extracted from one test specimen in relation to another test specimen provides an effective tool for discrimination.

6. Interferences

6.1 Since specific hollow cathode lamps or electrodeless discharge lamps for lead and cadmium are used, there are no interferences.

7. Apparatus

7.1 *Atomic Absorption Spectrophotometer (AAS)*, equipped with a 102-mm single slot or Boling burner head and digital concentration readout attachment (DCR) if available. This instrument should have a sensitivity of about 0.5 µg/mL of lead for 1 % absorption and a sensitivity of about 0.025 µg/mL of cadmium for 1 % absorption. Use the operating conditions as specified in the instrument manufacturer's analytical methods manual.

7.2 *Hollow Cathode or Electrodeless Discharge Lead Lamp*, set at 283.3 nm.

7.3 *Hollow Cathode or Electrodeless Discharge Cadmium Lamp*, set at 228.8 nm.

7.4 *Glassware* of chemically resistant borosilicate glass for use in preparing and storing reagents and solutions, and for use as test specimen containers.

7.5 Detection limits of lead and cadmium shall be determined and reported for individual instruments. In this test method, the detection limit shall be defined as twice the mean noise level at 0 µg/mL. Representative detection limits would be approximately 0.01 to 0.03 µg/mL for lead and 0.0005 to 0.0010 µg/mL for cadmium.

8. Reagents

8.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination. Analyze each new batch of reagents for lead and cadmium.

8.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled or deionized water.

8.3 *Acetic Acid* (4 volume %) —Mix 1 volume of glacial acetic acid with 24 volumes of water.

8.4 *Cadmium Standard Stock Solution* (1000 µg/mL of cadmium)—Dissolve 0.9273 g of anhydrous cadmium sulfate in 250 mL of 1 % HCl (8.6) and dilute to 500 mL with 1 % HCl. Commercially available standard cadmium solutions may also be used.

8.5 *Detergent Rinse*—Add 2 mL of hand dishwashing detergent to 1 L of lukewarm tap water.

8.6 *Hydrochloric Acid* (1 weight %)—Mix 1 volume of concentrated hydrochloric acid (HCl, sp gr 1.19) with 37 volumes of water.

8.7 *Lead Standard Stock Solution* (1000 µg/mL)—Dissolve 1.598 g of lead nitrate (Pb(NO₃)₂) in 4 % acetic acid and dilute to 1 L with 4 % acetic acid. Commercially available standard lead solutions may also be used.

9. Sampling

9.1 *Continuous Process*—Since the amount of metal released from a decoration can be affected by the firing conditions, which may not be uniform across the width of the lehr, a minimum of six samples should be taken representing both sides and the center of the lehr.

9.2 *Load or Pile*—A minimum of six samples should be randomly selected from throughout the load.

10. Preparation of Standards

10.1 *Lead Standard Working Solutions*—Dilute lead nitrate solution (8.7) with acetic acid (8.3) to obtain working standards having final lead concentrations of 0, 5, 10, 15, and 20 µg/mL.

10.2 *Cadmium Standard Working Solutions*—Dilute cadmium stock solution (8.4) with acetic acid (8.3) to obtain working standards having final cadmium concentrations of 0.0, 0.3, 0.5, 1, 1.5, and 2.0 µg/mL.

10.3 Fresh working solutions should be prepared daily.

11. Procedure

11.1 *Preparation of Sample*—Take six identical units and cleanse each with a detergent rinse. Then rinse with tap water followed by distilled water followed by air drying. Mark each unit 7 mm below the rim. Record the internal volume of each article in millilitres by filling from a graduated cylinder to approximately 6 to 7 mm (¼ in.) of overflowing. Mark each article, in a nondecorated area (if possible), 20 mm below the rim on the outside. Invert the article in an appropriate laboratory glassware container whose diameter is a minimum of 1.25 times and a maximum of 2.0 times the diameter of the test specimen at the rim. Carefully add 4 % acetic acid leaching solution from a graduated cylinder to the 20-mm mark. Record the volume of solution used. Cover the glassware containers, if possible, to prevent evaporation and to protect them from contamination. Let stand for 24 h at room temperature (20 to 24°C) in the dark. Remove the article after the 24-h leaching period and determine the lead and cadmium by atomic absorption. Record the lead and cadmium found in micrograms per millilitre.

NOTE 2—The possibility of a significant amount of evaporation exists. The analyst should determine whether the acetic acid leaching is noticeably below the 20-mm mark before removing the article. If it is, sufficient

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.