

AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Raw Linseed Oil¹

This standard is issued under the fixed designation D 234; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers raw linseed oil.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 93 Test Methods for Flash Point by Pensky-Martens $\ensuremath{\text{Closed Tester}}^2$
- D 555 Guide for Testing Drying Oils³
- D 1466 Test Method for Sampling Liquid Oils and Fatty Acids Commonly Used in Paints, Varnishes, and Related Materials³
- D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)⁴
- D 1639 Test Method for Acid Value of Organic Coating Materials³
- D 1954 Test Method for Foots in Raw Linseed Oil (Volumetric Method)³
- D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids³
- D 1960 Test Method for Loss on Heating of Drying Oils³

D 1962 Test Method for Saponification Value of Drying Oils, Fatty Acids, and Polymerized Fatty Acids³

- D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C³
- D 1965 Test Method for Unsaponifiable Matter in Drying Oils, Fatty Acids, and Polymerized Fatty Acids³
- D 1966 Test Method for Foots in Raw Linseed Oil (Gravimetric Method)³

² Annual Book of ASTM Standards, Vol 05.01.

³ Annual Book of ASTM Standards, Vol 06.03.

⁴ Annual Book of ASTM Standards, Vol 06.01.

TABLE 1 Properties of Raw Linseed Oil

Property	Requirement	ASTM Method
Specific gravity, 25/25°C	0.926 to 0.931	D 1963
Acid value, max	4.0	D 1639
Saponification value	189.0 to 195.0	D 1962
Unsaponifiable matter, max, %	1.50	D 1965
lodine value (Wijs), min	177	D 1959
Loss on heating at 105 to 110°C, max, %	0.2	D 1960
Clarity	clear and transpar- ent at 65°C	D 2090
Color (Gardner), max	13	D 1544
Foots, volumetric, heated oil, max, %	1.0	D 1954
Foots, volumetric, chilled oil, max, %	4.0	D 1954
Gravimetric foots, max %	0.25	D 1966
Flash point, min, °F	250	D 93

D 2090 Test Method for Clarity and Cleanness of Paint and Ink Liquids³

3. Properties

3.1 Linseed oil shall be the oil obtained from flaxseed and shall conform to the requirements given in Table 1.

NOTE 1—It is recognized that raw linseed oil is a natural product and that, in unusual crop years, the color, iodine value and acid value may vary from the stated specification limits. In this case the limits shall be agreed upon between the purchaser and the supplier.

4. Test Methods

4.1 *Sampling*—Sampling should be conducted in accordance with Test Method D 1466.

4.2 The properties enumerated in this specification shall be determined in accordance with the applicable ASTM methods listed in Table 1. The significance of the methods of testing enumerated under properties in this specification is discussed in Guide D 555.

5. Keywords

5.1 drying oils; linseed oil

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of D01.32 on Drying Oils.

Current edition approved June 25, 1982. Published September 1982. Originally published as D234 - 26 T. Last previous edition D234 - 72 (1976).

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.