



Designation: D3137 – 81 (Reapproved 2018)

## Standard Test Method for Rubber Property—Hydrolytic Stability<sup>1</sup>

This standard is issued under the fixed designation D3137; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the ability of rubber to withstand the environmental effects of high humidity. This is accomplished by examination of the material after removal from the moisture-laden environment. It is designed for testing specimens of rubber materials cut from standard sheets prepared in accordance with Practice [D3182](#).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* (For specific precautionary statements, see [Note 1](#).)

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

[D573 Test Method for Rubber—Deterioration in an Air Oven](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D11](#) on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee [D11.15](#) on Degradation Tests.

Current edition approved Aug. 1, 2018. Published September 2018. Originally approved in 1972. Last previous edition approved in 2013 as D3137 – 81 (2013). DOI: 10.1520/D3137-81R18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D3040 Practice for Preparing Precision Statements for Standards Related to Rubber and Rubber Testing](#) (Withdrawn 1987)<sup>3</sup>

[D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets](#)

### 3. Summary of Test Method

3.1 Test specimens are exposed to the influence of humid environments under definite conditions of temperature, humidity, and time for the purpose of measuring the resulting hydrolytic degradation by noting the change in tensile strength after exposure over distilled water.

### 4. Significance and Use

4.1 Rubber and rubber products for certain applications must withstand the environmental effect of high humidity and resist the deterioration of physical properties under these conditions with time. This test method allows performance properties to be determined under the accelerated conditions of high humidity and elevated temperature.

4.2 In view of climatic variations in service conditions, this method may not give results correlating exactly with service performance. However, the test method yields comparative data on which to base judgment as to service quality and it is useful in research and development work.

4.3 This test method is not applicable to coated fabrics; its use for materials other than rubber has not been established.

### 5. Test Conditions

5.1 *Temperature*—The test temperature shall be  $85 \pm 1^\circ\text{C}$  ( $185 \pm 2^\circ\text{F}$ ).

5.2 *Exposure Period*—The exposure period shall be  $96 \pm 1$  h.

5.3 *Conditioning Period*—After the specified exposure period, the specimens shall be conditioned on a flat surface for 16 to 96 h at  $50 \pm 5\%$  relative humidity and  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ).

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).