



Designation: D3150 – 21

Standard Specification for Crosslinked and Noncrosslinked Poly(Vinyl Chloride) Heat-Shrinkable Tubing for Electrical Insulation¹

This standard is issued under the fixed designation D3150; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification applies to flexible, crosslinked and noncrosslinked poly(vinyl chloride) heat-shrinkable tubing for electrical insulating purposes. It is supplied in an expanded form and will shrink to its extruded diameter when heated.

NOTE 1—This standard is similar but not identical to IEC 60684–3–201.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.2.1 In some cases (including the title), temperatures are described in degrees Celsius only.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D1711 Terminology Relating to Electrical Insulation
- D2671 Test Methods for Heat-Shrinkable Tubing for Electrical Use
- D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials
- D8355 Test Methods for Flammability of Electrical Insulating Materials Used for Sleeving or Tubing
- E176 Terminology of Fire Standards

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved Jan. 1, 2021. Published February 2021. Originally approved in 1973. Last previous edition approved in 2018 as D3150 – 18. DOI: 10.1520/D3150-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 Military Standards:³

- MIL-STD-104 Limits for Electrical Insulation Color
- MIL-H-5606 Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance
- MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4 and JP-5
- MIL-L-7808 Lubricating Oil, Aircraft, Turbine Engine, Synthetic Base
- MIL-L-23699 Lubricating Oil, Aircraft, Turbine Engines, Synthetic Base
- MIL-A-8243 Anti-Icing and De-Icing Defrosting Fluid

2.3 Federal Standard:⁴

- SS-S-550 Sodium Chloride, Technical, for Water-Softening Units

2.4 IEC Standards:⁵

- 60684–3–201 Flexible insulating sleeving, Part 3, Sheet 201: Heat shrinkable sleeving, general purpose, flexible, cross-linked PVC, shrink ratio 2:1

3. Terminology

3.1 Definitions:

- 3.1.1 For definitions pertaining to electrical insulation, refer to Terminology D1711.
- 3.1.2 For definitions pertaining to fire standards, refer to Terminology E176.

4. Classification

- 4.1 *Type I*—Flexible, noncrosslinked poly(vinyl chloride) tubing capable of being shrunk at 135 °C (275 °F) in 15 min.
- 4.2 *Type II*—Flexible, crosslinked poly(vinyl chloride) tubing capable of being shrunk at 175 °C (347 °F) in 15 min.

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁴ Available from U.S. Government Printing Office, Superintendent of Documents, 732 N. Capitol St., NW, Washington, DC 20401-0001, <http://www.access.gpo.gov>.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

5. Ordering Information

5.1 When tubing is ordered to this specification, the purchaser shall define the size, color, and type of the required tubing.

6. Materials and Manufacture

6.1 The polymers used in the manufacture of heat-shrinkable tubing shall be modified poly(vinyl chloride) and the finished compound shall be free of all foreign matter other than intended formulation additives as appropriate.

6.2 The tubing shall be extruded, crosslinked (Type II only), and then expanded to the required dimensions.

6.3 Conditioning:

6.3.1 Unless otherwise specified, all testing, except flammability, shall be conducted at 23 ± 5 °C (73 ± 9 °F) and a relative humidity of 50 ± 10 % RH. Flammability testing shall be conducted in still air at a temperature of 15 to 35 °C (59 to 95 °C) and a relative humidity of <75 %. All samples shall be preconditioned at 23 ± 5 °C (73 ± 9 °F) and a relative humidity of 50 ± 10 % RH. for a minimum of 30 min prior to test.

7. Chemical and Physical Property Requirements

7.1 The material shall conform to the chemical and physical property requirements specified in [Table 1](#).

7.2 Every lot of material shall be tested for dimensional requirements, restricted shrinkage, tensile strength, elongation, longitudinal change, and dielectric breakdown. Other requirements shall be tested at a frequency agreed upon between the supplier and the purchaser.

8. Dimensional Requirements

8.1 Type I material shall conform to the applicable requirements listed in [Table 2](#) or [Table 3](#).

8.2 Type II material shall conform to the requirements listed in [Table 3](#).

8.3 Tubing with non-standard dimensions shall be supplied only when agreed upon between purchaser and seller. Tubing with non-standard dimensions shall be considered to comply with this specification if the requirements of [Tables 1 and 2](#) are satisfied and the minimum recovered wall thickness equals or exceeds that of the identical or next largest as supplied size.

TABLE 1 Chemical and Physical Property Requirements

Property	Requirements	
	Type I	Type II
Restricted shrinkage, Procedure A: Type I—30 min, 135 ± 2 °C (275 ± 4 °F) Type II—30 min, 175 ± 2 °C (374 ± 4 °F) 2000-V proof voltage	no cracks no failures	no cracks no failures
Longitudinal change, max, %	0, - 25	+ 1, - 10
Dielectric strength, V/mil (kV/mm)	400 (15.75)	400 (15.75)
Color	MIL-STD-104	MIL-STD-104
Color stability, 24 h at 130 ± 2 °C (266 ± 4 °F)	MIL-STD-104	MIL-STD-104
Water absorption, 24 h at 25 ± 2 °C (77 ± 4 °F), max, %	1.0	1.0
Specific gravity, max	1.40	1.40
Volume resistivity, min, ohm-cm	10^{11}	10^{11}
Flammability, max, s, Test Methods D8355 , Test A	15	15
Heat shock: Type I—4 h at 180 ± 2 °C (236 ± 4 °F) Type II—4 h at 200 ± 2 °C (392 ± 4 °F)	no dripping, flowing, or cracking	no dripping, flowing, or cracking
Low-temperature flexibility, Procedure B, all sizes 1 h at -10 °C (14 °F) on as-received specimens	no cracking	no cracking
Tensile strength, min, psi (MPa)	2000 (13.8)	2000 (13.8)
Elongation, min, %	200	200
Heat resistance, 168 h at 136 ± 2 °C (277 ± 4 °F), followed by tests for:		
Elongation, min, %	150	130
Elongation, % of original, min	65	65
Fluid resistance, 24 h at 25 ± 2 °C (77 ± 4 °F): Hydraulic Fluid, MIL-H-5606 JP-4 Fuel, MIL-T-5624 Lubricating Oil, MIL-L-7808 Lubricating Oil, MIL-L-23699 De-icing Fluid, MIL-A-8243 5 % NaCl, SS-S-550 Followed by tests for:		
Dielectric strength, V/mil (kV/mm)	280 (11.0)	280 (11.0)
Tensile strength, min, psi (MPa)	1800 (12.4)	2000 (13.8)
Copper corrosion, Procedure B: 168 h at 136 °C (277 °F) Copper dust humidity test, Procedure C	no blackening or pitting of copper no corrosion or discoloration of copper dust	no blackening or pitting of copper no corrosion or discoloration of copper dust
Shelf life	A	A

^A The required shelf life is two weeks at 40 ± 2 °C (104 ± 4 °F). The supplier must advise and caution the customer if special storage and handling precautions must be observed to maintain required product dimensions and characteristics.