



Designation: D3823 – 07 (Reapproved 2018)

# Standard Practice for Determining Ticket Numbers for Sewing Threads<sup>1</sup>

This standard is issued under the fixed designation D3823; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice establishes standard ticket numbers for sewing thread regardless of fiber content or type of thread.

1.2 The values stated in inch-pound units are to be regarded as the standard; the values in English units are provided as information only and are not exact equivalents.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D123 Terminology Relating to Textiles](#)

[D204 Test Methods for Sewing Threads](#)

[D1907 Test Method for Linear Density of Yarn \(Yarn Number\) by the Skein Method](#)

[D4849 Terminology Related to Yarns and Fibers](#)

2.2 *ANSI Standard:*<sup>3</sup>

[ANSI/ASQC Z1.4 Sampling Procedures for Inspection by Attributes](#)

## 3. Terminology

3.1 For all terminology relating to D13.58, Yarns and Fibers, refer to Terminology [D4849](#).

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.58 on Yarns and Fibers.

Current edition approved July 1, 2018. Published August 2018. Originally approved in 1978. Last previous edition approved in 2012 as D3823 – 07(2012). DOI: 10.1520/D3823-07R18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

3.1.1 The following terms are relevant to this standard: geige thread, sewing thread, ticket number.

3.2 For all other terms related to textiles, refer to Terminology [D123](#).

## 4. Significance and Use

4.1 This system of sewing thread ticket numbers was developed to overcome the confusion arising from the use by the thread industry of a multiple number of undefined and unrelated ticketing systems.

4.2 The practice is used by sewing thread manufacturers to determine the ticket number to be assigned to a sewing thread. The ticket number is an indicator of the amount of raw fiber in the thread. It is based on greige thread rather than finished thread because finishing processes such as bleaching, dyeing, stretching, mercerizing, or sewing finish application significantly change the apparent thread size so that it may become an inadequate indicator of raw fiber present. Because of the foregoing it is not practical to verify the ticket number by sizing the finished thread.

## 5. Sampling

5.1 *Lot*—Unless otherwise agreed upon between the purchaser and supplier, a lot shall be a discrete manufacturing unit produced in a given period of time not to exceed a calendar month.

5.2 *Lot Sample*—Select the number of specimens as directed in ANSI/ASQC Z1.4 using single sampling with a general inspection level of S1 and a 1.0 AQL.

5.3 *Laboratory Sample*—As a laboratory sample for acceptance testing, take each unit in the lot sample.

5.4 *Test Specimens*—From each package in the laboratory sample, take one specimen.

## 6. Requirements

6.1 Sewing thread ticket numbers shall be based on the average resultant yarn number and shall be designated as indicated in [Table 1](#).

## 7. Procedure

7.1 Determine in tex the resultant yarn number of the greige thread as directed in Test Methods [D204](#).