

Designation: D4074/D4074M - 11 (Reapproved 2022)

Standard Test Method for Bitumen and Aggregate Content of Bitumen-Aggregate Mixtures From Roofing Samples¹

This standard is issued under the fixed designation D4074/D4074M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the bitumen content of adhered aggregate surfacing on a roof, and the approximate mass per unit area of the flood coat and adhered aggregate.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D71 Test Method for Relative Density of Solid Pitch and Asphalt (Displacement Method)

D2829/D2829M Practice for Sampling and Analysis of Existing Built-Up Roof Systems

3. Summary of Test Method

3.1 The proportions of bitumen and aggregate in a mixture are determined from their relative densities and the relative density of their mixture.

4. Significance and Use

4.1 This test method offers a convenient alternative to solvent extraction for the approximate determination of topcoating bitumen and adhered aggregate in roofing samples, particularly when the bitumen is coal-tar pitch.

5. Apparatus

5.1 *Beaker*, 500 mL minimum capacity, without a pour spout.³

5.2 *Glass Cover Plate*, 127 by 127 by 3 mm [5 by 5 by 0.12 in.].

5.3 *Balance*, 1000 ± 0.1 g capacity.

6. Materials

6.1 Isopropyl Alcohol, (CH₃)₂ CHOH, commercial grade.

6.2 *Paper Cups*, paraffin-coated, 61 mm [2.4 in.] in diameter by 76 in. [3 mm] high, 150 mL [5 oz] capacity.

7. Sampling

7.1 Obtain samples in the field in accordance with Practice D2829/D2829M.

8. Procedure

8.1 Cut a 100-mm [5⁵/₈-in.] square specimen from the roofing sample and collect any associated loose, bitumen-free aggregate in a tared paper cup.

8.2 Add additional loose, bitumen-free aggregate to the cup from the remaining sample, if necessary, to obtain a 100 to

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.20 on Roofing Membrane Systems.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1985. Last previous edition approved in 2015 as D4074/D4074M – 11 (2015). DOI: 10.1520/D4074_D4074M-11R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the beaker, Kimble Chase, part #14020-600 Kimax 600 mL without spout, known to the committee at this time is Fisher Scientific, 1022 Spruce St., P.O. Box 1502, Vineland, NJ 08362-1502. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.