

Designation: D4262 – 05 (Reapproved 2018)

# Standard Test Method for pH of Chemically Cleaned or Etched Concrete Surfaces<sup>1</sup>

This standard is issued under the fixed designation D4262; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers procedures for determining the acidity or alkalinity of concrete surfaces prepared by chemical cleaning or etching prior to coating.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

## 2. Terminology

### 2.1 Definitions:

2.1.1 *pH*, *n*—a measure of acidity or alkalinity of a solution or surface, with neutrality represented by a value of 7, with increasing acidity represented by smaller values, and with increasing alkalinity represented by increasing values.

#### 3. Significance and Use

3.1 Chemical cleaning and etching is used to prepare concrete for coating.

3.2 Residual chemicals not removed by water rinsing may adversely affect the performance and adhesion of coatings applied over prepared concrete surfaces. It is the intent of this test method to determine that residual chemicals have been removed by measuring the acidity or alkalinity of the final rinsed surface.

## 4. Apparatus

4.1 The specific apparatus for each test is described in Annex A1 – Annex A3.

#### 5. Materials

5.1 *Potable Water*, for rinsing chemically cleaned or etched concrete surfaces.

5.2 *Wet Concrete Surface*, following the final water rinse and before the rinse water has completely drained off the surface.

## 6. Procedure

6.1 The preparatory actions for each alternative are described in Annex A1 – Annex A3.

6.2 At least two surface pH readings shall be taken for each 500 square feet or portion thereof. Readings shall be taken at randomly selected locations immediately following the final rinse and before all the rinse water has drained off the surface.

6.3 The pH of the water used for rinsing shall be determined to establish acceptance criteria. Readings shall be taken at the beginning and end of the final rinse.

6.4 Unless otherwise specified, tests shall be conducted in accordance with this procedure.

### 7. Acceptance Criteria

7.1 The pH readings following the final rinse shall not be more than 1.0 pH lower or 2.0 higher than the pH of the rinse water unless otherwise specified.

#### 8. Keywords

8.1 etched concrete surface; pH

<sup>&</sup>lt;sup>1</sup> This test method is under the jurisdiction of ASTM Committee D33 on Protective Coating and Lining Work for Power Generation Facilities and is the direct responsibility of Subcommittee D33.05 on Application and Surface Preparation.

Current edition approved Aug. 1, 2018. Published August 2018. Originally approved in 1983. Last previous edition approved in 2012 as D4262 – 05 (2012). DOI: 10.1520/D4262-05R18.