



Designation: D4634 – 16 (Reapproved 2022)

# Standard Classification System and Basis for Specification for Styrene-Maleic Anhydride Molding and Extrusion Materials (S/MA)<sup>1</sup>

This standard is issued under the fixed designation D4634; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This classification system covers styrene-maleic anhydride materials suitable for molding or extrusion. This classification system does not apply to alloys or blends of styrene-maleic anhydride materials with non-elastomeric thermoplastics. Styrene-maleic anhydride materials, being thermoplastic, are reprocessible and recyclable. This classification system allows for the use of those materials provided that all the specific requirements of this classification system are met.

1.2 The properties included in this standard are those required to identify the compositions covered. Other requirements necessary to identify particular characteristics important to specialized applications are to be specified by using the suffixes as given in Section 5.

1.3 This classification system and subsequent line call out (specification) are intended to provide means of calling out properties of plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Materials should be selected by those having expertise in the plastics field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, costs involved, and the inherent properties of the material other than those covered by this classification system.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 The following precautionary caveat pertains only to the test methods portion, Section 11, of this classification system. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

<sup>1</sup> This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Sept. 1, 2022. Published September 2022. Originally approved in 1986. Last previous edition approved in 2016 as D4634 - 16. DOI: 10.1520/D4634-16R22.

NOTE 1—There is no known ISO equivalent to this standard.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D883 Terminology Relating to Plastics

D1525 Test Method for Vicat Softening Temperature of Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials

D3892 Practice for Packaging/Packing of Plastics

D4000 Classification System for Specifying Plastic Materials

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)<sup>3</sup>

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

2.2 *Military Standard*.<sup>4</sup>

**MIL-STD-1916 DOD Preferred Methods for Acceptance of Product**

2.3 *Underwriters Laboratories Standard*.<sup>5</sup>

**UL 94 Standard for Tests for Flammability for Parts in Devices and Appliances**

### 4. Classification

4.1 Styrene-maleic anhydride materials are classified into groups according to their use either for injection molding, or for extrusion. These groups are subdivided into classes and grades, as shown in Table S/MA.

NOTE 2—An example of this classification system is as follows: The designation S/MA 211 would indicate:

- S/MA = Styrene-maleic anhydride,
- 2 = injection-molding resin (group),
- 1 = general purpose (class),
- 1 = requirements given in Table S/MA (grade).

4.1.1 To facilitate the incorporation of future or special materials, the “other/unspecified” category (0) for group, class, and grade is shown in Table S/MA. The basic properties can be obtained from Tables A and B as they apply (see 4.3).

### 3. Terminology

3.1 The terminology used in this classification system is in accordance with Terminologies **D883** and **D1600**.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

<sup>5</sup> Available from Underwriters Laboratories (UL), 333 Pfingsten Rd., Northbrook, IL 60062-2096, <http://www.ul.com>.

**TABLE S/MA Requirements for Natural Color Only**

Group	Description	Class	Description	Grade	Description	Tensile Strength <sup>A</sup> (D638) min, MPa	Flexural Modulus <sup>B</sup> (D790) min, MPa	Izod Impact Strength <sup>C</sup> (D256) min, J/m	Vicat Softening Point <sup>D</sup> (D1525) min, °C
1	Crystal	1	general purpose	1		45	3000	10	120
				0	other	...	...	...	...
		2	high-heat resistant	1		45	2900	10	130
2	Impact-modified, molding	0	other	0	other	...	...	...	...
		1	general purpose	1		40	2200	140	115
				2		33	2100	170	115
				3		30	2000	200	115
				0	other	...	...	...	...
		2	high-impact	1		45	2200	500	115
				2		34	2200	300	120
				0	other	...	...	...	...
		3	high-heat resistant	1		35	2500	120	135
				2		33	2200	210	125
				3		30	2200	80	125
		3	Impact modified, extrusion	0	other	0	other	...	...
1	general purpose			1		40	2500	140	115
				2		35	2300	170	115
				3		30	2200	200	115
				0	other	...	...	...	...
2	high-heat resistant			1		33	2200	210	125
				2		30	2200	80	125
				0	other	...	...	...	...
3	FR			1		28	1900	130	115
				2		22	1800	70	115
				0	other	...	...	...	...
0	Other			0	other	0	other	...	...
		0	other	0	other	...	...	...	...

<sup>A</sup> Tensile strength determined on 3.2-mm thick injection-molded **D638**, Type I specimen, tested at 5 mm/min.

<sup>B</sup> Flexural modulus determined on centrally-loaded **D638**, Type I tensile bar, 2-in. span, tangent, Method 1, 1.3 mm/s.

<sup>C</sup> Izod impact strength determined on 12.5 by 3.2-mm injection molded specimen. The specimen shall be obtained from the central section of a **D638**, Type I tensile bar.

<sup>D</sup> Vicat softening point shall be 1-kg load, Rate B, 12.5 by 3.2-mm injection-molded specimen obtained from the central section of a **D638**, Type I tensile bar.