



Designation: D4873/D4873M – 17 (Reapproved 2021)

# Standard Guide for Identification, Storage, and Handling of Geosynthetic Rolls and Samples<sup>1</sup>

This standard is issued under the fixed designation D4873/D4873M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This guide provides guidelines for the identification and packaging of rolled geosynthetics by the manufacturer and for the handling and storage of geosynthetics by the end user. This guide is not to be considered as all encompassing since each project involving geosynthetics presents its own challenges and special conditions. Geosynthetic samples are often taken at manufacturer, supplier, or at the job site primarily for the purpose of conformance testing and verification. These samples should be properly labeled for identification purposes.

1.2 This guide is intended to aid manufacturers, suppliers, purchasers, and users of geosynthetics for identification, handling, and storage.

1.3 This guide is not applicable for factory-fabricated panels due to a different set of identifications for the panel by the fabricator. For fabricated geomembrane panels, refer to Guide [D7865](#).

1.4 This guide is not intended for geosynthetic clay liners. For GCLs, refer to Guide [D5888](#).

1.5 This guide is also applicable to geosynthetic samples.

1.6 Each type of geosynthetic is listed by section to address specific requirements.

Geotextiles – Section [5](#)  
Geogrids – Section [6](#)  
Geomembrane Rolls – Section [7](#)  
Geonets – Section [8](#)  
Geocomposites – Section [9](#)  
Rolled Erosion Control Products – Section [10](#)  
Sediment Retention Devices – Section [11](#)

1.7 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee [D35](#) on Geosynthetics and is the direct responsibility of Subcommittee [D35.06](#) on Geosynthetic Specifications.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 1988. Last previous edition approved in 2017 as D4873/D4873M – 17. DOI: 10.1520/D4873\_D4873M-17R21.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.9 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D123](#) Terminology Relating to Textiles

[D4354](#) Practice for Sampling of Geosynthetics and Rolled Erosion Control Products (RECPs) for Testing

[D4439](#) Terminology for Geosynthetics

[D5888](#) Guide for Storage and Handling of Geosynthetic Clay Liners

[D7865](#) Guide for Identification, Packaging, Handling, Storage and Deployment of Fabricated Geomembrane Panels

## 3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of geosynthetic terms, refer to Terminology [D4439](#).

3.1.2 For definitions of textile terms, refer to Terminology [D123](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *core, n*—a mandrel of cardboard, foam, or other material on which geosynthetics are rolled during manufacturing to facilitate handling.

3.2.2 *sample, n*—(1) a portion of material which is taken for testing or for record purposes. (See also sample, lot; sample, laboratory; and specimen.) (2) a group of specimens used, or of observations made, which provide information that can be used

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

for making statistical inferences about the population(s) from which the specimens are drawn.

3.2.3 *supplier, n*—the person or organization from whom a geosynthetic is purchased or otherwise obtained.

3.2.3.1 *Discussion*—The supplier is frequently the manufacturer of the geosynthetic, but need not be. A supplier who is not the manufacturer is expected to ensure that the responsibilities of the manufacturer are fully met.

#### 4. Significance and Use

4.1 For a geosynthetic to be properly used it must be adequately identified and packaged. It must be handled and stored in such a way that its physical property values are not degraded. Failure to follow good practice may result in the unnecessary failure of the geosynthetic in a properly designed application.

4.2 This guide is not intended to replace project-specific storage, handling, identification, packaging, or installation requirements or quality assurance programs.

#### 5. Procedure – Geotextiles

##### 5.1 *Packaging and Identification:*

5.1.1 When cores are required, use those that have a crushing strength sufficient to avoid collapse or other damage in normal use.

5.1.2 Cover each roll with an opaque wrapping material for protection from damage due to shipment, water, sunlight, or contaminants while being stored or handled in accordance with this guide.

5.1.3 Identify each roll with a durable, gummed label or equivalent, clearly readable on the roll packaging or on the inside of the core. Roll identification should include, at minimum, the name of the manufacturer or supplier, product or style number, and the unique roll number. Identification should also include the width and length of roll. Any other unique characteristics should be clearly identified. For rolls with no identification on the inside of the core, once the roll is unwrapped or samples taken, labels on the outer wrap of the roll packaging should be removed and placed inside the roll for traceability. All designations should be readable for clear identification.

NOTE 1—Rolls bundled or strapped as a single unit could be regarded as a single roll for identification purposes provided all the rolls remain as a single unit received by the end user.

##### 5.2 *Receiving and Storing at the Job Site:*

5.2.1 While unloading or transferring the geotextile from one location to another, prevent damage to the wrapping and to the geotextile itself. If practicable, use forklift trucks fitted with poles that can be inserted into the cores of rolls. Be sure that the poles are at least two thirds the length of the rolls to avoid breaking the cores and possibly damaging the geotextile. Slings may be used to carry relatively rigid rolls provided that the slings do not cause damage to the rolls. Do not drag the rolls as damage may result.

5.2.2 Geotextiles, when possible, should be stored elevated off of the ground and covered to ensure adequate protection from the following:

5.2.2.1 Precipitation (because geotextile roll goods saturation leads to handling difficulties),

5.2.2.2 Ultraviolet radiation,

5.2.2.3 Undesirable chemicals for any extended period of time,

5.2.2.4 Flames, including welding sparks,

5.2.2.5 Temperatures in excess of 160 °F [71 °C] and below 32 °F [0 °C] (see [Note 2](#)), and

5.2.2.6 Any other environmental condition that may damage the physical property values of the geotextile.

NOTE 2—Geotextiles may contain enough moisture to cause them to stiffen when frozen, which interferes with placement.

##### 5.3 *On-Site Handling:*

5.3.1 While transferring geotextiles from one location to another, prevent damage to the wrapping and to the geotextile itself. Follow the cautions specified in [5.2.1](#).

5.3.2 Before unrolling a roll at the job site, verify its identification. While unrolling the geotextile, inspect it for damage or defects.

5.3.3 Follow all applicable site or project specifications and manufacturer's recommendations for handling and installation.

5.3.4 Correct any damage that occurs during storage or installation as directed by the project specifications and the engineer in charge of installation.

##### 5.4 *Sample Identification:*

5.4.1 If samples are to be taken at the job site, follow removal of wrap and identification of roll according to [5.1.3](#). Outer layer of geotextile should be removed before sample is taken following sampling procedures as prescribed in Practice [D4354](#). Cut sample according to specified test method(s).

5.4.2 Identify each sample with a durable, gummed label or equivalent including, at a minimum, the sample designation, the name of the manufacturer or supplier, product or style number, the lot number or roll number, or both, location sampled or project name or project identification number, sampled by, and date sampled. If a third party is responsible for sampling, include with the name, the address, and telephone number.

5.4.3 Sample should be suitably packaged for shipping to prevent distortion. Sample should be packaged in suitable wrapping material for protection from damage due to shipping, water, sunlight, or contaminants.

#### 6. Procedure – Geogrids

##### 6.1 *Packaging and Identification:*

6.1.1 When cores are required, use those that have a crushing strength sufficient to avoid collapse or other damage in normal use.

6.1.2 As required, cover each roll with a wrapping material for protection from damage due to shipment, water, sunlight, or contaminants while being stored or handled in accordance with this guide.

6.1.3 Identify each roll with a durable, gummed label, tape, or equivalent, either clearly readable on the roll packaging, on the outer wrap when no packaging is required, or on the inside of the core. Roll identification should include, at minimum, the name of the manufacturer or supplier, product or style number, and the unique roll number. Identification should also include