



Designation: D4900 – 99 (Reapproved 2020)

Standard Test Method for Lignosulfonates (Sulfite Cellulose) in Tanning Extracts¹

This standard is issued under the fixed designation D4900; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended for use in detecting the presence of lignosulfonates (sulfite cellulose) in extracts of tanning materials.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D4901 Practice for Preparation of Solution of Liquid Vegetable Tannin Extracts

D4905 Practice for Preparation of Solution of Solid, Pasty and Powdered Vegetable Tannin Extracts

D6404 Practice for Sampling Vegetable Materials Containing Tannin

D6405 Practice for Extraction of Tannins from Raw and Spent Materials

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.01 on Vegetable Leather. This test method has been adapted from, and is a replacement for, Method A50 of the Official Methods of the American Leather Chemists Association.

Current edition approved Dec. 1, 2020. Published December 2020. Originally approved in 1989. Last previous edition approved in 2016 as D4900 – 99 (2016). DOI: 10.1520/D4900-99R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 ALCA Methods:

A50 Lignosulfonates (Sulfite Cellulose)³

3. Summary of Test Method

3.1 The reaction with aniline of a tanning material extract specimen is compared with that of a solution containing lignosulfonate and tanning material known to be free from lignosulfonate.

4. Significance and Use

4.1 This test method is useful to detect possible adulteration of tanning material extract with cheap and inferior lignosulfonates.

5. Specimen

5.1 The sample shall be drawn as described in Practice D6404.

5.2 The specimen shall consist of 5 mL of a solution of analytical strength (4.0 g tannin per L), prepared as described in Practices D4901, D4905, and Practice D6405.

6. Apparatus and Reagents

6.1 *Aniline.*

6.2 *Hydrochloric Acid*, concentrated.

6.3 *Comparison Solution*—This shall contain lignosulfonate (sulfite cellulose) in the proportion of 1 g total solids to 2000 mL of solution, and as much tanning material, similar to and of the same type as that being tested but known to be free from lignosulfonate, as will make up the solution to analytical strength.

7. Procedure

7.1 Place the specimen in a test tube. Add 0.5 mL of aniline, and shake well. Add 2 mL of concentrated hydrochloric acid, and again shake mixture well.

8. Results

8.1 If at least as much precipitate remains at the end of 15 min as is obtained when the comparison solution is similarly

³ Official Methods of the American Leather Chemists Association. Available from the American Leather Chemists Association, University of Cincinnati, P.O. Box 210014, Cincinnati, OH 45221-0014.