



Designation: D4926 – 20

Standard Test Method for Gamma Alumina Content in Catalysts and Catalyst Carriers Containing Silica and Alumina by X-ray Powder Diffraction¹

This standard is issued under the fixed designation D4926; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of gamma alumina and related transition aluminas in catalysts and catalyst carriers containing silica and alumina by X-ray powder diffraction, using the diffracted intensity of the peak occurring at about $67^\circ 2\theta$ when copper $K\alpha$ radiation is employed.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Summary of Test Method

3.1 A sample of catalyst or catalyst carrier is calcined and ground, and an X-ray powder diffraction pattern is obtained under specified conditions over the approximate range from 52 to $76^\circ 2\theta$. The diffracted intensity above background for the peak occurring at about $67^\circ 2\theta$ is compared to that of a

reference sample, after appropriate adjustments are made for scale settings and peak half-widths.

4. Significance and Use

4.1 This test method is for estimating the relative amount of gamma alumina in calcined catalyst or catalyst carrier samples, assuming that the X-ray powder diffraction peak occurring at about $67^\circ 2\theta$ is attributable to gamma alumina. Gamma alumina is defined as a transition alumina formed after heating in the range from 500 to 550°C , and may include forms described in the literature as eta, chi, and gamma aluminas. Delta alumina has a diffraction peak in the same region, but is formed above 850°C , a temperature to which most catalysts of this type are not heated. There are other possible components which may cause some interference, such as alpha-quartz and zeolite Y, as well as aluminum-containing spinels formed at elevated temperatures. If the presence of interfering material is suspected, the diffraction pattern should be examined in greater detail. More significant interference may be caused by the presence of large amounts of heavy metals or rare earths, which exhibit strong X-ray absorption and scattering. Comparisons between similar materials, therefore, may be more appropriate than those between widely varying materials.

5. Apparatus

5.1 *X-ray Powder Diffractometer Unit*, with standard sample mount, Cu $K\alpha$ radiation, monochromator, wide divergence and receiving slits (for example, 3° and 0.15° , respectively), goniometer speed of $0.5^\circ/\text{min}$ or equivalent, chart speed of about $0.5\text{ cm}/\text{min}$ or equivalent, and scale or gain factors to provide conveniently measurable peaks. Computerized data acquisition equipment may also be used.

NOTE 1—For diffractometers employing step scanning, convenient corresponding conditions include a step size of 0.02° and a counting time of $2.4\text{ s}/\text{step}$, which is equivalent to a scanning rate of $0.5^\circ/\text{min}$.

5.2 *Calcination Furnace*.

5.3 *Grinding Equipment*, suitable for preparing samples for mounting in the sample holder.

6. Procedure

6.1 Calcine the catalyst or catalyst carrier sample for 3 h at 500°C .

¹ This test method is under the jurisdiction of ASTM Committee D32 on Catalysts and is the direct responsibility of Subcommittee D32.01 on Physical-Chemical Properties.

Current edition approved Oct. 1, 2020. Published October 2020. Originally approved in 1989. Last previous edition approved in 2015 as D4926 – 15. DOI: 10.1520/D4926-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.