



Designation: D5759 – 12 (Reapproved 2020)

Standard Guide for Characterization of Coal Fly Ash and Clean Coal Combustion Fly Ash for Potential Uses¹

This standard is issued under the fixed designation D5759; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide recommends standards for the characterization of fly ash from the combustion of coal, fly ash from coal combusted in the presence of alkaline materials, and fly ash from combusted coal in which the flue gases have been treated with alkaline materials in the presence of the fly ash.

1.2 This guide provides recommended and optional test methods for fly ash evaluation. Acceptance criteria can be negotiated between the producer and the user according to the potential end use.

1.3 The coal fly ash and clean coal combustion fly ash of this guide do not include the following:

1.3.1 Dusts from kilns producing products such as lime, portland cement, activated clays, etc.;

1.3.2 By-products of flue gas desulfurization that are not collected with the primary fly ash removal equipment such as the baghouse or electrostatic precipitator; and

1.3.3 Fly ash or other combustion products derived from the burning of waste; municipal, industrial, or commercial garbage; sewage sludge or other refuse, or both; derived fuels; wood; wood waste products; rice hulls; agriculture waste; or other non-coal fuels or other such fuels blended with coal, or some combination thereof.

1.4 Fly ash may contain some trace elements that may affect performance or potential end use.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

¹ This guide is under the jurisdiction of ASTM Committee D34 on Waste Management and is the direct responsibility of Subcommittee D34.03 on Treatment, Recovery and Reuse.

Current edition approved May 1, 2020. Published May 2020. Originally approved in 1995. Last previous edition approved in 2012 as D5759 – 12. DOI: 10.1520/D5759-12R20.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- C22/C22M Specification for Gypsum
- C25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime
- C51 Terminology Relating to Lime and Limestone (as used by the Industry)
- C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- C110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone
- C114 Test Methods for Chemical Analysis of Hydraulic Cement
- C150/C150M Specification for Portland Cement
- C191 Test Methods for Time of Setting of Hydraulic Cement by Vicat Needle
- C311/C311M Test Methods for Sampling and Testing Fly Ash or Natural Pozzolans for Use in Portland-Cement Concrete
- C400 Test Methods for Quicklime and Hydrated Lime for Neutralization of Waste Acid
- C593 Specification for Fly Ash and Other Pozzolans for Use With Lime for Soil Stabilization
- C595/C595M Specification for Blended Hydraulic Cements
- C602 Specification for Agricultural Liming Materials
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- D546 Test Method for Sieve Analysis of Mineral Filler for Asphalt Paving Mixtures

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D1973 Guide for Design of a Liner System for Containment of Wastes (Withdrawn 2000)³
 - D2795 Test Methods for Analysis of Coal and Coke Ash (Withdrawn 2001)³
 - D3178 Test Methods for Carbon and Hydrogen in the Analysis Sample of Coal and Coke (Withdrawn 2007)³
 - D3682 Test Method for Major and Minor Elements in Combustion Residues from Coal Utilization Processes
 - D3683 Test Method for Trace Elements in Coal and Coke Ash by Atomic Absorption (Withdrawn 2018)³
 - D4326 Test Method for Major and Minor Elements in Coal and Coke Ash By X-Ray Fluorescence
 - D5239 Practice for Characterizing Fly Ash for Use in Soil Stabilization
 - D5681 Terminology for Waste and Waste Management
 - E1266 Practice for Processing Mixtures of Lime, Fly Ash, and Heavy Metal Wastes in Structural Fills and Other Construction Applications
- 2.2 Other Document:
- USEPA SW846 Method 9100 Saturated Hydraulic Conductivity, Saturated Leachate Conductivity and Intrinsic Permeability⁴

3. Terminology

3.1 *Definitions*—For definitions of terms used in this guide, refer to Terminology D5681.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *clean coal combustion*—the burning of coal, coal culm, or coal fines in a furnace designed to operate to minimize emissions (that is, a fluidized bed or aerated fluidized bed, etc.) or coal burned in the presence of alkaline materials, which combine to reduce these emissions.

4. Significance and Use

4.1 This guide provides guidance for the characterization of coal fly ash or clean coal combustion fly ash for potential uses in which absorption, cementitious activity, pozzolanic activity, pH adjustment, heat rise, or stabilization and solidification properties may be desired.

5. Chemical Composition

5.1 Fly ash from coal and clean coal combustion can be characterized by the recommended chemical tests of Table 1 and may be characterized further by the optional chemical tests of Table 2. Limits may be specified by the purchaser if required for a specific application. The most recent limits established by the appropriate regulatory agency shall govern if no specific parameters are required. See Appendix X1 for possible non-mandatory information for various end uses of fly ash.

6. Physical Tests

6.1 Fly ash from coal and clean coal combustion can be tested further in accordance with the optional physical tests of Table 3, if required by the purchaser.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available online at <http://www.epa.gov/osw/hazard/testmethods/sw846/pdfs/9100.pdf> (last accessed Feb. 10, 2012).

TABLE 1 Recommended Chemical Tests

Test Method	Component(s)	Limit ^A
C114	sulfur trioxide (SO ₃), % ^B	
C311/C311M	moisture content, %	
C311/C311M	loss on ignition, %	
C114, D2795, D3682, or D4326	calcium oxide (CaO), %	
C114, D2795, D3682, or D4326	magnesium oxide (MgO), %	
C114, D2795, D3682, or D4326	silicon dioxide (SiO ₂) plus aluminum oxide (Al ₂ O ₃) plus iron oxide (Fe ₂ O ₃), %	

^A On specific projects, a minimum or maximum may be applicable.

^B Fly ash replaces hydraulic cement in method.

TABLE 2 Optional Chemical Tests^A (Limits to Be Specified Only if Applicable, by the Purchaser)

Test Method	Component(s)	Limit ^B
C25	available lime index (ALI), % ^C	
C311/C311M	available alkalis as Na ₂ O, %	
C400	pH ^D	
C602	calcium carbonate equivalent (CaCO ₃), %	
D3178	carbon (C), %	
D3683	trace elements (totals) (for example, sulfide, sulfite, and sulfate)	

^A Individual requirements may be specified by the purchaser if applicable to the project for which fly ash is to be used.

^B On specific projects, a minimum or maximum may be applicable.

^C Fly ash replaces limestone in analysis.

^D Fly ash replaces quicklime in method.

TABLE 3 Optional Physical Tests^A (To Be Specified Only as Required by the Purchaser)

Test Method	Component(s)
C109/C109M	compressive strength of hydraulic cement mortars, psi ^B
C110	heat rise (slaking rate), °C ^C
C191	time of set, min ^B
C311/C311M	amount retained on No. 325 sieve, %
C311/C311M	strength activity index with portland cement
	7 days, % of control
	28 days, % of control
C311/C311M	water requirement, % of control ^D
C311/C311M	specific gravity
C311/C311M	increase in drying shrinkage, %
C311/C311M	reactivity with cement alkali, mortar expansion, % of control
C311/C311M	soundness
C593	amount retained on No. 200 sieve, %
C593	amount retained on No. 30 sieve, %
C593	lime pozzolan strength 7 days, psi
	lime pozzolan strength 28 days, psi
	USEPA SW846 Method 9100

^A Individual requirements may be specified by the purchaser if applicable to the project for which fly ash is to be used.

^B Modification of Test Method C109/C109M to approximate proportion(s) of fly ash instead of cement; or fly ash in combination with other materials to be used on the project (that is, cement, lime, etc.) should be used.

^C Modify Test Methods C110 to a proportion of fly ash instead of lime. The fly ash to water ratio may need to be modified further to obtain measurable results.

^D Comparisons of water requirements to a control material, used at an equal flow, may be useful to determine the relative water requirement.

7. Shipments for Delivery to Purchaser

7.1 Fly ash shipped for delivery to the purchaser should be from a single combustion unit or a blend from multiple combustion units, as agreed upon between the purchaser and