



Designation: D5799 – 19

Standard Test Method for Determination of Peroxides in Butadiene¹

This standard is issued under the fixed designation D5799; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of peroxides in butadiene.

1.2 This test method covers the concentrations range of 1 mg/kg to 10 mg/kg as available oxygen.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1265 Practice for Sampling Liquefied Petroleum (LP) Gases, Manual Method

D3700 Practice for Obtaining LPG Samples Using a Floating Piston Cylinder

3. Summary of Test Method

3.1 A known mass of the butadiene sample is placed in a flask and evaporated. The residue is then refluxed with acetic acid and sodium iodide reagents. The peroxides react to liberate iodine which is titrated with standard sodium thiosul-

fate solution using visual end-point detection. Interfering traces of iron are complexed with sodium fluoride.

4. Significance and Use

4.1 Due to the inherent danger of peroxides in butadiene, specification limits are usually set for their presence. This test method will provide values that can be used to determine the peroxide content of a sample of commercial butadiene.

4.2 Butadiene polyperoxide is a very dangerous product of the reaction between butadiene and oxygen that can occur. The peroxide has been reported to be the cause of some violent explosions in vessels that are used to store butadiene.

5. Apparatus

5.1 *Condensers*, Liebig, with 24/40 standard-tapered ground-glass joint connections.

5.2 *Cylinders*, graduated, 100 mL capacity.

5.3 *Flask*, Erlenmeyer, 250 mL capacity, with 24/40 standard-tapered ground-glass connections with marking at 100 mL.

5.4 *Heating Mantle*, electric, for 250 mL Erlenmeyer flasks.

5.5 *Microburette*, 10 mL capacity, graduated in 0.02 mL divisions.

5.6 *Water Bath*, a thermostatically controlled liquid bath capable of maintaining a water temperature of $60\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.D0.04 on C4 and C5 Hydrocarbons.

Current edition approved Dec. 1, 2019. Published January 2020. Originally approved in 1995. Last previous edition approved in 2014 as D5799 – 95 (2014). DOI: 10.1520/D5799-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ *ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

*A Summary of Changes section appears at the end of this standard