

AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Oiticica Oil (Permanently Liquid)¹

This standard is issued under the fixed designation D 601; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers oiticica oil that has been treated to render it permanently liquid.

2. Referenced Documents

2.1 ASTM Standards:

- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)²
- D 555 Guide for Testing Drying Oils³
- D 1466 Test Method for Sampling Liquid Oils and Fatty Acids Commonly Used in Paints, Varnishes, and Related Materials³
- D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products⁴
- D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)⁴
- D 1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method³
- D 1639 Test Method for Acid Value of Organic Coating Materials³
- D 1955 Test Method for Gel Time of Drying Oils³
- D 1958 Test Method for Chloroform Insoluble Matter in Oiticica Oil³

² Annual Book of ASTM Standards, Vol 05.01.

- ³ Annual Book of ASTM Standards, Vol 06.03.
- ⁴ Annual Book of ASTM Standards, Vol 06.01.

D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids³

D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at $25/25 \text{ C}^3$

3. Properties

3.1 Oiticica oil (permanently liquid) shall conform to the requirements in Table 1.

TABLE 1	Physical	Properties
---------	----------	------------

Property	Requirement	ASTM Method
Specific gravity, 25/25°C, min	0.972	D 1963, D1475
Viscosity at 25°C, approximate	11 to 23	D 1545, D445
Stokes		
Acid value, max	8.0	D 1639
lodine value (Wijs), min	135	D 1959
Color (Gardner 1933 Standards), max	11	D 1544
Gel time, minutes, max	17	D 1955
Refractive index at 25°C, min	1.5100	
Matter insoluble in chloroform, max, %	0.1	D 1958

4. Test Methods

4.1 *Sampling*—Sampling shall be conducted in accordance with Test Method D 1466.

4.2 The properties enumerated in this specification shall be determined in accordance with the applicable ASTM test methods listed in Table 1. The significance of these test methods enumerated under properties in this specification is discussed in Methods D 555.

5. Keywords

5.1 drying oils; oiticica oil

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D 01.32 on Drying Oils.

Current edition approved Oct. 30, 1987. Published December 1987. Originally published as D 601 - 41. Last previous edition $D 601 - 55 (1981)^{\varepsilon_1}$.