



Designation: D608 – 05 (Reapproved 2019)

Standard Specification for Dibutyl Phthalate¹

This standard is issued under the fixed designation D608; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers dibutyl phthalate (99 % grade).

1.2 The following applies to all specified limits in this standard: for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 For specific hazard information and guidance, see the supplier’s Material Safety Data Sheet for materials listed in this specification.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Material

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1296 Test Method for Odor of Volatile Solvents and Diluents

D1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved April 1, 2019. Published April 2019. Originally approved in 1941. Last previous edition approved in 2011 as D608 – 05 (2011). DOI: 10.1520/D0608-05R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

D1476 Test Method for Heptane Miscibility of Lacquer Solvents

D1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products

D1617 Test Method for Ester Value of Solvents and Thinners

D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E300 Practice for Sampling Industrial Chemicals

2.2 *U.S. Federal Specification:*³

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of

3. Properties

3.1 Dibutyl phthalate (99 % grade) shall conform to the following requirements:

Apparent specific gravity: 20/20 °C	1.046 to 1.050
or 25/25 °C	1.043 to 1.047
Color, Pt-Co scale, max ^A	20
Odor ^B	nonresidual
Water, max, weight %	0.2 ^C
Acidity (free acid as phthalic acid), max, weight %	0.01 ^D
Ester value, max, weight %	not less than 99.0

^A Instrumental Pt-Co color determined by Test Method D5386 has been shown to have no statistically significant difference from Pt-Co color determined by Test Method D1209. However, it is not known whether dibutyl phthalate was part of the sample set included in the interlaboratory study.

^B Optional as agreed upon between supplier and consumer.

^C This quantitative limit ensures that the material is miscible without turbidity with 19 volumes of 99 % heptane at 20 °C.

^D Equivalent to 0.067 mg of KOH per gram of sample.

4. Sampling

4.1 The material shall be sampled in accordance with Practice E300.

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, http://www.access.gpo.gov.