



Designation: D6585 – 17 (Reapproved 2022)

Standard Specification for Unsintered Polytetrafluoroethylene (PTFE) Extruded Film or Tape¹

This standard is issued under the fixed designation D6585; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers unsintered extruded films or tapes manufactured from virgin, unpigmented polytetrafluoroethylene, in nominal thickness from 0.025 to 0.51 mm (0.001 to 0.020 in.), which are $\geq 99\%$ PTFE in composition.

NOTE 1—For unsintered pigmented products, refer to Specification D7193.

1.1.1 The use of recycled PTFE for production of unsintered extruded films or tapes has not been identified at this time. When commercial usable processes and materials are available, this specification will be revised to include recycled materials.

1.2 The values stated in SI units are detailed in [IEEE/ASTM SI-10](#) are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following precautionary statement pertains only to the test method portion, Section 8 of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—Although this specification and ISO 13000-1 and ISO 13000-2 differ in approach or detail, data obtained relating to specific properties, using either are technically equivalent.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 2000. Last previous edition approved in 2017 as D6585 - 17. DOI: 10.1520/D6585-17R22.

2. Referenced Documents

2.1 ASTM Standards:²

- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation
- D257 Test Methods for DC Resistance or Conductance of Insulating Materials
- D618 Practice for Conditioning Plastics for Testing
- D882 Test Method for Tensile Properties of Thin Plastic Sheeting
- D883 Terminology Relating to Plastics
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1711 Terminology Relating to Electrical Insulation
- D3892 Practice for Packaging/Packing of Plastics
- D6040 Guide to Standard Test Methods for Unsintered Polytetrafluoroethylene (PTFE) Extruded Film or Tape
- D7193 Specification for Unsintered Pigmented Polytetrafluoroethylene (PTFE) Extruded Film or Tape
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): The Modern Metric System

2.2 ISO Standard:³

- ISO 13000-1 Plastics—Polytetrafluoroethylene (PTFE) Semi-Finished Products—Part 1: Requirements and Designation
- ISO 13000-2 Plastics—Polytetrafluoroethylene (PTFE) Semi-Finished Products—Part 2: Preparation of Test Specimens and Determination of Properties Designation

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

2.3 GSA Standard:

A-A-58092 Tape, Anti-seize, Polytetrafluorethylene⁴

NOTE 3—Supersedes MIL-T-27730A (ASG) 7 January 1997.

3. Terminology

3.1 *Definitions:* Definitions are in accordance with Terminology **D1711**, Terminology **D883**, and Test Method **D257** and abbreviated terms are in accordance with Terminology **D1600**, unless otherwise specified.

3.1.1 *lot, n*—one production run or a uniform blend of two or more production runs.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *film, n*—full width material received as finished film.

3.2.2 *tape, n*—material that has been slit from the finished film.

3.2.3 *tensile strength at yield, n*—from Test Methods **D882**.

4. Classification

4.1 This specification covers three types of unsintered extruded PTFE tapes:

4.1.1 *Type I*—Thread seal tape (T.S.T.) with an apparent density of 0.50 to 1.60 g/cm³.

4.1.2 *Type II*—Low density tape with an apparent density of 0.60 to 0.80 g/cm³.

4.1.3 *Type III*—Wire and cable tape with an apparent density of 1.50 to 1.70 g/cm³.

4.2 Grades of tape are identified in **Tables 1-3**.

NOTE 4—Other products that do not fall into these ranges are available. The values vary on these products and must be agreed to between supplier and purchaser.

4.3 A line callout system is used to specify materials in this specification. The system uses pre-defined cells to refer to specific aspects of this specification, as illustrated below:

Standard Number Block	Type	Specification Grade	Class	Special Notes
Example: ASTM D6585	III	2 mil	—	—

For this example, the line call-out would be: ASTM D6585, III, 2 mil, specifies an unsintered wire and cable tape, 2 mil thick, and having all of the properties listed for that type and grade in the appropriate specified properties tables. A comma is used as the separator between the standard number and the

⁴ A-A-58092 can be obtained from General Services Administration, Engineering and Commodity Management Division (9FTE-10), 400 15th St. SW, Auburn, WA 98001.

type. Separators are not needed between the type and grade because they are, in turn, Roman numerals and Arabic digits as provided in Section B8 of the *Form and Style for ASTM Standards*. Provision for “Special Notes” is included so that other information is provided when required. This example relates to wire and cable tape with no special or added requirements. When special notes are used, they shall be preceded by a comma.

5. Performance Requirements

5.1 Basic requirements from the property tables are always in effect unless superseded by specific suffix requirements, which always take precedence.

5.2 The materials shall conform to the requirements in **Tables 1-4** and suffix requirements as they apply.

5.3 The dielectric breakdown strength of unsintered samples shall be tested in accordance with Test Method **D149**. The required values are to be agreed upon between producer and consumer.

5.4 If invoked by contract, or to gain understanding of the electrical performance consistency of a particular material dielectric constant and volume resistivity shall be tested in accordance with Test Methods **D150** and **D257**, as seen in the guidelines found in Guide **D6040**.

5.5 The width tolerance of slit tape shall be in accordance with **Table 4** unless otherwise specified by contract.

6. Sampling

6.1 Sampling shall be in accordance with an adequate statistical sampling procedure.

7. Conditioning

7.1 For those tests where conditioning is required, condition the test specimens in accordance with Procedure A of Practice **D618**, except the time shall be for a period of at least 4 h prior to test instead of the 40 h required by this method. If the test material has been exposed to temperatures below 20°C (68°F) within 24 h period prior to test, the conditioning shall be at least 24 h.

7.2 Conduct tests at the standard laboratory temperature of 23 ± 2°C (73.4°F ± 3°F). The maintenance of constant humidity is not necessary. In reference cases, the standard atmosphere and 50 ± 5 % relative humidity shall apply.

TABLE 1 Type I Thread Seal Tape with an Apparent Density of 0.50 to 1.60 g/cm³

NOTE 1—Where no property is listed there is no requirement.

Grade	Apparent Density, g/cm ³		Thickness			Tensile Strength at Yield		Elongation at Maximum Strength	
	min	max	mm	tolerance	in.	tolerance	MPa	psi	min, %
Economy	0.50	0.90	0.076	...	0.0030
Standard	0.80	1.10	0.076	±0.0127	0.0030	±0.0005	50
Mil Spec., A-A-58092	1.20		0.088	+0.0254, −0.0381	0.0035	+0.0010, −0.0015	40
Premium	1.20	1.60	0.076	±0.0127	0.0030	±0.0005	11.72	1700	75