



Designation: D6625 – 13 (Reapproved 2020)

Standard Practice for Conducting a Test of Protective Properties of Polish Applied to a Painted Panel Using Fluorescent UV-Condensation Light- and Water-Exposure Apparatus¹

This standard is issued under the fixed designation D6625; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the selection of test conditions from Practice **G53** to be employed for exposure testing of polish-coated paint, related coatings, and materials. This practice covers the basic principles and operating procedures for using fluorescent ultraviolet (UV) and condensation apparatus to simulate the deterioration caused by sunlight and water as rain or dew.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D523 Test Method for Specular Gloss

G53 Practice for Operating Light-and Water-Exposure Apparatus (Fluorescent UV-Condensation Type) for Exposure of Nonmetallic Materials (Withdrawn 2000)³

¹ This practice is under the jurisdiction of ASTM Committee **D21** on Polishes and is the direct responsibility of Subcommittee **D21.04** on Performance Tests.

Current edition approved Oct. 1, 2020. Published October 2020. Originally approved in 2001. Last previous edition approved in 2013 as D6625 - 13. DOI: 10.1520/D6625-13R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3. Significance and Use

3.1 Organic coatings on exterior exposure are subjected to attack by degrading elements of the weather, particularly ultraviolet light, oxygen, and water. This practice may be used for evaluating the protective behavior of polish film applied to a coating. This polish-coated coating is then exposed in an apparatus that produces ultraviolet radiation, temperature variation, and water condensation for a given time period.

3.2 No single light exposure apparatus, with or without water, can be specified as a direct simulation of natural exposure. This practice does not imply a specific correlation with outdoor exposure. It is, however, useful in screening the relative protective qualities of a polish within the test parameter.

4. Apparatus and Material

4.1 *Fluorescent UV/Condensation Apparatus*, complying with Practice **G53**.

4.2 *Glossmeter*, using an angle of reflection of 60°. The instrument and the reference standards shall conform to the requirements prescribed in Test Method **D523**.

4.3 *Forced-air Oven*.

4.4 *Q Panel*, approximately 7.5 by 15 cm aluminum.

4.5 *Base Paint Coating*—should be a red paint that gives 100 % loss in gloss after being exposed to the test in this practice. Apply this paint to the aluminum Q panel according to the instructions on the spray can. Allow paint coating to air dry for 24 h followed by 2 h of drying in a forced-air oven at 50°C.

4.6 *Polishing and Application Cloth*— shall be the same size and type for each sample tested. Separate cloths shall be used for each polish and for the application step and buffing step. Materials such as washed cheesecloth, rumple cloth, flannel, cotton diaper cloth, and nonwoven fabrics are suitable for this purpose. Felt or paper shall not be used.

4.7 *Samples of Polish*, to be tested.

5. Procedure

5.1 Apply the test polish to one half of the prepared coated panel. If the polish is a commercially available product, follow