



Designation: D1384 – 05 (Reapproved 2019)

Standard Test Method for Corrosion Test for Engine Coolants in Glassware¹

This standard is issued under the fixed designation D1384; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a simple beaker-type procedure for evaluating the effects of engine coolants on metal specimens under controlled laboratory conditions (see [Appendix X1](#)).

NOTE 1—For more information on engine coolants, see (Refs [1-8](#)).²

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in [10.1.7.2](#), [10.1.7.3](#), and [10.1.7.4](#).

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

[B32 Specification for Solder Metal](#)

[B36/B36M Specification for Brass Plate, Sheet, Strip, And Rolled Bar](#)

[D1176 Practice for Sampling and Preparing Aqueous Solutions of Engine Coolants or Antirusts for Testing Purposes](#)

[E1 Specification for ASTM Liquid-in-Glass Thermometers](#)

[E178 Practice for Dealing With Outlying Observations](#)

¹ This test method is under the jurisdiction of ASTM Committee D15 on Engine Coolants and Related Fluids and is the direct responsibility of Subcommittee D15.06 on Glassware Performance Tests.

Current edition approved Oct. 1, 2019. Published October 2019. Originally approved in 1955. Last previous edition approved in 2012 as D1384–05 (2012). DOI: 10.1520/D1384–05R19.

² The boldface numbers in parentheses refer to the list of references at the end of this standard.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E230 Specification for Temperature-Electromotive Force \(emf\) Tables for Standardized Thermocouples](#)
[G31 Guide for Laboratory Immersion Corrosion Testing of Metals](#)

2.2 *ASTM Adjuncts:*

All-glass apparatus for corrosion test (2 drawings)⁴

3. Summary of Test Method

3.1 In this test method, specimens of metals typical of those present in engine cooling systems are totally immersed in aerated engine coolant solutions for 336 h at 88 °C (190 °F). The corrosion-inhibitive properties of the test solution are evaluated on the basis of the weight changes incurred by the specimens. Each test is run in triplicate, and the average weight change is determined for each metal. A single test may occasionally be completely out of line (see [11.2](#)).

4. Significance and Use

4.1 This test method will generally distinguish between coolants that are definitely deleterious from the corrosion standpoint and those that are suitable for further evaluation. However, the results of this test method cannot stand alone as evidence of satisfactory corrosion inhibition. The actual service value of an engine coolant formulation can be determined only by more comprehensive bench, dynamometer, and field tests.

5. Apparatus

5.1 *Container*—A 1000 mL, tall-form, spoutless beaker, made of heat-resistant glass, for containing the engine coolant solution and test specimens. The beaker shall be tightly closed with a No. 15 rubber stopper, having drill holes to accommodate a water condenser, an aerator tube, and a thermometer as shown in [Fig. 1](#). Optionally, an all-glass apparatus may be used.⁴

5.2 *Condenser*—A water condenser of the reflux, glass-tube type, having a 400 mm (16 in.) condenser jacket.

⁴ Details available from: ASTM International Headquarters. Order Adjunct No. [ADJD1384](#). Original adjunct produced in (1980).




FIG. 1 Metal Specimens and Equipment for the 336 h Corrosion Test

5.3 *Aerator Tube*—A gas-dispersion tube, porosity size 12-C,⁵ to ensure continuous aeration without plugging.

5.4 *Temperature Measuring Instrument (Environmentally Safe Thermometer or Thermocouple)*—An ASTM Partial Immersion Temperature Measuring Instrument having a range from -20 to 150°C (0 to 302°F) and conforming to the requirements for Thermometer 1C (1F), as prescribed in Specification E1 or Thermocouple as summarized in Specification E230.

5.5 *Heater*—A constant-temperature bath containing a high-boiling liquid (see Note 2) that is capable of giving continuous service with the specified temperature control.⁶ The size of the bath will be determined by the number of corrosion tests that are to be run concurrently.

⁵ The sole source of supply of the apparatus known to the committee at this time is the Corning Glass Works. Gas-dispersion tube No. 39533, manufactured by the Corning Glass Works, 44-5 Crystal St., Corning, NY, has generally been found satisfactory for this purpose. Optionally, a capillary tip bleed tube with 0.28 in. (7 mm) bore and 11.2 in. (280 mm) length may be used when consistent early plugging of gas dispersion tubes occurs. The tube, catalog No. 7815-19, may be obtained from the Corning Glass Works, Corning, NY 14830. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ If a water bath is used, a significant reduction in evaporation rate is achieved by addition of floating plastic chips on the water surface.

6. Metal Test Specimens

NOTE 2—The specimens prescribed in this test method have been accepted by automobile manufacturers, but their composition may not be the same as that of alloys currently used for engine cooling system components. Therefore, specimens other than those designated in this test method may be used by mutual agreement of the parties involved.

6.1 *Type*—The following metal test specimens,⁷ representative of cooling system metals, shall be used:

6.1.1 *Steel*, UNS G10200 (SAE 1020),⁸ cut from 1.59 mm ($1/16$ -in.) cold-rolled sheet stock to size 50.8 by 25.4 mm (2 by 1 in.). Chemical composition of the carbon steel is as follows: carbon, 0.17 to 0.23 %; manganese, 0.30 to 0.60 %; phosphorus, 0.040 % maximum; sulfur, 0.050 % maximum.

6.1.2 *Copper*, conforming to UNS C11000 (SAE CA110)⁸ or UNS C11300 (SAE CA113)⁸. Cold-rolled, cut from 1.59 mm ($1/16$ in.) sheet stock to size 50.8 by 25.4 mm (2 by 1 in.).

6.1.3 *Brass*, conforming to Alloy UNS C26000 (SAE CA 260).⁹ Half-hard, cut from 1.59 mm ($1/16$ in.) sheet stock to size 50.8 by 25.4 mm (2 by 1 in.).

6.1.4 *Solder*—A brass specimen as described in 6.1.3, coated with solder conforming to Alloy Grade 30A (SAE 3A) of Specification B32.⁹ Solder-coated specimens may be prepared, or used specimens recoated for reuse, by the procedure given in Annex A1. A solid solder specimen cut from 1.59 mm ($1/16$ in.) sheet stock of Alloy Grade 30A (SAE 3A) to size 50.8 by 25.4 mm (2 by 1 in.) may be used subject to mutual agreement of the parties involved. The use of a solid solder specimen must be reported along with the metal specimen weight loss results.

6.1.4.1 When agreed upon between the supplier and the purchaser of engine coolants, the standard solder specimen may be replaced with one having a different alloy composition than standard Alloy Grade 30A or 30B. Use of specimens other than standard Alloy Grade 30A or 30B shall be noted in the test report.

NOTE 3—Where non-standard alloy is used, the standard flux shown in A1.1.5 may not be satisfactory. A low corrosive flux may be required.

6.1.5 *Cast Aluminum*, conforming to Alloy UNS A23190 (SAE 329).⁸ Specimen size, 50.8 by 25.4 by 3.18 mm (2 by 1 by $1/8$ in.).

6.1.6 *Cast Iron*, conforming to Alloy UNS F10007 (SAE G3500).⁷ Specimen size, 50.8 by 25.4 by 3.18 mm (2 by 1 by $1/8$ in.).

6.2 Arrangement (See Fig. 2):

6.2.1 *Metal Specimen Arrangement*—None of the hardware used in metal specimen arrangement (metal specimen, screws, washers, metal spacers, insulating sleeves, insulating spacers and nuts) can be reused for a test. The metal test specimens shall be drilled through the center with a 6.75 mm ($17/64$ in.) drill to accommodate a 50.8 mm (2 in.) 10–24 brass machine

⁷ Complete sets or individual metal test specimens are available from (a) Chemical Specialties Manufacturers Association, Inc., Suite 1120, 1001 Connecticut Ave., N.W., Washington, DC 20036; (b) Astro-Mechanics, Inc., 8500 Research Blvd., Austin, TX 78766; (c) The Metaspac Company, P.O. Box 27707, San Antonio, TX 78227; or (d) Metal Samples Co. Inc., P.O. Box 8, Munford, AL 36268.

⁸ UNIFIED numbering system for metals and alloys, SAE-ASTM, July 1995.

⁹ Round-robin evaluation of coated solder report is available from ASTM Headquarters. Request RR:D15-0132.




FIG. 2 Metal Specimen Arrangement

screw covered with a thin-walled insulating sleeve. Tetrafluoroethylene tubing with a 6.35 mm ($\frac{1}{4}$ in.) outside diameter 1.59 mm ($\frac{1}{16}$ in.) wide and a wall thickness of 0.4 mm ($\frac{1}{64}$ in.) is satisfactory. Two half-hard brass legs shall be cut from 1.59 mm ($\frac{1}{16}$ in.) sheet stock to size 50.8 by 25.4 mm (2 by 1 in.). A 6.35 mm ($\frac{1}{4}$ in.) diameter hole shall be drilled in each leg with the center 6.35 mm ($\frac{1}{4}$ in.) from the top and 12.7 mm ($\frac{1}{2}$ in.) from each side. The test “bundle” shall be made up on the insulated screw with the specimens in the following order: brass leg, copper, solder, brass, steel, cast iron, cast aluminum, and brass leg. The specimens shall be separated by 4.76 mm ($\frac{3}{16}$ in.) thick solid metal spacers having a 6.75 mm ($\frac{1}{4}$ in.) inside diameter and a 11.11 mm ($\frac{7}{16}$ in.) outside diameter. Insulating spacers made from tetrafluoroethylene shall be used between the brass legs and the specimen “bundle,” and between the brass and steel specimens. Brass spacers shall be used between the brass, solder, and copper specimens, and steel spacers between the cast iron, steel, and cast aluminum specimens. The nut shall be tightened firmly to ensure good electrical contact between the test specimens in each section of the “bundle.”

6.2.2 Alternate Metal Specimen Arrangement—When agreed upon between the supplier and the purchaser, an alternate metal specimen arrangement may be used to evaluate multiple solder alloys, such as high lead Alloy Grade L50113⁹ consisting of 97 % lead, 2.5 % tin, 0.3 % silver, concurrently with Standard Alloy Grade 30A or 30B. It is recommended that the metal specimen arrangement be modified by replacing the copper specimen with the high lead solder specimen and arranging specimens in the bundle as follows:

High Lead Solder	Brass	Alloy Grade 30A or 30B	Steel	Cast Iron	Cast Aluminum
---------------------	-------	---------------------------	-------	-----------	------------------

Use of alternate specimens and metal specimens arrangements shall be noted in the test report.

7. Preparation of Test Specimens

7.1 Sand the cast iron and cast aluminum specimens on the 25.4 by 50.8 mm (1 by 2 in.) cut surfaces with “coarse” grade (No. 1) emery cloth. Remove any burrs from coupon edges and hole. Scrub all specimens vigorously, using a moistened bristle brush and ground pumice powder or fine silicon carbide grit

until the entire metal area is bright, shiny, and free from any visible oxide film or tarnish.

7.2 Rinse the specimens thoroughly with tap water; then rinse with acetone, dry, and weigh to the nearest 1 mg. Cast aluminum specimens should be dried in a 100 °C oven for 1 h, to a constant weight, prior to recording the weight.

NOTE 4—If the test specimens are not to be used immediately, keep them in a desiccator until required.

8. Test Solutions

8.1 The concentration of the engine coolant to be tested shall be as follows:

8.1.1 Engine Coolant—The engine coolant, EG or PG based, shall be mixed with the proper quantity of corrosive water to give a 33 $\frac{1}{3}$ volume % coolant test solution.

8.1.2 Corrosive Water (Note 4)—The corrosive water shall contain 100 ppm each of sulfate, chloride, and bicarbonate ions introduced as sodium salts.

8.2 Preparation of Sample—The preparation of the sample shall be done in accordance with the section on Preparation of Solutions Requiring Inclusion of Separated Solids and Liquids in Test Method **D1176**, except that the corrosive water shall be used for dilution instead of distilled water. Thus, any insoluble materials will be included in the representative sample.

NOTE 5—The specified corrosive water can be prepared by dissolving the following amounts of anhydrous sodium salts in a quantity of distilled or deionized water.

sodium sulfate	148 mg
sodium chloride	165 mg
sodium bicarbonate	138 mg

The resulting solution should be made up to a volume of 1 L with distilled or deionized water at 20 °C.

If relatively large amounts of corrosive water are needed for testing, a concentrate may be prepared by dissolving ten times the above amounts of the three chemicals, in distilled or deionized water, and adjusting the total volume to 1 L by further additions of distilled or deionized water. When needed, the water concentrate is diluted to the ratio of one part by volume of concentrate to nine parts of distilled or deionized water.

9. Test Conditions

9.1 Beaker Assembly—The arrangement of the assembled metal specimens with relation to the aerator tube and other components is shown in **Fig. 1**. Note that the tip of the condenser just emerges from the bottom of the rubber stopper.

9.2 Test Temperature—The test solution shall be maintained at a temperature of 88 \pm 2 °C (190 \pm 5 °F).

9.3 Aeration Rate—The aeration rate shall be 100 \pm 10 mL/min. The aerator tube should be located at least 12.7 mm ($\frac{1}{2}$ in.) away from the test “bundle” to avoid direct contact with the metal specimens.

9.4 Test Duration—The test shall be run continuously for 2 weeks (336 h).

10. Procedure

10.1 Make triplicate tests concurrently on each engine coolant solution in accordance with the following procedure:

10.1.1 Carefully clean the test beaker, condenser, rubber stopper, and aerator tube, and thoroughly rinse with water.