



Designation: D3359 – 22

Standard Test Methods for Rating Adhesion by Tape Test¹

This standard is issued under the fixed designation D3359; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 These test methods cover procedures for assessing the adhesion of relatively ductile coating films to metallic substrates by applying and removing pressure-sensitive tape over cuts made in the film.

1.2 Test Method A is primarily intended for use in the field while Test Method B is more suitable for use in laboratory or shop environments. Also, Test Method B is not considered suitable for films thicker than 125 μm (5 mils) unless wider spaced cuts are employed and there is an explicit agreement between the purchaser and seller.

1.3 These test methods are used to evaluate whether the adhesion of a coating to a substrate is adequate for the user's application. They do not distinguish between higher levels of adhesion for which more sophisticated methods of measurement are required.

1.4 This test method is similar in content (but not technically equivalent) to ISO 2409.

1.5 In multicoat systems adhesion failure may occur between coats so that the adhesion of the coating system to the substrate is not determined.

1.6 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Films.

Current edition approved July 1, 2022. Published July 2022. Originally approved in 1974. Last previous edition approved in 2017 as D3359 – 17. DOI: 10.1520/D3359-22.

2. Referenced Documents

2.1 *ASTM Standards*:²

D609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products

D823 Practices for Producing Films of Uniform Thickness of Paint, Coatings and Related Products on Test Panels

D1000 Test Methods for Pressure-Sensitive Adhesive-Coated Tapes Used for Electrical and Electronic Applications

D1730 Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting

D2092 Guide for Preparation of Zinc-Coated (Galvanized) Steel Surfaces for Painting (Withdrawn 2008)³

D2370 Test Method for Tensile Properties of Organic Coatings

D3330/D3330M Test Method for Peel Adhesion of Pressure-Sensitive Tape

D3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials

D4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser

2.2 *Other Standards*:

ISO 2409 Paint and Varnishes — Cross-cut test⁴

PSTC 101 International Standard for Peel Adhesion of Pressure Sensitive Tape⁵

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *adhesion, n*—the molecular attraction and mechanical bonds between a coating and its substrate.

3.1.2 *batch, n*—as it pertains to tape, a unique production run during manufacturing.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from the Pressure Sensitive Tape Council (PSTC), 1833 Centre Point Circle, Suite 123, Naperville, IL 60563, <http://www.pstc.org>.

3.1.3 *blemish, n*—an obvious surface flaw, such as cracking or discoloration of the coating.

3.1.4 *environmental conditions, n*—the characteristics of the immediate surroundings during the tests, such as temperature, and relative humidity.

3.1.5 *immersion conditions, n*—the characteristics of the fluid to which the test specimen was exposed, such as type of fluid, temperature of fluid and duration of immersion.

3.1.6 *lap, n*—one complete turn of the tape on a roll; the outer exposed layer of tape.

3.1.7 *lattice pattern, n*—one series of parallel lines intersected by another set of parallel lines that are at 90° to and centered on the first set.

3.1.8 *mean, n*—the classification rating that is obtained by adding together the digits of the classification ratings of the tests performed and dividing by the number of tests, frequently rounded to the nearest whole number classification rating.

3.1.9 *pressure-sensitive tape, n*—tape with an adhesive that requires some degree of pressure, and only pressure, to adequately bond to a surface.

3.1.10 *range, n*—the span of classification ratings for a set of tests, from minimum classification rating to maximum classification rating.

3.1.11 *solvent, n*—a liquid agent capable of dissolving or dispersing contaminants from the surface of the coating or film.

3.1.12 *substrate, n*—the structural foundation beneath the coating or film being tested.

3.1.13 *template, n*—a thin, rigid plate containing evenly distributed, parallel slits for use as a guide in generating the lattice pattern when accompanied by a single-blade cutting tool.

3.1.14 *test specimen, n*—the object whose coatings adhesion is of interest.

4. Summary of Test Methods

4.1 *Test Method A*—An X-cut is made through the film to the substrate, pressure-sensitive tape is applied over the cut and then removed, and adhesion is assessed qualitatively on a 0 to 5 scale.

4.2 *Test Method B*—A lattice pattern with either six or eleven cuts in each direction is made through the film to the substrate, pressure-sensitive tape is applied over the lattice pattern and then removed, and adhesion is assessed qualitatively on a 0 to 5 scale.

4.2.1 Subject to agreement between the purchaser and the seller, Test Method B can be used for films thicker than 125 μm (5 mils) if wider spaced cuts are employed.

5. Significance and Use

5.1 In order for a coating is to fulfill its function of protecting or decorating a substrate, the coating must remain adhered to the substrate. Because the substrate and its surface preparation (or lack thereof) have a drastic effect on the adhesion of coatings, a method to evaluate adhesion of a coating to different substrates or surface treatments, or of

different coatings to the same substrate, is of considerable usefulness in the industry.

5.2 This test method is limited to evaluating lower levels of adhesion (see 1.3). The intra- and inter-laboratory precision of this test method is similar to other test methods for coated substrates (for example, Test Method D2370 and Test Method D4060), and is insensitive to all but large differences in adhesion. Limiting the range of rankings from 0 to 5 reflects the inability of this test method to make fine distinctions between levels of adhesion. Users shall not use intermediate values for ranking adhesion tests within this method.

5.3 Extremes in temperatures or relative humidity may affect the adhesion of the tape or the coating.

5.4 A given tape may not adhere equally well to different coatings due to several factors, including differences in coating composition and topology. As such, no single tape is likely to be suitable for testing all coatings. Furthermore, these test methods do not give an absolute value for the force required for bond rupture, but serves only as an indicator that some minimum value for bond strength was met or exceeded (1, 2).⁶

5.5 Operators performing these test methods must be trained and practiced in order to obtain consistent results. The accuracy and precision of the test result obtained by using these methods depends largely upon the skill of the operator and the operator's ability to perform the test in a consistent manner. Key steps that directly reflect the importance of operator skill include the angle and rate of tape removal and the visual assessment of the tested sample. It is not unexpected that different operators might obtain different results (1, 2).

5.6 The standard requires that the free end of the tape be removed rapidly at as close to a 180° angle as possible. When the peel angle and rate vary, the force required to remove the tape can change dramatically due to the rheological properties of the backing and adhesive. Variation in pull rate and peel angle can effect large differences in test values and must be minimized to assure reproducibility (3).

NOTE 1—These test methods have been reported being used to measure adhesion of organic coatings on non-metallic substrates (for example, wood and plastic), although related precision and bias data is lacking. If testing coatings on non-metallic substrates, either Test Method A or Test Method B may be more appropriate and the method employed should be discussed by interested parties. Issues with plastic substrates are noted in Appendix X1. A similar test method, ISO 2409, permits tests on non-metallic substrates (for example, wood and plaster). Precision and bias data on the latter is lacking. Test Method D3359 was developed with metal as the substrate and, in the absence of supporting precision and bias data, is so limited.

TEST METHOD A—X-CUT TAPE TEST

6. Apparatus and Materials

6.1 *Cutting Tool*—Sharp razor blade, scalpel, knife or other fine-edged cutting device. The cutting edges shall be in good condition, preferably new or newly sharpened.

⁶ The boldface numbers in parentheses refer to the list of references at the end of this test method.

6.2 *Cutting Guide*—Steel or other hard metal straightedge to ensure straight cuts.

6.3 *Tape*—25-mm (1.0-in.) wide transparent or semitransparent pressure-sensitive tape with an adhesive peel strength between 6.34 N/cm (58 oz/in.) and 7.00 N/cm (64 oz/in.), as tested in accordance with Test Method D3330/D3330M, Test Method A, (equivalent to PSTC 101) and utilizing a 90 second dwell time on a standard steel panel.

6.3.1 Other tapes may be used by agreement between the parties involved.

6.3.2 Due to variability in adhesion strength from batch-to-batch and changes in adhesion properties of tapes over time, tape from the same batch shall be used when tests are to be run in different laboratories. When use of the same batch is not followed the test method shall be used only for ranking a series of test coatings. Refer to X1.5 for additional information

6.4 *Pressure Application Device*—Although other devices may suffice, a rubber eraser or rubber roller is commonly used to ensure good and uniform wetting of the coating with the adhesive of the tape.

6.5 *Illumination*—A light source is helpful in determining whether the cuts have been made through the film to the substrate.

7. Test Specimens

7.1 When this test method is used in the field, the specimen is the coated structure or article on which the adhesion is to be evaluated.

7.2 For laboratory use apply the materials to be tested to panels of the composition and surface conditions on which it is desired to determine the adhesion.

NOTE 2—Applicable test panel description and surface preparation methods are given in Practice D609 and Practices D1730 and D2092.

NOTE 3—Coatings should be applied in accordance with Practice D823, or as agreed upon between the purchaser and the seller.

NOTE 4—If desired or specified, the coated test panels may be subjected to a preliminary exposure such as water immersion, salt spray, or high humidity before conducting the tape test. The conditions and time of exposure will be governed by ultimate coating use or shall be agreed upon between the purchaser and seller.

8. Procedure

8.1 Select an area free of blemishes and minor surface imperfections. The area chosen for testing shall be clean and dry.

8.1.1 For specimens which have been immersed: After immersion, clean and wipe the surface with an appropriate solvent which will not harm the integrity of the coating. Then dry or prepare the surface, or both, as agreed upon between the purchaser and the seller.

8.2 Make two cuts in the film each about 40 mm (1.5 in.) long that intersect near their middle with a smaller angle of between 30 and 45°. When making the incisions, use the straightedge and cut through the coating to the substrate in one steady motion.

8.3 Inspect the incisions for reflection of light from the metal substrate to establish that the coating film has been penetrated. If the substrate has not been reached make another

X in a different location. Do not attempt to deepen a previous cut as this may affect adhesion along the incision.

8.4 At each day of testing, before initiation of testing, remove two complete laps of tape from the roll and discard. Remove an additional length at a steady (that is, not jerked) rate and cut a piece about 75 mm (3 in.) long.

8.5 Place the center of the tape at the intersection of the cuts with the tape running in the same direction as the smaller angles. Smooth the tape into place by finger in the area of the incisions taking care not to entrap air under the tape. Rub firmly over the surface of the tape with the pressure application device until the color is uniform in appearance. This indicates good, uniform contact between the tape’s adhesive and the coating surface.

8.6 Within 90 ± 30 s of application, remove the tape by seizing the free end and pulling it off rapidly (not jerked) back upon itself at as close to an angle of 180° as possible.

8.7 Inspect the X-cut area for removal of coating from the substrate or previous coating and rate the adhesion in accordance with the following scale, illustrated in Fig. 1:

Classification		Surface of "X" - Cut from which flaking/peeling has occurred
5A	No peeling or removal	None
4A	Trace peeling or removal along incisions or at their intersection	
3A	Jagged removal along incisions up to 1/16" on either side	
2A	Jagged removal along most of incisions up to 1/8" on either side	
1A	Removal from most of the area of the X under the tape	
0A	Removal beyond the area of the X	

FIG. 1 Classification of Adhesion Test Results for Test Method A