



Standard Specification for Drawing Alloy Steel, Sheet and Strip, Hot-Rolled and Cold-Rolled¹

This standard is issued under the fixed designation A507; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers hot-rolled and cold-rolled drawing alloy-steel sheet and strip. Material of this quality is produced principally for applications involving severe cold plastic deformation such as deep drawn or severely formed parts. This steel is produced by a closely controlled steel-making practice designed to assure internal soundness, relative uniformity of chemical composition, and freedom from injurious imperfections.

1.2 The material covered by this specification may be furnished in several conditions, heat treatments, surface finishes, and edges, as specified herein, in coils or cut lengths.

2. Referenced Documents

2.1 ASTM Standards:²

A505 Specification for Steel, Sheet and Strip, Alloy, Hot-Rolled and Cold-Rolled, General Requirements for A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *capable of*—as used in this specification, means that tests need not be performed. However, if application by the purchaser establishes that the material does not meet the requirements, the material shall be subject to rejection.

3.1.2 *drawing alloy steel*—alloy-steel sheet and strip intended for applications involving severe cold plastic deformation such as deep drawn or severely formed parts.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved May 1, 2016. Published May 2016. Originally approved in 1964. Last previous edition approved in 2012 as A507 – 12. DOI: 10.1520/A0507-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.3 *standard steels*—steel chemical compositions defined as “standard” by the Society of Automotive Engineers (SAE). See [Table 1](#).

3.1.4 *steels other than standard*—steel chemical compositions other than those defined as “standard,” and furnished to the composition limits shown in [Table 2](#).

4. General Requirements and Ordering Information

4.1 Material supplied to this specification shall conform to Specification A505, which includes the general requirements and establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

4.2 In addition to the Ordering Information required by Specification A505, the following shall also be included:

4.2.1 Mechanical properties, if required (show properties desired, which must be consistent with the grade and heat treatment),

4.2.2 Surface finish, if other than that normally furnished (see [Section 10](#)), and

4.2.3 Application, or end use (identification of the part to be made).

5. Manufacture

5.1 *Rolling*—The material shall be furnished either hot-rolled or cold-rolled, as specified on the order.

5.2 *Heat Treatment*—Unless otherwise specified on the order, the material shall be furnished spheroidize-annealed. (See Terminology A941 for heat treatment terms.)

5.2.1 If the material is to be heat treated by other than the producer, the order shall so state. The material may be ordered in the as-rolled condition, in such cases.

6. Chemical Requirements

6.1 The heat (cast) analysis shall conform to the requirements for the grade specified on the order.

6.1.1 Standard steels listed in [Table 1](#) are those commonly produced for drawing alloy-steel sheet and strip.

6.1.2 Nonstandard steel grades may be specified, using the ranges and limits shown in [Table 2](#).

*A Summary of Changes section appears at the end of this standard

TABLE 1 Standard Steels Commonly Produced for Drawing Alloy-Steel Sheet and Strip

Steel Designation No.	Chemical Composition Ranges and Limits, % (Heat Analysis) ^A								
	C	Mn	P	S	Si ^B	Ni	Cr	Mo	V
E3310 ^C	0.08–0.13	0.45–0.60	0.025	0.025	0.15–0.35	3.25–3.75	1.40–1.75
4012 ^C	0.09–0.14	0.75–1.00	0.025	0.025	0.15–0.35	0.15–0.25	...
4118	0.18–0.23	0.70–0.90	0.025	0.025	0.15–0.35	...	0.40–0.60	0.08–0.15	...
4130	0.28–0.33	0.40–0.60	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4135	0.33–0.38	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4137	0.35–0.40	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4140	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4142	0.40–0.45	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4145	0.43–0.48	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4147 ^C	0.45–0.50	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4150	0.48–0.53	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4320	0.17–0.22	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	0.40–0.60	0.20–0.30	...
4340	0.38–0.43	0.60–0.80	0.025	0.025	0.15–0.35	1.65–2.00	0.70–0.90	0.20–0.30	...
E4340	0.38–0.43	0.65–0.85	0.025	0.025	0.15–0.35	1.65–2.00	0.70–0.90	0.20–0.30	...
4520 ^C	0.18–0.23	0.45–0.65	0.025	0.025	0.15–0.35	0.45–0.60	...
4615	0.13–0.18	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	...	0.20–0.30	...
4620	0.17–0.22	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	...	0.20–0.30	...
4718	0.16–0.21	0.70–0.90	0.025	0.025	0.15–0.35	0.90–1.20	0.35–0.55	0.30–0.40	...
4815	0.13–0.18	0.40–0.60	0.025	0.025	0.15–0.35	3.25–3.75	...	0.20–0.30	...
4820	0.18–0.23	0.50–0.70	0.025	0.025	0.15–0.35	3.25–3.75	...	0.20–0.30	...
5015	0.12–0.17	0.30–0.50	0.025	0.025	0.15–0.35	...	0.30–0.50
5046	0.43–0.50	0.75–1.00	0.025	0.025	0.15–0.35	...	0.20–0.35
5115	0.13–0.18	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90
5120	0.17–0.22	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90
5130	0.28–0.33	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10
5132	0.30–0.35	0.60–0.80	0.025	0.025	0.15–0.35	...	0.75–1.00
5140	0.38–0.43	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90
5150	0.48–0.53	0.79–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90
5160	0.56–0.64	0.75–1.00	0.025	0.025	0.15–0.35	...	0.70–0.90
E51100 ^C	0.95–1.10	0.25–0.45	0.025	0.025	0.15–0.35	...	0.90–1.15
E52100	0.98–1.10	0.25–0.45	0.025	0.025	0.15–0.35	...	1.30–1.60
6150	0.48–0.53	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	...	0.15 min
6158 ^C	0.55–0.62	0.70–1.10	0.025	0.015	0.15–0.35	...	0.90–1.20	...	0.10–0.20
8615	0.13–0.18	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8617	0.15–0.20	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8620	0.18–0.23	0.70–0.90	0.035	0.035	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8630	0.28–0.33	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8640	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8642 ^C	0.40–0.45	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8645	0.43–0.48	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8650 ^C	0.48–0.53	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8655	0.51–0.59	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8660	0.55–0.65	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8720	0.18–0.23	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
8735 ^C	0.33–0.38	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
8740 ^C	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
9260	0.56–0.64	0.75–1.00	0.025	0.025	1.80–2.20
9262 ^C	0.55–0.65	0.75–1.00	0.025	0.025	1.80–2.20	...	0.25–0.40
E9310 ^C	0.08–0.13	0.45–0.65	0.025	0.025	0.20–0.35	3.00–3.50	1.00–1.40	0.08–0.15	...

^A The chemical ranges and limits shown are subject to product analysis tolerances. See Specification A505.

^B Other silicon limits can be substituted on agreement between the purchaser and producer.

^C Not an S.A.E. Steel Designation.

7. Metallurgical Structure

7.1 Microstructure:

7.1.1 *Requirements*—At least 75 % of the carbide microstructure shall be of the globular type.

7.1.2 *Number of Tests*—The number of tests shall be in accordance with the producer's standard quality control procedures. A specific number of tests is not required, but the material shall be produced by manufacturing practices established to assure compliance with the specified requirements. The material shall be subjected to mill tests and inspection procedures to assure such compliance. For government procurement, mill tests and inspection procedures utilized to

show conformance to the microstructure requirements shall be made available on request.

8. Mechanical Requirements

8.1 Tension and Hardness Tests:

8.1.1 *Requirements*—When tension tests or hardness tests, or both are specified on the order, the test results shall conform to the requirements specified on the order. Yield strength, tensile strength, and elongation requirements may be specified. The tensile properties will vary depending on the chemical composition, condition, and heat treatment. Producers are frequently consulted as to grade, resultant mechanical