



Designation: B298 – 12 (Reapproved 2017)

Standard Specification for Silver-Coated Soft or Annealed Copper Wire¹

This standard is issued under the fixed designation B298; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers silver-coated, soft or annealed, round copper wire, intended for use in electrical equipment, as follows:

1.1.1 *Class A*—Wire whose silver coating is at least 1.25 % of the total weight of the coated wire.

1.1.2 *Class B*—Wire whose silver coating is at least 2.50 % of the total weight of the coated wire.

1.1.3 *Class C*—Wire whose silver coating is at least 4.00 % of the total weight of the coated wire.

1.1.4 *Class D*—Wire whose silver coating is at least 6.10 % of the total weight of the coated wire.

1.1.5 *Class E*—Wire whose silver coating is at least 10.00 % of the total weight of the coated wire.

1.2 Silver-coated wire having different minimum percentages of silver by weight may be obtained by mutual agreement between the manufacturer and the purchaser. For information purposes the thickness of coating in microinches provided by the percentages listed above is shown in [Table 1](#) (Explanatory [Note 1](#)).

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3.1 *Exceptions*—The SI values for density, resistivity, and volume are to be regarded as standard.

1.4 The following precautionary caveat pertains only to the test method section of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific precautionary statements see [8.4.1.2](#) and Explanatory [Note 2](#).

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.04 on Conductors of Copper and Copper Alloys.

Current edition approved April 1, 2017. Published April 2017. Originally approved in 1955. Last previous edition approved in 2012 as B298 – 12. DOI: 10.1520/B0298-12R17.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect at the time of reference form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

[B49 Specification for Copper Rod for Electrical Purposes](#)
[B193 Test Method for Resistivity of Electrical Conductor Materials](#)

[B258 Specification for Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors](#)

[E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials](#)

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size,

3.1.2 Wire size, diameter in inches (see [5.3](#) and [Table 1](#)),

3.1.3 Class of coating (Section [1](#) and [Table 1](#)),

3.1.4 Type of copper, if special (see [4.2](#)),

3.1.5 Place of inspection (see [9.1](#)), and

3.1.6 Packaging and Package Marking (Section [10](#)).

3.1.7 In addition supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or purchase order for direct procurement by agencies of the U.S. Government (see S1, S2, and S3).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Tensile Requirements

Diameter, in.	Area at 20°C		Elongation in 10 in., min, %	Thickness of Coating, μ in. (For Information Only)				
	cmils	in. ²		Class A, 1.25 % Silver	Class B, 2.50 % Silver	Class C, 4.00 % Silver	Class D, 6.10 % Silver	Class E, 10.00 % Silver
0.1285	16 510	0.01297	30	340	680	1 090	1 659	2 720
0.1144	13 090	0.01028	30	303	605	970	1 477	2 422
0.1019	10 380	0.008155	25	270	539	864	1 316	2 157
0.0907	8 230	0.00646	25	240	480	768	1 171	1 941
0.0808	6 530	0.00513	25	214	428	684	1 043	1 710
0.0720	5 180	0.00407	25	190	381	610	930	1 524
0.0641	4 110	0.00323	25	170	339	542	828	1 357
0.0571	3 260	0.00256	25	151	302	483	737	1 209
0.0508	2 580	0.00203	25	134	269	430	656	1 075
0.0453	2 050	0.00161	25	120	240	383	585	959
0.0403	1 620	0.00128	25	107	213	341	520	853
0.0359	1 290	0.00101	25	95	190	304	464	760
0.0320	1 020	0.000804	25	85	169	270	413	677
0.0285	812	0.000638	25	75	151	241	368	603
0.0253	640	0.000503	25	67	134	214	327	536
0.0226	511	0.000401	25	60	120	191	292	478
0.0201	404	0.00317	20	53	106	170	260	425
0.0179	320	0.000252	20	47	95	151	231	379
0.0159	253	0.000199	20	42	84	135	205	337
0.0142	202	0.000158	20	...	75	120	183	301
0.0126	159	0.000125	20	...	67	107	163	267
0.0113	128	0.000100	20	...	60	96	146	239
0.0100	100	0.0000785	20	...	53	85	129	212
0.0089	79.2	0.0000622	15	...	47	75	115	188
0.0080	64.0	0.0000503	15	...	42	68	103	169
0.0071	50.4	0.0000396	15	60	92	150
0.0063	39.7	0.0000312	15	53	81	133
0.0056	31.4	0.0000246	15	47	72	119
0.0050	25.0	0.0000196	15	42	65	106
0.0045	20.2	0.0000159	15	58	95
0.0040	16.0	0.0000126	15	52	85
0.0035	12.2	0.00000962	15	45	74
0.0031	9.61	0.00000755	15	40	66
0.0028	7.84	0.00000616	10	59
0.0025	6.25	0.00000491	10	53
0.0022	4.84	0.00000380	10	47
0.0020	4.00	0.00000314	10	42

4. Materials and Manufacture

4.1 The material shall be silver-coated copper wire (Explanatory Note 2), of such quality and purity that the finished product shall have the properties and characteristics prescribed in this specification.

NOTE 1—The following specifications define copper suitable for use: Specification B49.

4.2 Copper of special qualities, forms, or types, as may be agreed upon between the manufacturer and the purchaser, and that will conform to the requirements prescribed in this specification may also be used.

5. General Requirements

5.1 *Tensile Properties*—The silver-coated wire shall conform to the requirements for elongation prescribed in Table 1. No requirements for tensile strength are specified. For wire whose nominal diameter is more than 0.001 in. (0.025 mm) greater than a size listed in Table 1, but less than that of the next larger size, the requirements of the next larger size shall apply.

5.2 *Resistivity*—The electrical resistivity of the coated wire at a temperature of 20°C shall not exceed 875.20 ohms-lb/mile².

5.3 *Dimensions and Permissible Variations*—The wire sizes shall be expressed as the diameter of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.0025 mm) (Explanatory Note 3). The coated wire shall not vary from the specified diameter by more than the following amounts:

Nominal Diameter, in.	Permissible Variations in Diameter, plus and minus
Under 0.0100	0.0001 in. (0.1 mil)
0.0100 or over	1 %

5.4 *Continuity of Coating*—The coating shall be continuous. The continuity of the coating shall be determined on representative samples taken before stranding or insulating and shall be determined by the sodium polysulfide test, in accordance with 8.4. Wire whose coating weight corresponds to a thickness less than 40 μ in. (0.00004 in.) shall not be subject to this test (Explanatory Note 4).

5.5 *Weight of Coating*—The weight of coating expressed in percent of the total weight of the wire shall be not less than 1.25 % for Class A; 2.50 % for Class B; 4.00 % for Class C; 6.10 % for Class D; and 10.00 % for Class E. When coatings other than these classes are required, the weight of the coating shall be not less than that specified. For ease of comparison, the thickness of coating for these classes has been included in Table 1 (Explanatory Note 4).

5.6 *Joints*—Necessary joints in the wire and rods prior to final plating and drawing shall be made in accordance with the best commercial practice. Joints made after plating shall not be allowed to remain in the final product.

5.7 *Finish*—The coating shall consist of a smooth continuous layer, firmly adherent to the surface of the copper. The wire shall be bright and free from all imperfections not consistent with the best commercial practice.

6. Conformance Criteria (Explanatory Note 5)

6.1 Any lot of wire, the samples of which comply with the conformance criteria of this section, shall be considered as complying with the requirements of Section 5. Individual production units that fail to meet one or more of the requirements shall be rejected. Failure of a sample group from a lot to meet one or more of the following criteria shall constitute cause for rejection of the lot. The conformance criteria for each of the prescribed properties given in Section 5 are as follows:

6.1.1 *Elongation*—The lot shall be considered conforming if the elongation of each of the selected specimens is not less than the elongation value in Table 1.

6.2 *Resistivity*—The electrical resistivity of each of the four specimens shall conform to the requirements of 5.2. Failure to meet these requirements shall constitute failure to meet the resistivity conformance criterion.

6.3 *Dimensions*—The dimensions of the first sample (Table 2) shall conform to the requirements of 5.3. If there are no failures, the lot conforms to this requirement. If there are failures, but the number of these do not exceed the allowable defect number, c_2 (Table 2), for the respective number of units in the sample, a second sample equal to n_2 shall be taken and the total defects of the n plus n_2 units shall not exceed the allowable defect number, c_2 . Failure to meet this requirement shall constitute failure to meet the dimensional conformance criterion.

6.4 *Continuity of Coating*—The continuity of the coating of each of the eight specimens shall conform to the requirements of 5.4. Failure of more than two specimens shall constitute failure to meet the continuity criterion. If not more than two specimens fail to meet the continuity criteria, eight additional specimens from the lot shall be tested, all of which shall conform to the continuity criteria. However, any individual production unit, the specimen from which failed to meet the continuity criteria, shall be rejected.

6.5 *Weight of Coating*—The weight of coating of each of the four specimens shall conform to the requirements of 5.5. Failure of more than one specimen shall constitute failure to meet the weight criteria. If only one specimen fails to meet the weight criteria, four additional specimens from the lot shall be tested, all of which shall conform to the weight criterion. However, any individual production unit, the specimen from which failed the weight criteria, shall be rejected.

6.6 *Packaging*—Conformance to the packaging requirements specified by the purchaser shall be determined in accordance with Table 3. The number of units in the sample showing nonconformance to the requirements shall not exceed the allowable defect number, c , in Table 3. Failure to meet this requirement shall constitute failure to meet the packaging conformance criterion.

7. Density

7.1 For the purpose of calculating weights, cross-sections, etc., the density of the copper shall be taken as 8.89 g/cm³ (0.32117 lb/in.³) at 20°C (Explanatory Note 6). The density of silver shall be taken as 10.5 g/cm³ (0.1 mil) (0.37933 lb/in.³).

8. Test Methods

8.1 *Tensile Strength and Elongation:*

8.1.1 No test for tensile strength shall be required.

8.1.2 The elongation of wire with a nominal diameter greater than 0.0808 in. (2.052 mm) shall be determined as the permanent increase in length due to the breaking of the wire in tension (see Explanatory Note 7). The elongation shall be measured between gage marks placed originally 10 in. (242 mm) apart upon the test specimen and expressed in percent of the original length.

8.1.3 The elongation of wire with a nominal diameter equal to or less than 0.0808 in. (2.053 mm) may be determined as described above or by measurements made between the jaws of the testing machine. When measurements are made between the jaws, the zero length shall be the distance between the jaws at the start of the tension test and be as near 10 in. (254 mm) as practicable. The final length shall be the distance between the jaws at the time of rupture. The fracture shall be between gage marks or jaws of the testing machine, depending on method used, and not closer than 1 in. (25.4 mm) to either gage mark or jaw.

8.2 *Resistivity*—The electrical resistivity of the material shall be determined in accordance with Test Method B193

TABLE 2 Sampling for Dimensional Measurements and Surface Finish

Number of Units in Lot	First Sample		Second Sample		Allowable Number of Defects in Both Sample c^2
	Number of Units in Sample, n_1	Allowable Number of Defects in First Sample, c_1	Number of Units in Sample, n_2	$n_1 + n_2$	
1 to 14, incl	All	0
15 to 50, incl	14	0
51 to 100, incl	19	0	23	42	1
101 to 200, incl	24	0	46	70	2
201 to 400, incl	29	0	76	105	3
401 to 800, incl	33	0	112	145	4
Over 800	34	0	116	150	4