



# Standard Specification for Nickel-Iron-Chromium-Silicon Alloy Bars and Shapes<sup>1</sup>

This standard is issued under the fixed designation B511/B511M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification<sup>2</sup> covers wrought alloys UNS N08330 and UNS N08332 in the form of hot-finished and cold-finished bar and shapes intended for heat-resisting applications and general corrosive service.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

**B536** Specification for Nickel-Iron-Chromium-Silicon Alloys (UNS N08330 and N08332) Plate, Sheet, and Strip

**B880** Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

**E8** Test Methods for Tension Testing of Metallic Materials

**E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

**E112** Test Methods for Determining Average Grain Size

**E1473** Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bar, n*—material round, rectangular, hexagonal, octagonal, or square solid section, furnished in straight lengths.

3.1.2 *shapes, n*—material of solid section in such forms as angles, channels, tees, I-beams, and four-fluted bars.

## 4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to the following:

4.1.1 Alloy (**Table 1**),

4.1.2 Quantity (weight or number of pieces),

4.1.3 ASTM designation and year of issue,

4.1.4 Section (round, square, I-beam, etc.),

4.1.5 Dimension, including length,

4.1.6 *Certification*—State if certification is required.

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis shall be furnished.

4.1.8 *Purchaser Inspection*—If a purchaser wishes to witness tests or inspections of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

## 5. Materials and Manufacture

5.1 All material shall be furnished in the heat-treated condition, except that cold-drawn hexagons may be given a cold-draw sizing pass subsequent to the final heat treatment.

NOTE 1—Hot-finished rectangular bar in widths 10 in. [2504 mm] and under may be furnished as hot-finished plate with sheared or cut edges in accordance with Specification **B536**.

## 6. Chemical Composition

6.1 The material shall conform to the requirements as to chemical composition specified in **Table 2**.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in accordance with Specification **B880**.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved May 1, 2016. Published May 2016. Originally approved in 1970. Last previous edition approved in 2009 as B511 – 01 (2009). DOI: 10.1520/B0511\_B0511M-16.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-511 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



**TABLE 1 Mechanical Properties**

Alloy	Condition	Tensile Strength, min, psi [MPa]	Yield Strength 0.2 % off-set, min, psi [MPa]	Elongation in 2 in. or 50 mm, or 4D, min, %
UNS N08330	annealed	70 000 [485]	30 000 [210]	30 <sup>A</sup>
UNS N08332	annealed	67 000 [465]	27 000 [190]	30

<sup>A</sup> Applies to round bar only. For other bar cross-sections and shapes the minimum elongation shall be 25 %.

**TABLE 2 Chemical Requirements**

Element	Composition Limits, %
C	... <sup>A</sup>
Mn	2.00 max
P	0.03 max
S	0.03 max
Si	0.75–1.50
Cr	17.0–20.0
Ni	34.0–37.0
Cu	1.00 max
Pb	0.005 max
Sn	0.025 max
Fe	remainder <sup>B</sup>

<sup>A</sup> Alloy UNS N08330: 0.08 max.

Alloy UNS N08332: 0.05–0.10.

<sup>B</sup> Element shall be determined arithmetically by difference.

**7. Mechanical and Other Properties**

7.1 The mechanical properties of the material at room temperature shall conform to those shown in **Table 1**.

7.2 *Grain Size*—Annealed alloy UNS N08332 shall conform to an average grain size of ASTM No. 5 or coarser.

7.3 *Annealing Temperature*—Alloy UNS N08330 shall be annealed at 1900°F [1040°C] minimum. Alloy UNS N08332 shall be annealed at 2100°F [1150°C] minimum.

**8. Dimensions and Permissible Variations**

8.1 All bars and shapes shall conform to the permissible variations in dimensions specified in **Tables 3-14**, inclusive.

**9. Workmanship, Finish, and Appearance**

9.1 The material shall be uniform in quality and temper, smooth, commercially straight, and free of injurious imperfections.

**10. Sampling**

10.1 *Lot Definition*:

10.1.1 A lot for chemical analysis shall consist of one heat.

10.1.2 A lot for mechanical properties and grain size testing shall consist of material from one heat of the same condition and cross section, and in no case more than 30 000 lb [13 600 kg] in weight.

10.2 *Test Material Selection*:

10.2.1 *Chemical Analysis*—Representative samples from each lot shall be taken during pouring or subsequent processing.

10.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

10.2.2 *Mechanical Properties and Grain Size*—Samples of the material to provide test specimens for mechanical properties and grain size shall be taken from such locations in each lot as to be representative of that lot.

**TABLE 3 Permissible Variations in Size of Hot-Rolled Round and Square Bars**

NOTE 1—Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section.

NOTE 2—Out-of-square section is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

NOTE 3—Size tolerances for rounds in the size range from ¼ to 5/16 in. [6.5 to 8.0 mm], incl, and for rounds in the size range from ¼ in. [6.5 mm] to approximate 5/8 in. [15.5 mm], which are produced on rod mills in coils, are not shown herein.

NOTE 4—Variations in size of coiled product made on rod mills are greater than size tolerances for product made on bar mills.

Specified Size		Size Tolerance				Out-of-Round (Note 1) or Out-of-Square Section (Note 2)	
		Over		Under		in.	[mm]
in.	[mm]	in.	[mm]	in.	[mm]		
¼ to 5/16	[6.5 to 8.0]	0.005	[0.13]	0.005	[0.13]	0.008	[0.20]
Over 5/16 to 7/16	[8.0 to 11.0]	0.006	[0.15]	0.006	[0.15]	0.009	[0.23]
Over 7/16 to 5/8	[11.0 to 15.5]	0.007	[0.18]	0.007	[0.18]	0.010	[0.26]
Over 5/8 to 7/8	[15.5 to 22.0]	0.008	[0.20]	0.008	[0.20]	0.012	[0.30]
Over 7/8 to 1	[22.0 to 25.0]	0.009	[0.23]	0.009	[0.23]	0.013	[0.34]
Over 1 to 1 1/8	[25.0 to 28.0]	0.010	[0.25]	0.010	[0.25]	0.015	[0.38]
Over 1 1/8 to 1 1/4	[28.0 to 31.5]	0.011	[0.28]	0.011	[0.28]	0.016	[0.42]
Over 1 1/4 to 1 3/8	[31.5 to 34.5]	0.012	[0.30]	0.012	[0.30]	0.018	[0.46]
Over 1 3/8 to 1 1/2	[34.5 to 38.0]	0.014	[0.35]	0.014	[0.35]	0.021	[0.53]
Over 1 1/2 to 2	[38.0 to 50.0]	1/64	[0.40]	1/64	[0.40]	0.023	[0.60]
Over 2 to 2 1/2	[50.0 to 63.0]	1/32	[0.80]	0	[0]	0.023	[0.60]
Over 2 1/2 to 3 1/2	[63.0 to 90.0]	3/64	[1.20]	0	[0]	0.035	[0.90]
Over 3 1/2 to 4 1/2	[90.0 to 115.0]	1/16	[1.60]	0	[0]	0.046	[1.20]
Over 4 1/2 to 5 1/2	[115.0 to 140.0]	5/64	[2.0]	0	[0]	0.058	[1.50]
Over 5 1/2 to 6 1/2	[140.0 to 165.0]	1/8	[3.00]	0	[0]	0.070	[1.80]
Over 6 1/2 to 8	[165.0 to 200.0]	5/32	[4.00]	0	[0]	0.085	[2.20]