



Standard Specification for Autocatalytic (Electroless) Nickel-Phosphorus Coatings on Metal¹

This standard is issued under the fixed designation B733; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers requirements for autocatalytic (electroless) nickel-phosphorus coatings applied from aqueous solutions to metallic products for engineering (functional) uses.

1.2 The coatings are alloys of nickel and phosphorus produced by autocatalytic chemical reduction with hypophosphite. Because the deposited nickel alloy is a catalyst for the reaction, the process is self-sustaining. The chemical and physical properties of the deposit vary primarily with its phosphorus content and subsequent heat treatment. The chemical makeup of the plating solution and the use of the solution can affect the porosity and corrosion resistance of the deposit. For more details, see ASTM STP 265 (1)² and Refs (2) (3) (4) and (5).

1.3 The coatings are generally deposited from acidic solutions operating at elevated temperatures.

1.4 The process produces coatings of uniform thickness on irregularly shaped parts, provided the plating solution circulates freely over their surfaces.

1.5 The coatings have multifunctional properties, such as hardness, heat hardenability, abrasion, wear and corrosion resistance, magnetics, electrical conductivity provide diffusion barrier, and solderability. They are also used for the salvage of worn or mismachined parts.

1.6 The low phosphorus (2 to 4 % P) coatings are microcrystalline and possess high as-plated hardness (620 to 750 HK 100). These coatings are used in applications requiring abrasion and wear resistance.

1.7 Lower phosphorus deposits in the range between 1 and 3 % phosphorus are also microcrystalline. These coatings are used in electronic applications providing solderability,

bondability, increased electrical conductivity, and resistance to strong alkali solutions.

1.8 The medium phosphorous coatings (5 to 9 % P) are most widely used to meet the general purpose requirements of wear and corrosion resistance.

1.9 The high phosphorous (more than 10 % P) coatings have superior salt-spray and acid resistance in a wide range of applications. They are used on beryllium and titanium parts for low stress properties. Coatings with phosphorus contents greater than 11.2 % P are not considered to be ferromagnetic.

1.10 The values stated in SI units are to be regarded as standard.

1.11 The following precautionary statement pertains only to the test method portion, Section 9, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:³

B368 Test Method for Copper-Accelerated Acetic Acid-Salt Spray (Fog) Testing (CASS Test)

B374 Terminology Relating to Electroplating

B380 Test Method for Corrosion Testing of Decorative Electrodeposited Coatings by the Corrodokote Procedure

B487 Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section

B499 Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals

B504 Test Method for Measurement of Thickness of Metallic Coatings by the Coulometric Method

¹ This specification is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.03 on Engineering Coatings.

Current edition approved Nov. 1, 2015. Published November 2015. Originally approved in 1984. Last previous edition approved in 2014 as B733 – 09(2014). DOI: 10.1520/B0733-15.

² The boldface numbers given in parentheses refer to a list of references at the end of the text.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [B537 Practice for Rating of Electroplated Panels Subjected to Atmospheric Exposure](#)
- [B567 Test Method for Measurement of Coating Thickness by the Beta Backscatter Method](#)
- [B568 Test Method for Measurement of Coating Thickness by X-Ray Spectrometry](#)
- [B571 Practice for Qualitative Adhesion Testing of Metallic Coatings](#)
- [B578 Test Method for Microhardness of Electroplated Coatings](#)
- [B602 Test Method for Attribute Sampling of Metallic and Inorganic Coatings](#)
- [B667 Practice for Construction and Use of a Probe for Measuring Electrical Contact Resistance](#)
- [B678 Test Method for Solderability of Metallic-Coated Products](#)
- [B697 Guide for Selection of Sampling Plans for Inspection of Electrodeposited Metallic and Inorganic Coatings](#)
- [B762 Test Method of Variables Sampling of Metallic and Inorganic Coatings](#)
- [B849 Specification for Pre-Treatments of Iron or Steel for Reducing Risk of Hydrogen Embrittlement](#)
- [B850 Guide for Post-Coating Treatments of Steel for Reducing the Risk of Hydrogen Embrittlement](#)
- [B851 Specification for Automated Controlled Shot Peening of Metallic Articles Prior to Nickel, Autocatalytic Nickel, or Chromium Plating, or as Final Finish](#)
- [D1193 Specification for Reagent Water](#)
- [D2670 Test Method for Measuring Wear Properties of Fluid Lubricants \(Falex Pin and Vee Block Method\)](#)
- [D2714 Test Method for Calibration and Operation of the Falex Block-on-Ring Friction and Wear Testing Machine](#)
- [D3951 Practice for Commercial Packaging](#)
- [D4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser](#)
- [E60 Practice for Analysis of Metals, Ores, and Related Materials by Spectrophotometry](#)
- [E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness](#)
- [E156 Test Method for Determination of Phosphorus in High-Phosphorus Brazing Alloys \(Photometric Method\) \(Withdrawn 1993\)⁴](#)
- [E352 Test Methods for Chemical Analysis of Tool Steels and Other Similar Medium- and High-Alloy Steels](#)
- [F519 Test Method for Mechanical Hydrogen Embrittlement Evaluation of Plating/Coating Processes and Service Environments](#)
- [G5 Reference Test Method for Making Potentiodynamic Anodic Polarization Measurements](#)
- [G31 Guide for Laboratory Immersion Corrosion Testing of Metals](#)
- [G59 Test Method for Conducting Potentiodynamic Polarization Resistance Measurements](#)

- [G85 Practice for Modified Salt Spray \(Fog\) Testing](#)
- 2.2 *Military Standards:*
- [MIL-R-81841 Rotary Flap Peening of Metal Parts⁵](#)
- [MIL-S-13165 Shot Peening of Metal Parts⁵](#)
- [MIL-STD-105 Sampling Procedures and Tables for Inspection by Attribute⁵](#)
- 2.3 *ISO Standards:*
- [ISO 4527 Autocatalytic Nickel-Phosphorus Coatings—Specification and Test Methods⁶](#)

3. Terminology

3.1 Definitions:

3.1.1 *significant surfaces*—those substrate surfaces which the coating must protect from corrosion or wear, or both, and that are essential to the performance.

3.2 *Other Definitions*—Terminology [B374](#) defines most of the technical terms used in this specification.

4. Coating Classification

4.1 The coating classification system provides for a scheme to select an electroless nickel coating to meet specific performance requirements based on alloy composition, thickness and hardness.

4.1.1 TYPE describes the general composition of the deposit with respect to the phosphorus content and is divided into five categories which establish deposit properties (see [Table 1](#)).

NOTE 1—Due to the precision of some phosphorus analysis methods a deviation of 0.5 % has been designed into this classification scheme. Rounding of the test results due to the precision of the limits provides for an effective limit of 4.5 and 9.5 % respectively. For example, coating with a test result for phosphorus of 9.7 % would have a classification of TYPE V, see [Appendix X5](#), Alloy TYPES.

4.2 Service Condition Based on Thickness:

4.2.1 Service condition numbers are based on the severity of the exposure in which the coating is intended to perform and minimum coating thickness to provide satisfactory performance (see [Table 2](#)).

4.2.2 *SC0 Minimum Service*, 0.1 μm—This is defined by a minimum coating thickness to provide specific material properties and extend the life of a part or its function. Applications include requirements for diffusion barrier, undercoat, electrical conductivity and wear and corrosion protection in specialized environments.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

TABLE 1 Deposit Alloy Types

Type	Phosphorus % wt
I	No Requirement for Phosphorus
II	1 to 3
III	2 to 4
IV	5 to 9
V	10 and above

⁴ The last approved version of this historical standard is referenced on www.astm.org.

**TABLE 2 Service Conditions
Coating Thickness Requirements**

Service Condition	Minimum Coating Thickness Specification	µm	in.
SC0	Minimum Thickness	0.1	0.000004
SC1	Light Service	5	0.0002
SC2	Mild Service	13	0.0005
SC3	Moderate Service	25	0.001
SC4	Severe Service	75	0.003

4.2.3 *SC1 Light Service, 5 µm*—This is defined by a minimum coating thickness of 5 µm for extending the life of the part. Typical environments include light-load lubricated wear, indoor corrosion protection to prevent rusting, and for soldering and mild abrasive wear.

4.2.4 *SC2 Mild Service, 13 µm*—This is defined by mild corrosion and wear environments. It is characterized by industrial atmosphere exposure on steel substrates in dry or oiled environments.

4.2.5 *SC3 Moderate Service, 25 µm*—This is defined by moderate environments such as non marine outdoor exposure, alkali salts at elevated temperature, and moderate wear.

4.2.6 *SC4 Severe Service, 75 µm*—This is defined by a very aggressive environment. Typical environments would include acid solutions, elevated temperature and pressure, hydrogen sulfide and carbon dioxide oil service, high-temperature chloride systems, very severe wear, and marine immersion.

NOTE 2—The performance of the autocatalytic nickel coating depends to a large extent on the surface finish of the article to be plated and how it was pretreated. Rough, non uniform surfaces require thicker coatings than smooth surfaces to achieve maximum corrosion resistance and minimum porosity.

4.3 *Post Heat Treatment Class*—The nickel-phosphorus coatings shall be classified by heat treatment after plating to increase coating adhesion and or hardness (see [Table 3](#)).

4.3.1 *Class 1*—As-deposited, no heat treatment.

4.3.2 *Class 2*—Heat treatment at 260 to 400°C to produce a minimum hardness of 850 HK100.

4.3.3 *Class 3*—Heat treatment at 180 to 200°C for 2 to 4 h to improve coating adhesion on steel and to provide for hydrogen embrittlement relief (see section [6.6](#)).

TABLE 3 Classification of Post Heat Treatment

CLASS	Description	Temperature (°C)	Time (h)
1	No Heat Treatment, As Plated		
2	Heat Treatment for Maximum Hardness TYPE I	260	20
		285	16
		320	8
		400	1
		350 to 380	1
	TYPE II	360 to 390	1
	TYPE III	365 to 400	1
	TYPE IV	375 to 400	1
	TYPE V		
3	Adhesion on Steel	180 to 200	2 to 4
4	Adhesion, Carburized Steel and Age Hardened Aluminum	120 to 130	1 to 6
5	Adhesion on Beryllium and Aluminum	140 to 150	1 to 2
6	Adhesion on Titanium	300–320	1–4

4.3.4 *Class 4*—Heat treatment at 120 to 130°C for at least 1 h to increase adhesion of heat-treatable (age-hardened) aluminum alloys and carburized steel (see [Note 3](#)).

4.3.5 *Class 5*—Heat treatment at 140 to 150°C for at least 1 h to improve coating adhesion for aluminum, non age-hardened aluminum alloys, copper, copper alloys and beryllium.

4.3.6 *Class 6*—Heat treatment at 300 to 320°C for at least 1 h to improve coating adhesion for titanium alloys.

NOTE 3—Heat-treatable aluminum alloys such as Type 7075 can undergo microstructural changes and lose strength when heated to over 130°C.

5. Ordering Information

5.1 The following information shall be supplied by the purchaser in either the purchase order or on the engineering drawing of the part to be plated:

5.1.1 Title, ASTM designation number, and year of issue of this specification.

5.1.2 Classification of the deposit by type, service condition, class, (see [4.1](#), [4.2](#) and [4.3](#)).

5.1.3 Specify maximum dimension and tolerance requirements, if any.

5.1.4 Peening, if required (see [6.5](#)).

5.1.5 The tensile strength of the material in MPa (see [6.3.1](#) and [6.6](#)).

5.1.6 Stress relief heat treatment before plating, (see [6.3](#)).

5.1.7 Hydrogen Embrittlement Relief after plating, (see [6.6](#)).

5.1.8 Significant surfaces and surfaces not to be plated must be indicated on drawings or sample.

5.1.9 Supplemental or Special Government Requirements such as, specific phosphorus content, abrasion wear or corrosion resistance of the coating, solderability, contact resistance and packaging selected from Supplemental Requirements.

5.1.10 Requirement for a vacuum, inert or reducing atmosphere for heat treatment above 260°C to prevent surface oxidation of the coating (see [S3](#)).

5.1.11 Test methods for coating adhesion, composition, thickness, porosity, wear and corrosion resistance, if required, selected from those found in Section [9](#) and Supplemental Requirements.

5.1.12 Requirements for sampling (see Section [8](#)).

NOTE 4—The purchaser should furnish separate test specimens or coupons of the basis metal for test purposes to be plated concurrently with the articles to be plated (see [8.4](#)).

6. Materials and Manufacture

6.1 *Substrate*—Defects in the surface of the basis metal such as scratches, porosity, pits, inclusions, roll and die marks, laps, cracks, burrs, cold shuts, and roughness may adversely affect the appearance and performance of the deposit, despite the observance of the best plating practice. Any such defects on significant surfaces shall be brought to the attention of the purchaser before plating. The producer shall not be responsible for coatings defects resulting from surface conditions of the metal, if these conditions have been brought to the attention of the purchaser.