



Designation: C 36/C 36M – 03^{e1}

Standard Specification for Gypsum Wallboard¹

This standard is issued under the fixed designation C 36/C 36M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{e1} NOTE—The word rating(s) was added to the term fire resistance throughout editorially October 2004.

1. Scope*

1.1 This specification covers gypsum wallboard which is designed to be used for walls, ceilings, or partitions and affords a surface suitable to receive decoration.

NOTE 1—Specification C 840 contains application procedures for gypsum wallboard.

1.2 The values stated in either inch-pound or SI (metric) units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system shall be used independent of the other. Values from the two systems shall not be combined.

1.3 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:²

- C 11 Terminology Relating to Gypsum and Related Building Materials and Systems
- C 473 Test Methods for Physical Testing of Gypsum Panel Products
- C 645 Specification for Nonstructural Steel Framing Members
- C 840 Specification for Application and Finishing of Gypsum Wallboard
- C 1264 Specification for Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage of Gypsum Board
- E 84 Test Method for Surface Burning Characteristics of Building Materials

E 96 Test Methods for Water Vapor Transmission of Materials

E 119 Test Methods for Fire Tests of Building Construction and Materials

3. Terminology

3.1 Definitions of terms shall be in accordance with Terminology C 11.

4. Materials and Manufacture

4.1 Gypsum wallboard shall consist of a noncombustible core, essentially gypsum, surfaced with paper bonded to the core.

4.2 Foil-backed gypsum wallboard shall consist of gypsum wallboard with a layer of aluminum foil laminated to the back surface.

4.3 Gypsum wallboard, type X (special fire-resistant) designates gypsum wallboard complying with this specification that provides not less than 1-h fire resistance rating for boards $\frac{5}{8}$ in. [15.9 mm] thick or $\frac{3}{4}$ -h fire resistance rating for boards $\frac{1}{2}$ in. [12.7 mm] thick, applied parallel with and on each side of load bearing 2×4 wood studs spaced 16 in. [406 mm] o.c. with 6d coated nails, $\frac{1}{8}$ in. [48 mm] long, 0.0915 in. [2.32 mm] diameter shank, $\frac{1}{4}$ in. [6.4 mm] diameter heads, spaced 7 in. [178 mm] o.c. with wallboard joints staggered 16 in. [406 mm] on each side of the partition and tested in accordance with the requirements of Test Methods E 119.

NOTE 2—Consult producers for independent test data on assembly details and fire resistance ratings for other types of construction. See fire test reports, or listings from recognized fire testing laboratories, for assembly particulars, materials, and ratings.

4.4 Gypsum wallboard shall have a flame spread index of not more than 25 when tested in accordance with Test Method E 84.

5. Physical Properties

5.1 Specimens shall be taken from the samples obtained in accordance with Specification C 1264.

5.2 Specimens shall be tested in accordance with Test Methods C 473.

¹This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products.

Current edition approved Oct. 1, 2003. Published November 2003. Originally approved in 1921. Last previous edition approved in 2001 as C 36/C 36M – 01.

²For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

5.2.1 *Flexural Strength*—The specimens shall be tested face up and face down. The average breaking load shall be not less than the following:

Thickness, in. [mm]	Method A		Method B	
	Load, lbf [N] Bearing Edges Across Fiber of Surfacing	Load, lbf [N] Bearing Edges Parallel to Fiber of Surfacing	Load, lbf [N] Bearing Edges Across Fiber of Surfacing	Load, lbf [N] Bearing Edges Parallel to Fiber of Surfacing
¼ [6.4]	50 [222]	20 [89]	46 [205]	16 [71]
⅜ [7.9]	65 [289]	25 [111]	62 [276]	21 [93]
½ [9.5]	80 [356]	30 [133]	77 [343]	26 [116]
⅝ [12.7]	110 [489]	40 [178]	107 [476]	36 [160]
¾ [15.9]	150 [667]	50 [222]	147 [654]	46 [205]
¾ [19.0]	170 [756]	60 [267]	167 [743]	56 [249]

5.2.2 *Humidified Deflection*—The specimens shall have an average deflection of not more than the following:

Thickness, in. [mm]	Humidified Deflection, Eighths of an inch [mm]
¼ [6.4]	not required
⅜ [7.9]	not required
½ [9.5]	15 [48]
⅝ [12.7]	10 [32]
¾ [15.9]	5 [16]
¾ [19.0]	5 [16]

5.2.3 *Core, End, and Edge Hardness*—The specimens shall have an average hardness of not less than 15 lbf [67 N] when tested by Method A and 11 lbf [49 N] when tested by Method B.

5.2.4 *Nail Pull Resistance*—The specimen shall have an average nail pull resistance of not less than the following:

Thickness, in. [mm]	Method A	Method B
	Nail Pull Resistance, lbf [N]	Nail Pull Resistance, lbf [N]
¼ [6.4]	40 [180]	36 [160]
⅜ [7.9]	50 [220]	46 [200]
½ [9.5]	60 [270]	56 [250]
⅝ [12.7]	80 [360]	77 [340]
¾ [15.9]	90 [400]	87 [390]
¾ [19.0]	100 [440]	97 [430]

5.3 *Foil-Backed Gypsum Wallboard:*

5.3.1 Foil-backed gypsum wallboard shall meet all of the requirements for gypsum wallboard.

5.3.2 When tested in accordance with Test Method E 96, the permeance of foil-backed gypsum wallboard shall be not more than 0.30 perm [17 ng/Pa·s·m²] (Desiccant Method) for the condition of 50 % relative humidity on the face of the board and 0 % relative humidity on the foil-covered back side of the board.

6. Dimensions and Tolerances

6.1 Specimens shall be taken from the samples obtained in accordance with Specification C 1264.

6.2 Thickness, width, length, and end squareness shall be determined in accordance with Test Methods C 473.

6.2.1 *Thickness*—The nominal thickness shall be ¼, ⅜, ½, ⅝, ¾ in. [6.4, 7.9, 9.5, 12.7, 15.9, 19.0 mm] with tolerances in the nominal thickness of ± ⅛ in. [0.4 mm] with local variations of ± ⅜ in. [0.8 mm] from the nominal thickness.

6.2.2 *Width*—The nominal width shall be up to 48 in. [1220 mm], or up to 54 in. [1370 mm], with a tolerance of ⅜ in. [3 mm] under the specified width.

6.2.3 *Length*—The nominal length and tolerance shall be as follows:

Thickness in. [mm]	Length ft. [mm]	Variation in. [mm]
¼ [6.4]	4 to 12 [1220 to 3660]	± ¼ [6]
⅜ [7.9]	4 to 14 [1220 to 4270]	± ¼ [6]
½ [9.5]	4 to 16 [1220 to 4880]	± ¼ [6]
⅝ [12.7]	4 to 16 [1220 to 4880]	± ¼ [6]
¾ [15.9]	4 to 16 [1220 to 4880]	± ¼ [6]
¾ [19.0]	4 to 16 [1220 to 4880]	± ¼ [6]

6.2.4 *Tapered Edge Depth*—The average thickness of the edge of recessed or tapered edge shall be not less than 0.020 in. [0.51 mm] but not more than 0.090 in. [2.29 mm] less than the average thickness of the gypsum wallboard.

6.2.5 *End Squareness*—Corners shall be square with a tolerance of ± ⅛ in. [3 mm] in the full width of the board.

6.3 *Edges and Ends*—The edges and ends shall be straight and either square, beveled, featured, tapered, or featured and tapered.

7. Finish and Appearance

7.1 The surfaces of gypsum wallboard shall be true and free from imperfections that render the gypsum wallboard unfit for use with or without decoration.

8. Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling and Storage

8.1 Shall be in accordance with Specification C 1264.

9. Keywords

9.1 ceiling; foil-backed; gypsum; gypsum wallboard; gypsum wallboard, type X; partitions; wall