



Standard Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Aluminum Oxide and Aluminum Oxide-Boron Carbide Composite Pellets¹

This standard is issued under the fixed designation C809; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover procedures for the chemical, mass spectrometric, and spectrochemical analysis of nuclear-grade aluminum oxide and aluminum oxide-boron carbide composite pellets to determine compliance with specifications.

1.2 The analytical procedures appear in the following order:

	Sections
Boron by Titrimetry and ICP OES	7 to 16
Separation of Boron for Mass Spectrometry	17 to 22
Isotopic Composition by Mass Spectrometry	23 to 26
Separation of Halides by Pyrohydrolysis	27 to 30
Chloride and Fluoride by Ion-Selective Electrode	31 to 33
Chloride, Bromide, and Iodide by Amperometric Microtitrimetry	34 to 36
Trace Elements by Emission Spectroscopy	37 to 49
Keywords	50

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* (For specific precautionary statements, see Section 5.)

2. Referenced Documents

2.1 *ASTM Standards:*²

[C784 Specification for Nuclear-Grade Aluminum Oxide-Boron Carbide Composite Pellets](#)

[C785 Specification for Nuclear-Grade Aluminum Oxide Pellets](#)

[C791 Test Methods for Chemical, Mass Spectrometric, and](#)

[Spectrochemical Analysis of Nuclear-Grade Boron Carbide](#)

[C799 Test Methods for Chemical, Mass Spectrometric, Spectrochemical, Nuclear, and Radiochemical Analysis of Nuclear-Grade Uranyl Nitrate Solutions](#)

[D1193 Specification for Reagent Water](#)

[E115 Practice for Photographic Processing in Optical Emission Spectrographic Analysis \(Withdrawn 2002\)](#)³

[E116 Practice for Photographic Photometry in Spectrochemical Analysis \(Withdrawn 2002\)](#)³

3. Significance and Use

3.1 Aluminum oxide pellets are used in a reactor core as filler or spacers within fuel, burnable poison, or control rods. In order to be suitable for this purpose, the material must meet certain criteria for impurity content. These test methods are designed to show whether or not a given material meets the specifications for these items as described in Specification [C785](#).

3.1.1 Impurity content is determined to ensure that the maximum concentration limit of certain impurity elements is not exceeded.

3.2 Aluminum oxide-boron carbide composite pellets are used in a reactor core as a component in neutron absorber rods. In order to be suitable for this purpose, the material must meet certain criteria for boron content, isotopic composition, and impurity content as described in Specification [C784](#).

3.2.1 The material is assayed for boron to determine whether the boron content is as specified by the purchaser.

3.2.2 Determination of the isotopic content of the boron is made to establish whether the ¹⁰B concentration is in compliance with the purchaser's specifications.

3.2.3 Impurity content is determined to ensure that the maximum concentration limit of certain impurity elements is not exceeded.

¹ These test methods are under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and are the direct responsibility of Subcommittee C26.03 on Neutron Absorber Materials Specifications.

Current edition approved Jan. 1, 2013. Published January 2013. Originally approved in 1980. Last previous edition approved in 2007 as C809 – 94 (2007). DOI: 10.1520/C0809-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

4. Reagents

4.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

4.2 *Purity of Water*—Unless otherwise indicated, reference to water shall be understood to mean reagent water conforming to Specification **D1193**, Type III.

5. Safety Precautions

5.1 Many laboratories have established safety regulations governing the use of hazardous chemicals and equipment. The users of these test methods should be familiar with such safety practices.

6. Sampling

6.1 Criteria for sampling aluminum oxide pellets are given in Specification **C785**.

6.2 Criteria for sampling aluminum oxide-boron carbide composite pellets are given in Specification **C784**.

BORON BY TITRIMETRY AND ICP OES

7. Scope

7.1 For the determination of boron in aluminum oxide-boron carbide composites by titrimetry and ICP OES the procedures detailed in Test Method **C791**, Sections 17–26 shall be used.

8. Summary of Test Method

8.1 Powdered aluminum oxide-boron carbide composite is mixed with alkaline reagents and this mixture is fused to decompose the aluminum oxide-boron carbide. The melt is dissolved in diluted hydrochloric acid and heated or purged with nitrogen to remove carbon dioxide. The boron as boric acid is titrated with standardized sodium hydroxide solution, using the mannitoboric acid procedure. Alternatively, the boron in the samples solution is measured using ICP OES.

NOTE 1—Sodium carbonate or a mixture of sodium carbonate and potassium carbonate (1:1) is normally used as alkaline reagent to decompose the aluminum oxide-boron carbide composite.

9. Interferences

9.1 *Titrimetry*—Because metallic impurities in high concentrations may distort the inflection points of the titration aluminum should be precipitated from the sample solution using barium carbonate. No distortion was found for concen-

trations of Fe < 2 %, Ti < 1 %. Interferences by dissolved CO₂ shall be removed by heating the sample solution or by purging the sample solution with nitrogen.

9.2 *ICP OES*—Interference effects depend primarily upon the resolving power of the spectrometer and the selection of the analytical lines. In practice, line interferences (spectral interferences) and non spectral interferences are critical. Non spectral interferences are caused primarily by different chemical composition of calibration solution and sample solution, resulting in an alteration of nebulization and excitation properties. Also memory-effects can play a role. The best way to minimize non spectral interferences is the use of calibration samples with the same composition of matrix, ideally certified reference materials.

10. Apparatus

10.1 See Test Methods **C791**, Section 20.

11. Reagents

11.1 See Test Methods **C791**, Section 21.

12. Precautions

12.1 See Test Methods **C791**, Section 22.

13. Sampling and Sample Preparation

13.1 See Test Methods **C791**, Section 23.

14. Procedure

14.1 See Test Methods **C791**, Section 24.

15. Titrimetric Determination of Boron

15.1 See Test Methods **C791**, Section 25.

16. ICP OES

16.1 See Test Methods **C791**, Section 26.

SEPARATION OF BORON FOR MASS SPECTROMETRY

17. Scope

17.1 This test method covers the separation of boron from aluminum and other impurities. The isotopic composition of the separated boron is measured using mass spectrometry. The test method for isotopic composition is found in this standard.

NOTE 2—Alternatively, the separation of boron can be performed by pyrohydrolysis. A stream of moist oxygen is passed over the powdered sample at 1100 °C. The pyrohydrolytic reaction releases boric acid and boron oxide from the sample, which volatilize and collect in the condensate (see Test Methods **C791**, Section 40). The condensate is used for measurement of isotopic composition by ICP-MS (see Test Methods **C791**, Section 32).

18. Summary of Test Method

18.1 Boron is put into solution using a sealed-tube dissolution method. It is separated from aluminum and other impurities by solvent extraction and ion exchange.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.