



Designation: C989/C989M – 16^{ε1}

Standard Specification for Slag Cement for Use in Concrete and Mortars¹

This standard is issued under the fixed designation C989/C989M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

¹ NOTE—Footnote 4 was corrected editorially in March 2017.

1. Scope*

1.1 This specification covers slag cement for use as a cementitious material in concrete and mortar.

NOTE 1—The material described in this specification may be used for blending with portland cement to produce a cement meeting the requirements of Specification C595/C595M or as a separate ingredient in concrete or mortar mixtures. The material may also be useful in a variety of special grouts and mortars, and when used with an appropriate activator, as the principal cementitious material in some applications.

NOTE 2—Information on technical aspects of the use of the material described in this specification is contained in Appendix X1, Appendix X2, and Appendix X3. More detailed information on that subject is contained in ACI 233R-03.²

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. Values are stated in only SI units when inch-pound units are not used in practice.

1.3 The text of this standard references notes and footnotes that provide explanatory information. These notes and footnotes (excluding those in tables) shall not be considered as requirements of this standard.

1.4 The following safety hazards caveat pertains only to the test methods described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this*

standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:³

- C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- C114 Test Methods for Chemical Analysis of Hydraulic Cement
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C150/C150M Specification for Portland Cement
- C185 Test Method for Air Content of Hydraulic Cement Mortar
- C188 Test Method for Density of Hydraulic Cement
- C204 Test Methods for Fineness of Hydraulic Cement by Air-Permeability Apparatus
- C430 Test Method for Fineness of Hydraulic Cement by the 45- μ m (No. 325) Sieve
- C452 Test Method for Potential Expansion of Portland-Cement Mortars Exposed to Sulfate
- C465 Specification for Processing Additions for Use in the Manufacture of Hydraulic Cements
- C595/C595M Specification for Blended Hydraulic Cements
- C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- C1012/C1012M Test Method for Length Change of Hydraulic-Cement Mortars Exposed to a Sulfate Solution
- C1038/C1038M Test Method for Expansion of Hydraulic Cement Mortar Bars Stored in Water
- C1437 Test Method for Flow of Hydraulic Cement Mortar
- C1778 Guide for Reducing the Risk of Deleterious Alkali-Aggregate Reaction in Concrete

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.27 on Ground Slag.

Current edition approved Dec. 15, 2016. Published January 2017. Originally approved in 1982. Last previous edition approved in 2014 as C989/C989M – 14. DOI: 10.1520/C0989_C0989M-16E01.

² ACI 233R-03 Slag Cement in Concrete and Mortar. Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

D3665 Practice for Random Sampling of Construction Materials
TABLE 2 Chemical Requirements

Sulfide sulfur (S), max, %	2.5
----------------------------	-----

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology **C125**.

4. Classification

4.1 Slag cement is classified by performance in the slag activity test in three grades: Grade 80, Grade 100, and Grade 120 (see **Table 1**).

5. Ordering Information

5.1 The purchaser shall specify the grade of slag cement desired and the optional chemical or physical data to be reported.

6. Additions

6.1 Slag cement covered by this specification shall contain no additions except as follows:

6.1.1 It is permissible to add calcium sulfate to slag cement provided it has been demonstrated by Test Method **C1038/C1038M** that a test mixture will not develop expansion in water exceeding 0.020 % at 14 days. In the test mixture, 50 % of the mass of portland cement shall be replaced by an equal mass of slag cement. The portland cement used in the test mixture shall meet the requirements of Specification **C150/C150M**. When the manufacturer supplies cement under this provision, upon request, supporting data shall be supplied to the purchaser.

6.1.2 When processing additions are used in the manufacture of slag cement, the maximum amount used shall comply with the requirements of Specification **C465** when tested using a blend that is 50 % slag cement and 50 % portland cement by mass.

7. Chemical Composition

7.1 Slag cement shall conform to the chemical requirements prescribed in **Table 2**.

8. Physical Properties

8.1 Slag cement shall conform to the physical requirements of **Table 1**.

9. Sampling

9.1 The following sampling and testing procedures shall be used by the purchaser to verify compliance with this specification.

NOTE 3—Sulfur in granulated blast-furnace slag is present predominantly as sulfide sulfur. In most cases, instrumental analyses, such as x-ray fluorescence, cannot differentiate sulfide sulfur from sulfate. Determine and report the sulfide sulfur content separately, and do not include it in the SO₃ calculations.

9.2 Take random grab samples either from a delivery unit or at some point in the loading or unloading process so that no sample represents more than 115 Mg [125 tons] (**Note 4**). If samples are taken from rail cars or trucks, take at least two separate 2-kg [5-lb] portions and thoroughly mix them to obtain a test sample (**Note 5**). Sample by removing approximately a 300-mm [12-in.] layer of slag cement. Make a hole before obtaining a sample to avoid dust collector material that has discharged into the delivery unit after the predominant slag cement flow has ceased. Sample at a rate of one sample per month or one sample for each 2300 Mg [2500 tons] of shipments, whichever is more frequent.

NOTE 4—Standard statistical procedures are recommended for ensuring that samples are selected by a random procedure; see Practice **D3665**. These procedures can be used to select the days within a month or within a week that samples will be taken. The delivery unit or time of day then should be chosen randomly.

NOTE 5—The quantity of sample specified is more than adequate for the testing required. A 2-kg [5-lb] portion should be retained in a sealed container for retesting if that is considered necessary to verify compliance.

10. Test Methods
10.1 Slag-Activity Tests with Portland Cement:

10.1.1 Slag activity shall be evaluated by determining the compressive strength of portland-cement mortars and the corresponding mortars made with the same mass of a blend that is 50 % slag cement and 50 % portland cement by mass.

NOTE 6—**Appendix X1** discusses the effects of cement, temperature, and amount of slag cement used on performance with portland cement.

10.1.2 *Reference Cement*—The portland cement used in the slag activity tests shall be the common reference cement supplied by CCRL⁴ that complies with the standard chemical and physical requirements of Specification **C150/C150M**, Type I or Type II, and with the additional requirements of total alkali content and compressive strength limits as shown in **Table 3**. Alternatively, a portland cement source meeting the standard

⁴ The sole source of commercially available reference portland cement known to the committee at this time is CCRL, 4441 Buckeystown Pike, Suite C; Frederick, Maryland 21704; www.CCRL.us. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

TABLE 1 Physical Requirements

Item		
	Average of Last Five Consecutive Samples	Any Individual Sample
Fineness:		
Amount retained when wet screened on a 45-µm (No. 325) sieve, max %	20	
Specific surface by air permeability, Test Methods C204 shall be determined and reported although no limits are required.	...	
Air Content of Slag Mortar, max %	12	
Slag Activity Index ^A		
28-Day Index, min %		
Grade 80	75	70
Grade 100	95	90
Grade 120	115	110

^A 7-Day Slag Activity Index shall be determined on Grades 100 and 120, and reported for informational purposes.

TABLE 3 Alkali and Strength Limits of Reference Portland Cement for Slag Activity Tests

Total Alkalies (Na ₂ O + 0.658 K ₂ O)	min %	0.60
	max %	0.90
Compressive Strength, MPa, min, 28 days ^A		35 [5000 psi]

^A The minimum strength limit is based solely on the strength of the Test Method C109/C109M mortar cubes, as required in Specification C150/C150M, regardless of the strength of the flow-controlled Specification C989 mortar cubes.

chemical and physical requirements for a C150, Type I or Type II, including the additional limits in Table 3, is permitted to be used. Sufficient cement shall be reserved to avoid changing reference cement more often than every two months. After the initial testing to determine compliance with the compressive strength requirement of Table 3, the reference cement shall be re-qualified at least every six months.

NOTE 7—Different reference cements may produce different Slag Activity Index results. Reference portland cement meeting the requirements of 10.1.2 is available from CCRL.⁵

10.1.3 *Preparation of Specimens*—Prepare mortars in accordance with Test Method C109/C109M, except that sufficient water shall be used in each batch to produce mortar at a flow of 105 to 115 % as defined in Test Method C1437. The proportions of dry ingredients shall be as follows:

Reference Cement Mortar:

- 500 g portland cement
- 1375 g graded standard sand

Slag Cement-Reference Cement Mortar:

- 250 g portland cement
- 250 g slag cement
- 1375 g graded standard sand

10.1.3.1 Mix a reference cement batch each day that a slag cement-reference cement batch is mixed until at least five batches have been mixed with the reference cement. Thereafter, reference cement batches need not be mixed more often than once a week whenever slag cement is being produced or shipped.

10.1.4 *Test Ages*—Determine the compressive strength of mortar specimens at 7 and 28 days age in accordance with Test Method C109/C109M.

10.1.5 *Calculation*—Calculate the slag activity index to the nearest percent for both 7 days and 28 days as follows:

$$\text{Slag activity index, \%} = (SP/P) \times 100 \quad (1)$$

where:

- SP* = average compressive strength of slag cement-reference cement mortar cubes at designated ages, MPa [psi], and
- P* = average compressive strength of reference cement mortar cubes at designated age, MPa [psi].

The reference cement-mortar strength used to calculate a slag activity index shall, when a reference cement mortar is mixed on the same day as a slag cement-reference cement

mortar, be the result for that batch. Otherwise, the average of tests of the five most recent reference cement-mortar batches shall be used.

10.1.6 *Report*—The report should include the following:

- 10.1.6.1 Slag activity index, %,
- 10.1.6.2 Compressive strength at 7 and 28 days, of slag cement-reference cement mortar,
- 10.1.6.3 Compressive strength at 7 and 28 days, of portland cement mortar,
- 10.1.6.4 Total alkalies of the reference cement (Na₂O + 0.658 K₂O),
- 10.1.6.5 Fineness of reference cement, and
- 10.1.6.6 Potential compound composition of the reference portland cement.

10.1.7 *Precision*—The single and multilaboratory statements are based on slag activity index tests using one slag cement, in duplicate, at 7 and 28 days after fabrication of samples. The same slag cement and CCRL reference cement were used at each of 22 laboratories (Note 8).

NOTE 8—The precision of this test method was determined from an interlaboratory study (ILS) under the jurisdiction of ASTM Subcommittee C09.27. The ILS program was conducted in 2015. Practice C670 was followed for the design and analysis of the data. The details are given in RR:C09-1048.⁶

10.1.7.1 The single-laboratory standard deviation has been found to be 1.65 % at 7 days and 2.62 % at 28 days. Therefore, the slag activity indices of properly conducted tests based on single batches of mortar mixed on the same day would not be expected to differ by more than 4.6 % at 7 days and 7.3 % at 28 days in more than one case in 20.

10.1.7.2 The multilaboratory standard deviation has been found to be 6.88 % at 7 days and 4.78 % at 28 days. Therefore, the slag activity indices of properly conducted tests of single batches by different laboratories would not be expected to differ by more than 19.3 % at 7 days or 13.4 % at 28 days in more than one case in 20.

10.2 *Slag Cement Density*—Determine in accordance with Test Method C188.

10.3 *Amount of Slag Cement Retained on a 45- μ m (No. 325) Sieve*—Determine in accordance with Test Method C430.

10.4 *Slag Cement Fineness by Air Permeability*—Determine in accordance with Test Methods C204.

10.5 *Sulfate Ion in Slag Cement Reported as SO₃*—Determine as sulfur trioxide in accordance with Test Methods C114, except the sample need not be completely decomposed by acid.

10.6 *Sulfide Sulfur in Slag Cement*—Determine in accordance with Test Methods C114.

10.7 *Chloride Content of Slag*—Determine in accordance with Test Methods C114.

10.8 *Air Content of Slag Cement Mortar*—Determine in accordance with Test Method C185, except use 350 g of slag

⁵ The sole source of commercially available reference portland cement known to the committee at this time is CCRL, 4441 Buckeystown Pike, Suite C; Frederick, Maryland 21704; www.CCRL.us. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C09-1048. Contact ASTM Customer Service at service@astm.org.