



Standard Test Methods for Vitrified Ceramic Materials for Electrical Applications¹

This standard is issued under the fixed designation D116; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 These test methods outline procedures for testing samples of vitrified ceramic materials that are to be used as electrical insulation. Where specified limits are mentioned herein, they shall not be interpreted as specification limits for completed insulators.

1.2 These test methods are intended to apply to unglazed specimens, but they may be equally suited for testing glazed specimens. The report section shall indicate whether glazed or unglazed specimens were tested.

1.3 The test methods appear as follows:

Procedure	Section
Compressive strength	6 C773
Dielectric strength	13 D618, D149
Elastic properties	8 C623
Electrical resistivity	15 D618, D257, D1829
Flexural strength	7 C674, F417
Hardness	9 C730, E18
Porosity	5 C373
Relative permittivity and dissipation factor	14 D150, D2149, D2520
Specific gravity	4 C20, C329, F77
Thermal conductivity	10 C177, C408
Thermal expansion	12 C539, E288
Thermal shock resistance	11

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precaution statements are given in 11.3, 13.5, and 15.3.

2. Referenced Documents

2.1 *ASTM Standards:*²

C20 Test Methods for Apparent Porosity, Water Absorption,

- Apparent Specific Gravity, and Bulk Density of Burned Refractory Brick and Shapes by Boiling Water
- C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C329 Test Method for Specific Gravity of Fired Ceramic Whiteware Materials
- C373 Test Method for Water Absorption, Bulk Density, Apparent Porosity, and Apparent Specific Gravity of Fired Whiteware Products, Ceramic Tiles, and Glass Tiles
- C408 Test Method for Thermal Conductivity of Whiteware Ceramics
- C539 Test Method for Linear Thermal Expansion of Porcelain Enamel and Glaze Frits and Ceramic Whiteware Materials by Interferometric Method
- C623 Test Method for Young’s Modulus, Shear Modulus, and Poisson’s Ratio for Glass and Glass-Ceramics by Resonance
- C674 Test Methods for Flexural Properties of Ceramic Whiteware Materials
- C730 Test Method for Knoop Indentation Hardness of Glass
- C773 Test Method for Compressive (Crushing) Strength of Fired Whiteware Materials
- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation
- D257 Test Methods for DC Resistance or Conductance of Insulating Materials
- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D1829 Test Method for Electrical Resistance of Ceramic Materials at Elevated Temperatures (Withdrawn 2001)³
- D2149 Test Method for Permittivity (Dielectric Constant) And Dissipation Factor Of Solid Dielectrics At Frequencies To 10 MHz And Temperatures To 500°C
- D2520 Test Methods for Complex Permittivity (Dielectric Constant) of Solid Electrical Insulating Materials at Microwave Frequencies and Temperatures to 1650°C

¹ These test methods are under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.03 on Methods for Whitewares and Environmental Concerns.

Current edition approved July 1, 2016. Published July 2016. Originally approved in 1921. Last previous edition approved in 2011 as D116 – 86 (2011). DOI: 10.1520/D0116-86R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

E18 Test Methods for Rockwell Hardness of Metallic Materials

E288 Specification for Laboratory Glass Volumetric Flasks

F77 Test Method for Apparent Density of Ceramics for Electron Device and Semiconductor Application (Withdrawn 2001)³

F417 Test Method for Flexural Strength (Modulus of Rupture) of Electronic-Grade Ceramics (Withdrawn 2001)³

3. Significance and Use

3.1 For any given ceramic composition, one or more of the properties covered herein may be of more importance for a given insulating application than the other properties. Thus, it may be appropriate that selected properties be specified for testing these ceramic materials.

3.2 Pertinent statements of the significance of individual properties may be found in the sections pertaining to such properties.

4. Specific Gravity

4.1 *Scope*—Three methods are given, providing for accuracy, convenience, or testing of small specimens.

4.2 *Significance and Use*—Specific gravity measurements provide data indicating the control of quality of the ceramic material. The thermal maturity of specimens may be estimated from such data. Specific gravity data are related to electrical, thermal, and mechanical properties of ceramics.

4.3 Procedure:

4.3.1 When the destruction of the specimen can be tolerated and the highest precision is required, determine the specific gravity in accordance with Test Method **C329**.

4.3.2 When it is not desirable to destroy the specimen and less precise values are acceptable, determine the specific gravity in accordance with Test Methods **C20**.

4.3.3 When only a very small specimen is available, determine the specific gravity in accordance with Test Method **F77**.

5. Porosity

5.1 *Scope*—Three methods are given based on the relative porosity of the specimens.

5.2 *Significance*—Amount of porosity of a specimen is used as a check on structural reproducibility and integrity.

5.3 Method A:

5.3.1 In the case of relatively porous ceramics (water absorption greater than 0.1 %), determine the porosity as water absorption in accordance with Test Method **C373**.

NOTE 1—Test Method **C373** has been found suitable for determining water absorption in the range of 0.1 %, although that method was derived specifically for absorptions exceeding 3.0 %.

5.3.2 An alternative to Method A, using gas as a fluid, may be found in the literature.^{4,5}

5.4 Method B—Dye Penetration Under Pressure:

5.4.1 *Apparatus*—The apparatus shall consist of a suitable pressure chamber of such dimensions as to accommodate the test specimen when immersed in the dye solution with arrangements for obtaining and maintaining the required pressure for the required time.

5.4.2 *Reagent*—A fuchsine dye solution consisting of 1 g of basic fuchsine in 1 L of 50 % reagent ethyl alcohol is suitable.

5.4.3 *Specimens*—The specimens shall be freshly broken fragments of the ceramic body, having clean and apparently unshattered surfaces exposed. At least 75 % of the area of such specimens should be free of glaze or other surface treatment. Fragments approximately 5 mm in the smallest dimension up to 20 mm in the largest dimensions are recommended.

5.4.4 Procedure:

5.4.4.1 Place the specimen fragments in the pressure chamber and immerse completely in the fuchsine solution.

5.4.4.2 Apply a pressure of 28 MPa (4000 psi) \pm 10 % for approximately 15 h. An optional pressure of 70 MPa (10 000 psi) \pm 10 % for 6 h may be used.

5.4.4.3 At the conclusion of the application of the test pressure, remove the specimens from the pressure chamber, rinse and dry thoroughly, and break as soon as possible for visual examination.

5.4.4.4 Porosity is indicated by penetration of the dye into the ceramic body to an extent visible to the unaided eye. Disregard any penetration into small fissures formed in preparing the test specimen.

5.4.5 *Report*—The report shall include a statement of the observations recorded in accordance with the examination in **5.4.4.4**.

5.4.6 *Precision and Bias*—This method has been in use for many years, but no statement for precision has been made and no activity is planned to develop such a statement. A statement of bias is unavailable in view of the lack of a standard reference material for this property.

5.5 Method C—Dye Penetration Under Atmospheric Pressure:

5.5.1 *Apparatus*—The apparatus shall consist of a suitable open-air chamber of such dimensions as to accommodate the test specimens when immersed in the dye solution.

5.5.2 *Reagent*—The fuchsine solution of **5.4.2** is suitable.

5.5.3 *Specimens*—The specimens of **5.4.3** are suitable.

5.5.4 Procedure:

5.5.4.1 Place the test specimens in the chamber and immerse completely in the fuchsine solution.

5.5.4.2 Permit the specimens to remain immersed for 5 min or longer, remove, rinse, dry thoroughly and break as soon as possible for visual examination.

5.5.4.3 Porosity is indicated by penetration into the ceramic body to an extent visible with the unaided eye. Disregard any penetration into small fissure formed in the preparation of the specimens.

⁴ Wasburn, E. W. and Bunting, E. N., "The Determination of the Porosity of Highly Vitrified Bodies," *Journal of the American Ceramic Society*, Vol 5, 1922, pp. 527–535.

⁵ Navias, Louis, "Metal Porosimeter for Determining the Pore Volume of Highly Vitrified Ware," *Journal of the American Ceramic Society*, Vol 8, 1925, pp. 816–821.