



Standard Practice for Rubber—Standard Conditions for Testing¹

This standard is issued under the fixed designation D1349; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 Reliable comparisons between different rubber compounds and between different laboratories is an essential component of effective testing.

1.2 It is necessary to standardize the temperature and humidity conditions to which materials are subjected prior to and during testing.

1.3 Section 2 of this practice includes the definition of terms commonly used to describe the conditions of testing.

1.4 Section 3 of this practice covers a list of standard test temperatures for testing from which selection may be made for a specification, procedure, practice, standard or method.

1.4.1 Any specification, procedure, practice, standard or method that specifies test temperatures shall take precedence over this practice.

1.4.2 The standard test temperatures for testing do not apply to preparation, mixing, processing, or vulcanizing temperatures for rubber compounds.

1.5 Section 4 of this practice covers a list of standard relative humidity conditions for testing from which selection may be made for a specification, procedure, practice, standard or method.

1.5.1 Any specification, procedure, practice, standard or method that specifies relative humidity shall take precedence over this practice.

1.5.2 The standard relative humidity conditions for testing do not apply to preparation, mixing, processing, or vulcanizing of rubber compounds, but may serve as a guide when the condition is not specified.

1.6 Section 5 of this practice covers the standard conditioning of materials for testing.

1.6.1 Any specification, procedure, practice, standard or method that specifies the conditioning of materials for testing shall take precedence over this practice.

1.7 Section 6 of this practice includes the keywords associated with this document which may be used in standard document or internet searches.

1.8 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.9 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Terminology

2.1 Definitions:

2.1.1 *room temperature, n*—a temperature in the range from 20 to 30°C (68 to 86°F).

2.1.2 *standard laboratory atmosphere, n*—an atmosphere having a temperature of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and a relative humidity of $50 \pm 10\%$ RH (40 to 60 %RH) shall be the standard laboratory atmosphere.

2.1.3 *standard laboratory temperature, n*—a temperature of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) shall be the standard laboratory temperature.

3. Temperatures for Testing

3.1 When data are to be obtained for comparison purposes at a specific temperature, select the test temperature and associated tolerance from Table 1.

3.1.1 The temperatures in Table 1 are not to be considered exclusive. If agreed upon between customer and supplier, temperatures within the range shown in Table 1 may be employed, that is, where 195°C was found to be a desired temperature for testing, it would be used with a $\pm 2.0^\circ\text{C}$ tolerance. The temperature shall be recorded and reported.

3.1.2 Unless otherwise specified, tolerance for temperature shall be as given in Table 1.

3.1.3 A tolerance of $\pm 1^\circ\text{C}$ ($\pm 1.8^\circ\text{F}$) or less, may be required by a specification, procedure, practice, standard or method, or as agreed upon between customer and supplier and shall be recorded and reported. Refer to 4.3.1.

¹ This practice is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.10 on Physical Testing.

Current edition approved July 1, 2014. Published August 2014. Originally approved in 1954. Last previous edition approved in 2009 as D1349 – 09. DOI: 10.1520/D1349-14.