



Standard Specification for Rubber General Purpose, Household or Beautician Gloves¹

This standard is issued under the fixed designation D4679; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorially corrected 8.4.2 in January 2015.

1. Scope

1.1 This specification covers requirements for gloves made of rubber-like latex, whether made of natural or synthetic materials, unsupported with or without a flock lining, intended for household, beautician use, or general use.

1.2 This specification is intended to serve as a guide to permit obtaining gloves of consistent performance. The safe and proper use of gloves is excluded from the scope of this specification.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension

D573 Test Method for Rubber—Deterioration in an Air Oven

D865 Test Method for Rubber—Deterioration by Heating in Air (Test Tube Enclosure)

D3767 Practice for Rubber—Measurement of Dimensions

D5151 Test Method for Detection of Holes in Medical Gloves

¹ This specification is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.40 on Consumer Rubber Products.

Current edition approved Jan. 1, 2015. Published February 2015. Originally approved in 1987. Last previous edition approved in 2007 as D4679 – 02 (2007). DOI: 10.1520/D4679-02R15E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *ISO Standard*:

ISO 2859 Sampling Procedures and Tables for Inspection by Attributes³

3. Materials and Manufacture

3.1 Any rubber-like material whether comprised of natural synthetic, or other polymer compound that permits the glove to meet the requirements of this specification is acceptable.

4. Workmanship, Finish, and Appearance

4.1 The gloves shall have a uniform finish and be free of discoloration, thin spots, air bubbles, embedded particles, tackiness, and other blemishes likely to affect serviceability.

5. Precautions

5.1 Performance requirements are limited to minimum physical properties initially, and after heat aging, in accordance with 8.5.2 because performance testing for all possible use situations is impractical. Gloves covered under this specification are not intended for use with, or exposure to, chlorinated or aromatic solvents, or other strong chemicals. If the gloves are made of, or contain natural rubber latex, they are not intended for exposure to products containing petroleum or petroleum derivatives.

6. Performance Requirements

6.1 Gloves, sampled in accordance with Section 7, shall meet the following requirements:

6.1.1 Free from holes when tested in accordance with 8.2,

6.1.2 Consistent design in accordance with 8.3,

6.1.3 Consistent physical dimensions in accordance with 8.4, and

6.1.4 Have acceptable physical property characteristics in accordance with 8.5.

7. Sampling and Inspection

7.1 For referee purposes, gloves shall be sampled and inspected in accordance with ISO 2859. The inspection levels

³ Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036.