



Standard Test Method for Rubber Chemical Antidegradants—Purity of *p*-Phenylenediamine (PPD) Antidegradants by High Performance Liquid Chromatography¹

This standard is issued under the fixed designation D5666; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the purity of Type I, II, and III *p*-phenylenediamine (PPD) antidegradants as described in Classification [D4676](#) by high performance liquid chromatography (HPLC) using ultraviolet detection and external standard calculations.

1.2 Expertise in HPLC is necessary to the successful application of this test method.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D3853 Terminology Relating to Rubber and Rubber Latices—Abbreviations for Chemicals Used in Compounding](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

[D4676 Classification for Rubber Compounding Materials—Antidegradants](#)

2.2 ISO Standards:³

[ISO 5725 Precision of Test Methods](#)

[ISO 6472 Rubber Abbreviations](#)

[Compounding](#)

[Ingredients—](#)

3. Terminology

3.1 Definitions:

3.1.1 *external standard calculation*—a method of calculating the percent composition by measuring the area of the analyte peak, multiplying by a response factor, and dividing by the sample concentration. All components are assumed to be resolved from the component of interest.

3.1.2 *lot sample*—a production sample representative of a standard production unit, normally referred to as the sample.

3.1.3 *specimen*—the actual material used in the analysis, also known as the test portion. It must be representative of the lot sample.

3.2 Abbreviations:

3.2.1 The following abbreviations are in accordance with Terminology [D3853](#) and ISO 6472:

3.2.2 *77PD*—N,N' bis-(1,4-dimethylpentyl)-*p*-phenylenediamine.

3.2.3 *DTPD*—N,N'-ditolyl-*p*-phenylenediamine.

3.2.4 *IPPD*—N-isopropyl-N'-phenyl- *p*-phenylenediamine.

3.2.5 *PPD*—*p*-phenylenediamine.

3.2.6 *6PPD*—N-(1,3 dimethylbutyl)-N'-phenyl-*p*-phenylenediamine.

4. Summary of Test Method

4.1 A specimen is dissolved in acetonitrile and a fixed loop volume is analyzed by isocratic HPLC using a thermostated C18 reversed phase column and an ultraviolet (UV) detector. Peak areas are determined using a chromatographic integrator or laboratory data system with the amount of analyte being determined by external calibration.

5. Significance and Use

5.1 This test method is designed to determine the purity of *p*-phenylenediamine antidegradants.

¹ This test method is under the jurisdiction of ASTM Committee [D11](#) on Rubber and is the direct responsibility of Subcommittee [D11.11](#) on Chemical Analysis.

Current edition approved Aug. 1, 2014. Published November 2014. Originally approved in 1995. Last previous edition approved in 2009 as D5666 – 95 (2009). DOI: 10.1520/D5666-95R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

5.2 Since the results of this test method are based on an integrated peak area as determined by HPLC, it is assumed that all analytes of interest are resolved from interfering peaks.

6. Interferences

6.1 Components co-eluting with the analyte of interest will cause erroneous results; thus it is required that the system be capable of providing a minimum of 10 000 theoretical plates.

7. Apparatus

7.1 *Liquid Chromatograph*, consisting of the following:

7.1.1 Precision chromatographic pump,

7.1.2 Variable wavelength UV detector,

7.1.3 A method for thermostating the column at $35 \pm 1^\circ\text{C}$, for example, a column oven or water jacket,

7.1.4 A fixed injector made of either a 20 mm^3 (μL) rheodyne loop or an automatic sampler.

7.2 *HPLC Columns*, consisting of:

7.2.1 A precolumn packed with C18 grafted silica with particle size of 35 to $40 \mu\text{m}$ (100 to 150 mm), and

7.2.2 A column of 10- to 15-cm length packed with C18 grafted silica with particle size of 3 to $5 \mu\text{m}$.

7.3 *Integrator/Data System*, capable of determining absolute amounts of analyte of interest by means of integration of detector output versus time.

7.4 *Analytical Balance*, capable of measuring within ± 0.01 mg.

7.5 *Shaking Machine*, or ultrasonic tank.

7.6 *Volumetric Flask*, 100 cm^3 .

7.7 *Syringes*, with rheodyne loop, 2 cm^3 .

7.8 *Clear Screw-Top Vials*, with suitable septa, 125 cm^3 .

8. Reagents and Materials

8.1 *Acetonitrile*, HPLC grade.

8.2 *Ethanolamine*, HPLC grade.

8.3 *Water*, HPLC grade or double distilled water or water of resistivity greater than 2 megohms/cm.

9. Calibration and Standardization

9.1 A primary standard of known purity is used to determine the response factor for each analyte.

10. Procedure

10.1 *Chromatographic Conditions*:

10.1.1 Determine the eluant phase composition and the flow rate by adjusting the chromatographic parameters for the particular column chosen. The eluant phase consists of the appropriate mixture of HPLC grade acetonitrile and HPLC grade or equivalent water, both containing 0.2 kg/m^3 (g/L) ethanolamine or less according to the product to be tested.

NOTE 1—Different liquid chromatography columns may exhibit different elution characteristics. See Table 1 for suggested chromatographic starting parameters for analysis.

10.2 *Detector*—Monitor the absorbance of the sample at the prescribed wavelength. The detector should be set to 1 absorbance unit full scale (AUFS).

TABLE 1 Suggested Chromatographic Starting Parameters

	N,N'-dialkyl- paraphenylene- diamine 77-PPD	N-aryl-N'-alkyl- paraphenylene- diamine IPPD 6-PPD	N,N'-diaryl- paraphenylene- diamine DPPD DTPD
Eluant phase			
% acetonitrile	85	65	70
% Water	15	35	30
Ethanolamine (g/L)	0.2	0.1	0.1
Flow rate (cm^3/min)	1	1	1
Wavelength (nm)	260	290	280

10.3 *Integrator/Data System*—The integrator settings should be adjusted to give a full-scale response to 1 absorbance unit (AU).

10.4 *Sample Storage Before Analysis*—Samples must always be stored in a refrigerator.

10.5 *Standard Preparation*—Weigh the clear vial to the nearest 0.1 mg, introduce approximately 20 mg of the standard using a spatula and weigh the standard and vial to the nearest 0.1 mg. Using a volumetric flask, add 100 cm^3 of acetonitrile to the vial. Stopper the vial so that it is hermetically sealed immediately after adding the solvent. Dissolve the product at $23 \pm 3^\circ\text{C}$ in the ultrasonic bath tank or on the shaking machine. The standard must be analyzed within 4 h of being prepared.

NOTE 2—*Preparation of Standards*—The analytical standards are prepared by multiple recrystallizations or distillations of the paraphenylenediamines. The procedure can be repeated until the desired purity is obtained. The purity of the standard is estimated by gradient HPLC analysis of the impurities and differential thermal analysis (DTA). The impurities in the standard should be reestimated every 90 days by HPLC. The standard should be stored at 5°C or lower.

10.6 *Sample Preparation*—To ensure sample homogeneity, 5 g of sample should be ground with a mortar and pestle.

10.7 *Sample Analysis*:

10.7.1 Weigh at least 20 mg to the nearest 0.1 mg of the sample in a clear vial and dissolve it in 100 cm^3 acetonitrile following the procedure in 10.5. The sample must be analyzed within 4 h of being prepared.

10.7.2 *Injection of the Solutions*:

10.7.2.1 *Manual Method*—Take approximately $100 \mu\text{L}$ of the solution using a syringe and inject a quantity greater than the volume of the rheodyne loop, that is, approximately $60 \mu\text{L}$ for a $20\text{-}\mu\text{L}$ loop. Rinse the syringe with solvent and dry.

10.7.2.2 *Automatic Method*—Put the flasks containing the sample and standard solutions in place and program the automatic sampler.

10.7.3 Chromatograph the samples using parameters as prescribed in 10.1.1.

11. Calculation

11.1 *Response Factor*—Calculate the response factor for the standard by dividing the concentration of the standard by the measured area count and multiplying this by the purity of the standard:

$$RF = (\text{concentration/area count}) \times \% \text{ purity} \quad (1)$$

NOTE 3—Throughout the calculation the units of concentration must be