



# Standard Test Method for Determination of the Amount of Polypropylene (PP) in Polypropylene/LDPE Mixtures Using Infrared Spectrophotometer (FTIR)<sup>1</sup>

This standard is issued under the fixed designation D7399; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method uses an infrared approach for determining the presence of polypropylene (PP) physically mixed in with low density polyethylene – usually for recycling purposes.

NOTE 1—Quantitative determinations require several standard mixtures in the concentration range of interest and well defined baseline anchoring points.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—There is no known ISO equivalent to this standard.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D883 Terminology Relating to Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

D2238 Test Methods for Absorbance of Polyethylene Due to Methyl Groups at 1378  $\text{cm}^{-1}$

D5033 Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics (Withdrawn 2007)<sup>3</sup>

E131 Terminology Relating to Molecular Spectroscopy

E168 Practices for General Techniques of Infrared Quantitative Analysis

E932 Practice for Describing and Measuring Performance of Dispersive Infrared Spectrometers

E1421 Practice for Describing and Measuring Performance of Fourier Transform Mid-Infrared (FT-MIR) Spectrom-

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.70 on Analytical Methods.

Current edition approved Sept. 1, 2008. Published September 2008. DOI: 10.1520/D7399-08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

eters: Level Zero and Level One Tests

IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): The Modern Metric System

## 3. Terminology

3.1 *Definitions*—For definitions of plastics terms used in this test method, see Terminology standards D883, D1600, and D5033.

3.2 *Terminology*—Units, symbols, and abbreviations used in this test method appear in Terminology E131 or IEEE/ASTM SI-10.

## 4. Summary of Test Method

4.1 Thin films representing a typical portion of the material are analyzed with an IR spectrophotometer using two absorbance bands—one characteristic for polypropylene (PP) and one for low density polyethylene (LDPE). The ratio of these two absorbencies is used to assess the presence of polypropylene.

4.2 For quantitative determinations, several standards with known concentrations of PP in LDPE bracketing the range of interest are needed to develop a calibration curve. Also, baseline placement shall be defined to produce repeatable results.

## 5. Significance and Use

5.1 In recycling PP and LDPE, it is important to the end product properties as well as to the processing conditions to know what the purity of the mixture is. In many cases, it is vital to know that the recycled material is reasonably free of a contaminant.

## 6. Interferences

6.1 Presence of materials other than PP or LDPE in a sample might cause error in measurement.

6.2 Inhomogeneous sample is known to cause false reading. It is recommended to verify sample homogeneity by measuring different areas of the sample.