Designation: E1795 - 17

Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings¹

This standard is issued under the fixed designation E1795; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers minimum material performance requirements and laboratory test procedures for non-reinforced liquid coating encapsulation products (single or multiple-coat systems) for leaded paint in buildings. Performance properties addressed in this specification are:
 - 1.1.1 Impact resistance,
 - 1.1.2 Adhesion.
 - 1.1.3 Dry Abrasion Resistance,
 - 1.1.4 Water Vapor Transmission,
 - 1.1.5 Water and Chemical Resistance,
 - 1.1.6 Surface Burning Characteristics,
 - 1.1.7 Volatile Organic Compound (VOC) Content,
 - 1.1.8 Weathering,
 - 1.1.9 Aging,
 - 1.1.10 Scrub Resistance,
 - 1.1.11 Mildew Resistance,
 - 1.1.12 Paintability/Repairability,
 - 1.1.13 Flexibility, and
 - 1.1.14 Tensile Properties.
- 1.2 This specification does not address the selection of an encapsulation product for specific use conditions. Specific use conditions may require performance values other than those stated in this specification. See Guide E1796.
- 1.3 This specification complements Specification E1797 for reinforced liquid coating encapsulation products.
- 1.4 This specification does not cover the use of encapsulation products on industrial steel structures nor on residential coated metal surfaces because no corrosion control requirements are included.
- 1.5 This specification applies to any non-reinforced liquid applied product that relies primarily on adhesion for attachment to the surface. These products are used to encapsulate a leaded paint surface with the intent of reducing human exposure to lead.
- ¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.23 on Lead Hazards Associated with Buildings.
- Current edition approved March 1, 2017. Published March 2017. Originally approved in 1995. Last previous edition approved in 2012 as E1795-12. DOI: 10.1520/E1795-17.

- 1.6 The results of the test methods included in this specification will not necessarily predict field performance.
- 1.7 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.
- 1.8 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:²
- D16 Terminology for Paint, Related Coatings, Materials, and Applications
- D522/D522M Test Methods for Mandrel Bend Test of Attached Organic Coatings
- D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels
- D1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers
- D1212 Test Methods for Measurement of Wet Film Thickness of Organic Coatings
- D1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes
- D1475 Test Method For Density of Liquid Coatings, Inks, and Related Products
- D1653 Test Methods for Water Vapor Transmission of Organic Coating Films
- D2370 Test Method for Tensile Properties of Organic Coatings
- D2486 Test Methods for Scrub Resistance of Wall Paints
- D2794 Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)
- D3273 Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



D3274 Test Method for Evaluating Degree of Surface Disfigurement of Paint Films by Fungal or Algal Growth, or Soil and Dirt Accumulation

D3359 Test Methods for Measuring Adhesion by Tape Test D3891 Practice for Preparation of Glass Panels for Testing Paint, Varnish, Lacquer, and Related Products

D3924 Specification for Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials (Withdrawn 2016)³

D3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings

D3960 Practice for Determining Volatile Organic Compound (VOC) Content of Paints and Related Coatings

D4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser

D4214 Test Methods for Evaluating the Degree of Chalking of Exterior Paint Films

D4414 Practice for Measurement of Wet Film Thickness by Notch Gages

D4708 Practice for Preparation of Uniform Free Films of Organic Coatings

D7091 Practice for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to Ferrous Metals and Nonmagnetic, Nonconductive Coatings Applied to Non-Ferrous Metals

E84 Test Method for Surface Burning Characteristics of Building Materials

E1605 Terminology Relating to Lead in Buildings

E1796 Guide for Selection and Use of Liquid Coating Encapsulation Products for Leaded Paint in Buildings

E1797 Specification for Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings

E2239 Practice for Record Keeping and Record Preservation for Lead Hazard Activities

G154 Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials

2.2 Federal Test Methods Standard 141C:⁴

2011 Preparation of Steel Panels

2012 Preparation of Tin Panels

2.3 Federal Test Methods Standard 141D:⁴

3011 Condition in Container

3. Terminology

- 3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminologies D16 and E1605.
 - 3.2 Definition of Term Specific to This Standard
- 3.2.1 *lead inaccessibility*—the ability of an encapsulation product to resist or inhibit the transport of lead to its surface.

4. Classification

4.1 *Type I: Interior Use Only*—Type I defines encapsulation products intended for interior use. These products shall meet the requirements of this specification except those for weath-

ering and exterior aging (that is, test methods described in 10.9 and 10.10.1 not conducted).

- 4.2 Type II: Exterior Use Only—Type II defines encapsulation products intended for exterior use. These products shall meet the requirements of this specification except that for interior aging (that is, test method described in 10.10.2 not conducted).
- 4.3 Type III: Either Exterior or Interior Use—Type III defines encapsulation products intended for either interior or exterior use. These products shall meet all the requirements of this specification.

5. Performance Requirements

5.1 Performance requirements that shall be met for a non-reinforced liquid coating encapsulation product are given in Table 1.

Note 1—In addition to those given in Table 1, performance requirements for three other properties are of concern for liquid coating encapsulation products. These are combustion toxicity, emissions during application and curing, and lead accessibility. However, requirements for these properties cannot be included in this specification at this time because there are no adequate ASTM or Federal test methods for determining them. Requirements for two of these properties, combustion toxicity and emissions during application and curing, may be subject to regulations or ordinances promulgated by authorities having jurisdiction. The user of this specification is advised to determine whether such regulations or ordinances exist. The addition of requirements for these properties to this specification will be undertaken when suitable test methods are available.

6. Sampling

- 6.1 A 3.8-L (1-gal) sample is usually sufficient for the recommended tests.
- 6.2 Prior to sampling, establish the condition of the container since damage to it may cause evaporation, skinning, or other undesirable effects. Excessive storage time and temperature fluctuations may cause settling or changes in viscosity. Materials beyond the manufacturer's stated shelf life shall not be sampled.
- 6.3 Thickening, settling, and separation are undesirable and objectionable if the coating, after storage, cannot be readily made suitable for application with a reasonable amount of stirring. Determine the conditions in the container in accordance with Method 3011 of the Federal Test Method Standard No. 141C.
- 6.4 Sample the encapsulant in accordance with Practice D3925. Determine the density in accordance with Test Method D1475 and repeat until two successive readings agree within 90 g (0.2 lb). Samples for testing may then be taken.
- 6.5 Report the size of the container from which the sample was taken and product identification codes.

7. Number of Tests

7.1 The number of tests that shall be conducted for each performance property is given in Table 1.

8. Retesting

8.1 In cases where encapsulation products fail to pass one or more requirements of this specification, retesting shall be

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from DLA Document Services, Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, http://quicksearch.dla.mil.