

STANDARDS AUSTRALIA

Amendment No. 1
to
AS 2281—1993
Flexible cellular polyurethane for seat cushioning and bedding

CORRECTION

The 1993 edition of AS 2281 is amended as follows; the amendment should be inserted in the appropriate place.

SUMMARY: This Amendment applies to Table 4.

Published on 14 March 1994.

AMDT
No. 1
MAR.
1994

Page 7 Table 4

Delete the text and properties associated with *accelerated ageing* in Table 4.

Add the following requirements for *compression set* and *accelerated ageing* to Table 4.

<i>Compression set 75%</i> (22 h at 70°C)	Max.	≤80 ≥100	2282.9	% change	15 10	15 10	* 20	15 10
<i>Accelerated ageing</i> Heat aged (22 h at 140°C) Tensile change	Max.	All	2282.10 2282.6	%	30	30	30	30
Humidity aged (5 h at 120°C) Compression force on deflection % loss on ageing	Max.	All	2282.10 2282.8B	%	30	30	30	30
50% compression set (22 h at 70°C).	Max.	All	2282.9	%	30	30	NA	30