

STANDARDS AUSTRALIA

---

**RECONFIRMATION**

**OF**

**AS 4133.2.1.1—2005**

**Methods of testing rocks for engineering purposes**

**Method 2.1.1: Rock porosity and density tests—Determination of rock porosity and dry density—Saturation and calliper techniques**

---

**RECONFIRMATION NOTICE**

Technical Committee CE-009 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 17 December 2015.

The following are represented on Technical Committee CE-009:

Association of Geotechnical Testing Authorities (Qld)  
Australian Building Codes Board  
Australian Chamber of Commerce and Industry  
Australian Geomechanics Society  
Australian Stabilisation Industry Association  
AUSTROADS  
Cement Concrete & Aggregates Australia – Aggregates  
Engineering & Construction Laboratories Association  
Engineers Australia  
National Association of Testing Authorities Australia  
The University of Melbourne  
The University of Sydney  
Victorian Construction Materials Laboratories Association

## NOTES

---

## Methods of testing rocks for engineering purposes

### Method 2.1.1: Rock porosity and density tests— Determination of rock porosity and dry density— Saturation and calliper techniques

---

#### 1 SCOPE

This Standard sets out the method for determining the porosity and dry density of rock samples in the form of specimens of regular geometry.

The method is applicable only to non-friable, coherent rocks that can be machined and do not appreciably swell or disintegrate when they are oven-dried or are immersed in water. The method is suitable when regularly shaped specimens are required for other test purposes.

NOTE: Information on uncertainty of measurement is given in Appendix A.

#### 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS	
1289	Methods of testing soils for engineering purposes
1289.0	Method 0: General requirements and list of methods
ISO/IEC 17025	General requirements for the competence of testing and calibration laboratories
ISO	
GUM	Guide to the expression of uncertainty in measurement

#### 3 APPARATUS

The following apparatus is required:

- A drying oven complying with AS 1289.0.
- A measuring instrument capable of measuring specimen dimensions to 0.1 mm.
- Vacuum saturation equipment such that the specimens can be immersed in water under a vacuum of not less than 800 Pa for a period of at least 1 h.
- A balance of suitable capacity, and with appropriate limit of performance.  
NOTE: The limit of performance and precision of mass determination of the balance will depend on the sample mass. Suitable balances are shown in Table 1.
- A thermometer or other suitable temperature measuring device covering the range of 0°C to 50°C graduated to 1°C or less.