



Designation: B121/B121M – 23

## Standard Specification for Leaded Brass Plate, Sheet, Strip, and Rolled Bar<sup>1</sup>

This standard is issued under the fixed designation B121/B121M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification establishes the requirements for leaded brass plate, sheet, strip, and rolled bar for general application produced from Copper Alloy UNS Nos. C33500, C34000, C34200, C35000, C35300, and C35600.

1.2 *Units*—The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

[B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar](#)

[B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar \(Metric\)](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved April 1, 2023. Published May 2023. Originally approved in 1939. Last previous edition approved in 2016 as B121/B121M – 16. DOI: 10.1520/B0121\_B0121M-23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast](#)

[B846 Terminology for Copper and Copper Alloys](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

[E112 Test Methods for Determining Average Grain Size](#)

[E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition \(Withdrawn 2023\)](#)<sup>3</sup>

[E478 Test Methods for Chemical Analysis of Copper Alloys](#)

### 3. General Requirements

3.1 The following sections of Specifications [B248](#) or [B248M](#) constitute a part of this specification:

3.1.1 Terminology

3.1.2 Materials and Manufacture

3.1.3 Workmanship, Finish, and Appearance

3.1.4 Sampling—except for chemical analysis

3.1.5 Number of Tests and Retests

3.1.6 Specimen Preparation

3.1.7 Test Methods—except for chemical analysis

3.1.8 Significance of Numerical Limits

3.1.9 Inspection

3.1.10 Rejection and Rehearing

3.1.11 Certification

3.1.12 Test Reports

3.1.13 Packaging and Package Marking

3.1.14 Supplementary Requirements

3.2 In addition, when a section with a title identical to that referenced in 3.1 appears in this specification, it contains additional requirements which supplement those appearing in Specifications [B248](#) or [B248M](#).

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard

#### 4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology **B846**.

#### 5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification, as applicable:

- 5.1.1 ASTM designation and year of issue,
- 5.1.2 Copper [Alloy] UNS No. designation,
- 5.1.3 Temper (Section 8),
- 5.1.4 Dimensions: thickness and width (**11.2** and **11.3**),
- 5.1.5 How furnished: straight lengths or coils,
- 5.1.6 Quantity—total weight or total length or number of pieces of each size,
- 5.1.7 Type of edge, if required (slit, sheared, sawed, square corners, round corners, rounded edges, or full-rounded edges) (**11.6**),
- 5.1.8 Length (**11.4**), and
- 5.1.9 Intended application.

5.2 The following options are available but may not be included unless specified at the time of placing the order when required:

- 5.2.1 Heat identification or traceability details.
- 5.2.2 Certification,
- 5.2.3 Test Report,

5.2.4 If product is purchased for agencies of the U. S. government (see the Supplementary Requirements section of Specifications **B248** or **B248M** for additional requirements, if specified).

#### 6. Materials and Manufacture

##### 6.1 Materials:

6.1.1 The material of manufacture shall be a form (cast bar, cake, slab, et cetera) of Copper Alloy UNS Nos. C33500, C34000, C34200, C35000, C35300, or C35600 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 1—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

##### 6.2 Manufacture:

6.2.1 The product shall be manufactured by such hot working, cold working, and annealing processes as to produce a uniform wrought structure in the finished product.

6.2.2 The product shall be hot or cold worked to the finished size and subsequently annealed when required, to meet the temper properties specified.

##### 6.3 Edges:

6.3.1 Slit edges shall be furnished unless otherwise specified in the contract or purchase order.

#### 7. Chemical Composition

7.1 The material shall conform to the composition requirements in **Table 1** for the Copper Alloy UNS No. designation specified in the ordering information.

7.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and purchaser, limits may be established and analysis required for unnamed elements.

7.3 For alloys in which zinc is listed as “remainder,” either copper or zinc may be taken as the difference between the sum of results of all other elements determined and 100 %. When all elements in **Table 1** are determined, the sum of the results shall be as shown in the following table:

Copper Alloy UNS No.	Copper Plus Named Elements, % min.
C33500	99.6
C34000	99.6
C34200	99.6
C35000	99.6
C35300	99.5
C35600	99.5

#### 8. Temper

8.1 The standard tempers for products described in this specification are given in **Tables 2** and **3**.

- 8.1.1 Cold rolled tempers H01 to H10.
- 8.1.2 Annealed tempers OS025 to OS070.

#### 9. Grain Size for Annealed Tempers

9.1 Grain size shall be the standard requirement for all product in the annealed tempers.

9.2 Acceptance or rejection based upon grain size shall depend only on the average grain size of a test specimen taken from each of two sample portions, and each specimen shall be within the limits prescribed in **Table 3** when determined in accordance with Test Methods **E112**.

9.3 Grain size shall be determined on a plane parallel to the flat surfaces of the product.

#### 10. Mechanical Property Requirements

##### 10.1 Tensile Strength Requirements:

10.1.1 Product furnished under this specification shall conform to the tensile requirements prescribed in **Table 2** when tested in accordance with Test Method **E8/E8M**.

10.1.2 Acceptance or rejection based on mechanical properties shall depend only on tensile strength.

##### 10.2 Rockwell Hardness:

**TABLE 1 Chemical Requirements**

Copper Alloy UNS No.	Composition			
	Copper	Lead	Iron	Zinc
C33500	62.0–65.0	0.25–0.7	0.10 max	remainder
C34000	62.0–65.0	0.8–1.5	0.10 max	remainder
C34200	62.0–65.0	1.5–2.5	0.10 max	remainder
C35000	60.0–63.0	0.8–2.0	0.10 max	remainder
C35300	60.0–63.0	1.5–2.5	0.10 max	remainder
C35600	60.0–63.0	2.0–3.0	0.10 max	remainder