



Designation: D4122 – 17 (Reapproved 2023)

# Standard Practice for Carbon Black—Evaluation of an Industry Reference Black<sup>1</sup>

This standard is issued under the fixed designation D4122; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice covers guidelines for the production and testing for uniformity of a lot of carbon black to be used as an Industry Reference Black (IRB).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D1506 Test Methods for Carbon Black—Ash Content
- D1508 Test Method for Carbon Black, Pelleted Fines and Attrition
- D1509 Test Methods for Carbon Black—Heating Loss
- D1510 Test Method for Carbon Black—Iodine Adsorption Number
- D1513 Test Method for Carbon Black, Pelleted—Pour Density
- D1514 Test Method for Carbon Black—Sieve Residue
- D1618 Test Method for Carbon Black Extractables—

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.61 on Carbon Black Sampling and Statistical Analysis.

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1982. Last previous edition approved in 2017 as D4122 – 17<sup>ε1</sup>. DOI: 10.1520/D4122-17R23.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- Transmittance of Toluene Extract
- D2414 Test Method for Carbon Black—Oil Absorption Number (OAN)
- D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets
- D3191 Test Methods for Carbon Black in SBR (Styrene-Butadiene Rubber)—Recipe and Evaluation Procedures
- D3192 Test Methods for Carbon Black Evaluation in NR (Natural Rubber)
- D3265 Test Method for Carbon Black—Tint Strength
- D3493 Test Method for Carbon Black—Oil Absorption Number of Compressed Sample (COAN)
- D5230 Test Method for Carbon Black—Automated Individual Pellet Hardness
- D6556 Test Method for Carbon Black—Total and External Surface Area by Nitrogen Adsorption

## 3. Significance and Use

3.1 These guidelines are intended to ensure that IRBs are evaluated by a standard procedure.

3.2 These guidelines are to be used to establish the average physicochemical and physical rubber properties of a lot of carbon black to be used as an IRB.

## 4. Production, Quality Control, and Quality Assurance

4.1 It is assumed that the manufacturer of the IRB will use state-of-the-art techniques to ensure maximum uniformity throughout the entire production run. The production should be made in one continuous production lot run. The testing called for in this practice is not intended to be a substitute for in-process quality control. This interlaboratory study is only adequate to verify the quality of a homogeneous lot.

4.2 The size of the lot is determined by historical records on the rate of use. The lot should have an expected life of eight to ten years at the most recent rate of use.

4.3 The black should be bagged in 50 lb polyethylene bags to reduce moisture incursion. Each pallet of bagged black should be wrapped in plastic to reduce environmental exposure. Depending on the size of the lot, the bagged black will be segregated into equal sized sublots, typically ten to twenty, representing some logical subdivision, such as a truck load.

**5. Sampling**

5.1 To avoid having to break down stacked and wrapped bags on a pallet, the bags to be used as samples for uniformity and property determination testing are typically removed at appropriate times from the bagging stream. At least one sample per subplot will be collected for uniformity testing. If more than one sample point is identified for each subplot, they should be spaced to represent approximately equal quantities. Typically, two bags are taken at each sampling point. One is retained by the producer for in-house uniformity testing and one is used for samples to be distributed to participants in the rubber testing and uniformity ITP. The bags selected will be numbered from one through *n*, where *n* is the total number of sublots, in order to represent the corresponding production lot or labeled to identify the subplot and its position relative to the whole of the corresponding production lot.

5.2 *n* 4-dm<sup>3</sup> (1 gal) samples, numbered from one through *n*, or marked with the labels from 5.1 as taken from the corresponding bags, will be sent to each participant in the interlaboratory study to evaluate the new IRB.

5.3 Additionally, a 4-dm<sup>3</sup> (1 gal) sample of the *previous* IRB taken from a common blended source will also be sent to each participant.

**6. Procedure**

6.1 It is preferred that all of the samples be tested on the same day for any of the test methods described in 6.2 and 6.3. If the testing cannot be completed in the same day, it should be completed in consecutive days.

6.2 *Rubber Physical Tests:*

6.2.1 Perform the following physical tests in rubber on both the new and previous IRB. Test samples mixed in accordance with Test Methods **D3191**, Test Method A, Test Method B, or Test Method C and cure for 50 min at 145 °C as well as samples mixed in accordance with Test Methods **D3192**, Test Method A, Test Method B, or Test Method C and cure for 30 min at 145 °C. It is preferred that participating laboratories be found so that data from all test methods can be included for evaluation.

6.2.1.1 In accordance with Test Methods **D412**, Test Method A, test five dumbbells from each cured sheet and determine the mean values of tensile stress at 300 % elongation, tensile strength, and ultimate elongation.

6.2.1.2 Record data in absolute numbers (not as differences from IRB) on **Table 1**, reporting tensile stress and tensile strength to the nearest 0.1 MPa and ultimate elongation to the nearest 5 %.

6.3 *Informational Physicochemical Tests:*

6.3.1 Perform the following physicochemical tests on the new IRB:

6.3.1.1 *Iodine Adsorption Number (Test Method D1510)*—Report the result obtained from an individual determination in grams of iodine per kilogram to the nearest 0.1 unit.

6.3.1.2 *Oil Absorption Number (Test Method D2414)*—Report the result obtained from an individual determination in 10<sup>-5</sup> m<sup>3</sup>kg (cm<sup>3</sup>/100 g) to the nearest 0.1 unit.

6.3.2 Record data on **Table 2** (or in a form that captures the same information as in **Table 2**).

**TABLE 1 Industry Reference Black Test Data**

Laboratory Number _____ Test Method _____									
Day of Mixing and Date	Sample No.	Tensile Strength, MPa <b>D3191</b>		Tensile Stress at 300 %, MPa <b>D3191</b>		Elongation, % <b>D3191</b>		Tensile Strength, MPa <b>D3192</b>	
		50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	
Day No. _____ Date _____	Prev. IRB	50'						30'	