This Research Report is issued under the fixed designation RR: D31-1007. You agree not to reproduce or circulate or quote, in whole or part, this document outside of ASTM International Committee/Society activities, or submit it to any other organization or standards body (whether national, international or other) except with the approval of the Chairman of the Committee having jurisdiction and the written authorization of the President of the Society. If you do not agree to these conditions, please immediately destroy all copies of this document. *Copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. All rights reserved.* 

## 13 September 1984

## Committee D31 on Leather Subcommittee D31.07 on Physical Properties

**Research Report D31-1007** 

Interlaboratory Study to Establish Precision Statements for ASTM D1516-05 Standard Test Method for Width of Leather

> ASTM International 100 Barr Harbor Drive West Conshohocken, PA 19428-2959

## Width Measurement Round Robin Width in millimeters

•	width in mi.	llimeters		
Specimen				
Designation	Laboratory A	Laboratory B	Laboratory C	Average
Alb	50.0	50.0	50.5	50.2
A1C	49.0	49.0	50.0	49.3
A2B	49.0	49.0	49.5	49.2
A2C	49.0	49.0	50.0	49.3
A3B	49.0	49.5	49.5	49.3
A3C	49.0	48.5	49.5	49.0
A4C	49.0	49.0	49.5	49.3
A5B	49.0	49.0	50.0	49.3
A6C	48.5	48.5	49.5	48.8
A7B	49.0	49.0	50.0	49.3
A8B	49.0	49.0	49.5	49.2
A9B	49.0	49.0	50.0	49.3
A10B	48.5	49.0	49,5	49.0
A10C	49.5	48.5	50.p	49.3
AllB	48.5	49.0	49.5	49.0
AllC	49.0	48.5	50 <b>.</b> Ø	49.2
B1B	.50.5	50.5	50.5	50.5
B2B	50.5	50.5	50 <b>.</b>  5	50.5
B3C	50.0	49.5	50 <b>.</b> 0	49.8
B4B	50.0	50.0	50 <b>.</b> 0	50.0
B4C	50.0	50.0	50.p	50.0
B5B	50.0	50.0	50 <b>.</b> 0	50.0
B5C	50.0	50.0	50.p	50.0
B6B	50.0	49.5	50,5	50.0
B6C	49.5	49.5	50.0	49.7
B7B	50.5	50.5	50,5	50.5
B7C	50.0	50.0	50.0	50.0
B8B	50.0	50.0	50.0	50.0
B8C	50.0	50.0	50.0	50.0
B9B	50.5	50.5	50 <b>.</b> 5	50.5
B9C	50.5	50.5	50.5	50.5
B10B	49.5	49.5	50.0	49.7
B10C	49.5	49.5	50.0	49.7
B11B	50.0	50.5	50.0	50.2
B11C	50.0	50.0	50.0	50.0
B12B	49.5	49.5	50.0	49.7
B12C C1B	49.5	49.5	50.0	49.7
CIC	50.0	49.5	50.0	49.8
010	50.0	49.5	50.0	49.8

D 1516-84 D-31

4