



Designation: A2 – 02 (Reapproved 2020)

# Standard Specification for Carbon Steel Girder Rails of Plain, Grooved, and Guard Types<sup>1</sup>

This standard is issued under the fixed designation A2; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification covers carbon steel girder rails<sup>2</sup> of three classes based on type or type and weight, and chemistry defined as follows and in [Table 1](#).

1.1.1 Unless otherwise specified by the purchaser, girder-guard rails shall be Class A.

1.1.2 Plain and grooved-girder rails under 135 lb/yd (67.1 kg/m) in weight shall be specified by the purchaser as either Class A or Class B.

1.1.3 Plain and grooved-girder rails of 135 lb/yd in weight and heavier shall be Class C, unless otherwise specified.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

[A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)  
[E10 Test Method for Brinell Hardness of Metallic Materials](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.01 on Steel Rails and Accessories.

Current edition approved March 1, 2020. Published March 2020. Originally approved in 1912. Last previous edition approved in 2014 as A2 – 02 (2014). DOI: 10.1520/A0002-02R20.

<sup>2</sup> Design details for carbon steel girder rails are indicated in the girder rail catalogs of individual manufacturers.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Classification of Rails

3.1 *No. 1 Rails*—Rails that are free of injurious imperfections and flaws of all kinds.

3.2 *No. 2 Rails*—Rails that contain surface imperfections in such number or of such character that shall not, in the judgment of the inspector, render them unfit for recognized uses.

## 4. Ordering Information

4.1 Orders for girder rails under this specification shall include the following information as appropriate:

4.1.1 ASTM designation and date of issue;

4.1.2 Quantity (tons or pieces as appropriate);

4.1.3 Complete identification of section with dimensional drawing if required;

4.1.4 Arrangement of bolt holes, bond holes, and tie rod holes with dimensional drawings, if required;

4.1.5 Class (in accordance with [1.1](#) and [Table 1](#)); and

4.1.6 Certification and Test Report (see [12.1](#)).

## 5. Manufacture

5.1 *Melting Practice*—The steel shall be made by any of the following processes: open-hearth, basic-oxygen, or electric-furnace.

5.1.1 The steel may be cast by a continuous process or in ingots.

5.2 *Discard*—Sufficient discard shall be made to secure freedom from injurious segregation and piping.

## 6. Chemical Composition

6.1 *Heat or Cast Analysis*—An analysis for each heat or cast of steel shall be made by the manufacturer to determine the percentage of the elements specified in [Table 1](#). The analysis shall be made from a test sample representing the heat or cast and shall conform to the requirements in [Table 1](#).

6.2 Upon request by the purchaser, similar samples shall be provided to verify the heat or cast analysis as determined in [6.1](#).

6.3 *Product Analysis*—When ladle tests are not available, finished material representing the heat may be product tested.