



Designation: A487/A487M – 21

# Standard Specification for Steel Castings Suitable for Pressure Service<sup>1</sup>

This standard is issued under the fixed designation A487/A487M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification<sup>2</sup> covers low-alloy steels and martensitic stainless steels in the normalized and tempered, or quenched and tempered, condition suitable for pressure-containing parts. The weldability of the classes in this specification varies from readily weldable to weldable only with adequate precautions, and the weldability of each class should be considered prior to assembly by fusion welding.

1.2 Selection will depend on design, mechanical, and service conditions. Users should note that hardenability of some of the grades mentioned may restrict the maximum size at which the required mechanical properties are obtained.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3.1 Within the text, the SI units are shown in brackets.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 1963. Last previous edition approved in 2020 as A487/A487M – 20. DOI: 10.1520/A0487\_A0487M-21.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specifications SA-487 in Section II of that code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel](#)

[A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts](#)

[A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts](#)

[E165/E165M Practice for Liquid Penetrant Testing for General Industry](#)

[E709 Guide for Magnetic Particle Testing](#)

2.2 *American Society of Mechanical Engineers:*<sup>4</sup>

[ASME Boiler and Pressure Vessel Code, Section IX](#)

2.3 *Manufacturers Standardization Society of the Valve and Fittings Industry Standards:*<sup>5</sup>

[SP-55 Quality Standard for Steel Castings—Visual Method](#)

## 3. General Conditions for Delivery

3.1 Except for investment castings, castings furnished to this specification shall conform to the requirements of Specification [A703/A703M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A703/A703M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A703/A703M](#), this specification shall prevail.

3.2 Investment castings furnished to this specification shall conform to the requirements of Specification [A985/A985M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A985/A985M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A985/A985M](#), Specification [A985/A985M](#) shall prevail.

## 4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

<sup>5</sup> Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.msshq.com>.

\*A Summary of Changes section appears at the end of this standard

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 ASTM designation and year of issue,

4.1.3 Grade and class of steel,

4.1.4 Options in the specification, and

4.1.5 The supplementary requirements desired, including the standard of acceptance.

## 5. Heat Treatment

5.1 All castings shall receive a heat treatment indicated in **Table 1**. Preliminary heat treatment prior to final heat treatment, as well as multiple tempering, is permitted.

5.2 Heat treatment shall be performed after the castings have been allowed to cool below the transformation range.

5.3 The furnace temperature for heat treating shall be effectively controlled by use of recording-type pyrometers.

## 6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 2**. Except for investment castings, product analysis tolerance shall conform to the product analysis tolerance shown in Specification **A703/A703M**. For investment castings, the product analysis tolerance shall conform to the product analysis tolerance shown in Specification **A985/A985M**.

## 7. Tensile Requirements

7.1 Tensile properties of steel used for the castings shall conform to the requirements prescribed in **Table 3**.

**TABLE 1 Heat Treat Requirement**

Grade	Class	Austenitizing Temperature, min, °F [°C]	Media <sup>A</sup>	Quenching Cool Below °F [°C]	Tempering Temperature, <sup>B</sup> °F [°C]
1	A	1600 [870]	A	450 [230]	1100 [595]
1	B	1600 [870]	L	500 [260]	1100 [595]
1	C	1600 [870]	A or L	500 [260]	1150 [620]
2	A	1600 [870]	A	450 [230]	1100 [595]
2	B	1600 [870]	L	500 [260]	1100 [595]
2	C	1600 [870]	A or L	500 [260]	1150 [620]
4	A	1600 [870]	A or L	500 [260]	1100 [595]
4	B	1600 [870]	L	500 [260]	1100 [595]
4	C	1600 [870]	A or L	500 [260]	1150 [620]
4	D	1600 [870]	L	500 [260]	1150 [620]
4	E	1600 [870]	L	500 [260]	1100 [595]
6	A	1550 [845]	A	500 [260]	1100 [595]
6	B	1550 [845]	L	500 [260]	1100 [595]
7	A	1650 [900]	L	600 [315]	1100 [595]
8	A	1750 [955]	A	500 [260]	1250 [675]
8	B	1750 [955]	L	500 [260]	1250 [675]
8	C	1750 [955]	L	500 [260]	1250 [675]
9	A	1600 [870]	A or L	500 [260]	1100 [595]
9	B	1600 [870]	L	500 [260]	1100 [595]
9	C	1600 [870]	A or L	500 [260]	1150 [620]
9	D	1600 [870]	L	500 [260]	1150 [620]
9	E	1600 [870]	L	500 [260]	1100 [595]
10	A	1550 [845]	A	500 [260]	1100 [595]
10	B	1550 [845]	L	500 [260]	1100 [595]
11	A	1650 [900]	A	600 [315]	1100 [595]
11	B	1650 [900]	L	600 [315]	1100 [595]
12	A	1750 [955]	A	600 [315]	1100 [595]
12	B	1750 [955]	L	400 [205]	1100 [595]
13	A	1550 [845]	A	500 [260]	1100 [595]
13	B	1550 [845]	L	500 [260]	1100 [595]
14	A	1550 [845]	L	500 [260]	1100 [595]
16	A	1600 [870] <sup>C</sup>	A	600 [315]	1100 [595]
17	A	1590 [865] <sup>C</sup>	L	500 [260]	1095 [590] <sup>F,G</sup>
CA15	A	1750 [955]	A or L	400 [205]	900 [480]
CA15	B	1750 [955]	A or L	400 [205]	1100 [595]
CA15	C	1750 [955]	A or L	400 [205]	1150 [620] <sup>D,E</sup>
CA15	D	1750 [955]	A or L	400 [205]	1150 [620] <sup>D,E</sup>
CA15M	A	1750 [955]	A or L	400 [205]	1100 [595]
CA6NM	A	1850 [1010]	A or L	200 [95]	1050–1150 [565–620]
CA6NM	B	1850 [1010]	A or L	200 [95]	1225–1275 [665–690] <sup>E,F</sup>
					1050–1150 [565–620] <sup>G</sup>

<sup>A</sup> A = air, L = liquid.

<sup>B</sup> Minimum temperature unless a range is specified.

<sup>C</sup> Double austenitize.

<sup>D</sup> Double temper with the final temper at a lower temperature than the intermediate temper.

<sup>E</sup> Air cool to below 200 °F [95 °C] after first temper.

<sup>F</sup> Intermediate.

<sup>G</sup> Final.



TABLE 2 Chemical Composition Requirements<sup>A,B</sup>

Grade Class Type (UNS Number)	Element, %											
	Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Copper	Vanadium	Boron	Tungsten
1 ABC V (J13002)	0.30	1.00	0.035	0.035	0.80	0.50 <sup>D</sup>	0.35 <sup>D</sup>	0.04-0.12	0.50 <sup>D</sup>	0.04-0.12	...	0.10 <sup>D</sup>
2 ABC Mn-Mo (J13005)	0.30	1.00-1.40	0.035	0.035	0.80	0.50 <sup>D</sup>	0.35 <sup>D</sup>	0.10-0.30	0.50 <sup>D</sup>	0.03 <sup>D</sup>	...	0.10 <sup>D</sup>
4 ABCDE Ni-Cr-Mo (J13047)	0.30	1.00	0.035	0.035	0.80	0.40-0.80	0.40-0.80	0.15-0.30	0.50 <sup>E</sup>	0.03 <sup>E</sup>	...	0.10 <sup>E</sup>
6 AB Mn-Ni-Cr-Mo (J13855)	0.05-0.38	1.30-1.70	0.035	0.035	0.80	0.40-0.80	0.40-0.80	0.30-0.40	0.50 <sup>E</sup>	0.03 <sup>E</sup>	...	0.10 <sup>E</sup>
7 A Ni-Cr-Mo-VF (J13084)	0.05-0.20	0.60-1.00	0.035	0.035	0.80	0.70-1.00	0.40-0.80	0.40-0.60	0.15-0.50	0.03-0.10	0.002-0.006	0.10
8 ABC Cr-Mo (J22091)	0.05-0.20	0.50-0.90	0.035	0.035	0.80	...	2.00-2.75	0.90-1.10	0.50 <sup>E</sup>	0.03 <sup>E</sup>	...	0.10 <sup>E</sup>
9 ABCDE Cr-Mo (J13345)	0.05-0.33	0.60-1.00	0.035	0.035	0.80	0.50 <sup>D</sup>	0.75-1.10	0.15-0.30	0.50 <sup>D</sup>	0.03 <sup>D</sup>	...	0.10 <sup>D</sup>
10 AB Ni-Cr-Mo (J23015)	0.30	0.60-1.00	0.035	0.035	0.80	1.40-2.00	0.55-0.90	0.20-0.40	0.50 <sup>E</sup>	0.03 <sup>E</sup>	...	0.10 <sup>E</sup>
11 AB Ni-Cr-Mo (J12082)	0.05-0.20	0.50-0.80	0.035	0.035	0.60	0.70-1.10	0.50-0.80	0.45-0.65	0.50 <sup>G</sup>	0.03 <sup>G</sup>	...	0.10 <sup>G</sup>
12 AB Ni-Cr-Mo (J22000)	0.05-0.20	0.40-0.70	0.035	0.035	0.60	0.60-1.00	0.50-0.90	0.90-1.20	0.50 <sup>G</sup>	0.03 <sup>G</sup>	...	0.10 <sup>G</sup>
13 AB Ni-Mo (J13080)	0.30	0.80-1.10	0.035	0.035	0.60	1.40-1.75	0.40 <sup>H</sup>	0.20-0.30	0.50 <sup>H</sup>	0.03 <sup>H</sup>	...	0.10 <sup>H</sup>