



Designation: A 570/A 570M – 98

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Structural Steel, Sheet and Strip, Carbon, Hot-Rolled¹

This standard is issued under the fixed designation A 570/A 570M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers hot-rolled carbon structural steel sheet and strip in cut lengths or coils. This material is intended for structural purposes where mechanical test values are required, and is available in a maximum thickness of 0.229 in. [6.0 mm] except as limited by Specifications A 568/A 568M and A 749/A 749M. The maximum thickness may be further limited by the capacity of the composition to meet the specified mechanical property requirements.

1.1.1 The following grades are covered in this specification:

| Grade | Mechanical Properties | |
|-----------|--------------------------------|--------------------------------|
| | Yield Point, min, ksi [MPa] | Tensile Strength, ksi [MPa] |
| 30 | 30 [205] | 49 [340] min |
| 33 | 33 [230] | 52 [360] min |
| 36 Type 1 | 36 [250] | 53 [365] min |
| 36 Type 2 | 36 [250] | 58–80 [400–550] |
| 40 | 40 [275] | 55 [380] min |
| 45 | 45 [310] | 60 [415] min |
| 50 | 50 [345] | 65 [450] min |
| 55 | 55 [380] | 70 [480] min |

1.2 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:

A 568/A 568M Specification for Steel, Sheet, Carbon and High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, General Requirements for²

A 749/A 749M Specification for Steel, Strip, Carbon and High-Strength, Low-Alloy, Hot-Rolled, General Requirements for²

3. Ordering Information

3.1 Orders for material under this specification shall include

the following information, as required, to describe the required material adequately:

3.1.1 ASTM specification number and date of issue, and grade,

3.1.2 Copper-bearing steel (if required),

3.1.3 Special requirements (if required),

3.1.4 Name of material (hot-rolled sheets or strip),

3.1.5 Condition—Material to this specification is furnished in the hot-rolled condition. Pickled (or blast cleaned) should be specified if required. Material so ordered will be oiled unless ordered dry, and

3.1.6 Dimensions, including type of edges.

3.1.6.1 As agreed upon between the purchaser and the producer, material ordered to this specification will be supplied to meet the appropriate standard or restricted thickness tolerance table shown in Specification A 568/A 568M.

NOTE 1—Not all producers are capable of meeting all of the limitations of the thickness tolerance tables in Specification A 568/A 568M. The purchaser should contact the producer regarding possible limitations prior to placing an order.

3.1.7 Coil size requirements.

NOTE 2—A typical ordering description is as follows: ASTM A 570—19XX, Grade 36, Hot-Rolled Sheets, 0.075 by 36 cut edge by 96 in. or ASTM A 570M—19XX, Grade 36, Hot-Rolled Sheets, 1.85 by 900 cut edge by 2450 mm.

4. Chemical Composition

4.1 The cast or heat analysis of the steel shall conform to the requirements prescribed in Table 1.

4.1.1 Unspecified elements may be present. Limits on elements shall be as stated in Table 2.

4.1.1.1 Each of the elements listed in Table 2 shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium, or molybdenum is less than 0.02 %, the analysis may be reported as <0.02 %. When the amount of vanadium or columbium is less than 0.008 %, the analysis may be reported as <0.008 %.

5. Mechanical Property Requirements

5.1 Tensile Tests:

5.1.1 Requirements—Material as represented by the test specimen shall conform to the tensile requirements specified in Table 3.

5.1.2 Number of Tests—Two tensile tests shall be made

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved June 10, 1998. Published November 1998. Originally published as A 570 – 66 T. Last previous edition A 570 – 97.

² Annual Book of ASTM Standards, Vol 01.03.