



Designation: A739 – 90a (Reapproved 2022)

# Standard Specification for Steel Bars, Alloy, Hot-Wrought, for Elevated Temperature or Pressure-Containing Parts, or Both<sup>1</sup>

This standard is issued under the fixed designation A739; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification<sup>2</sup> covers hot-wrought, ferritic alloy steel bars for elevated temperature or pressure-containing parts suitable for fusion welding or both.

1.2 The bars are furnished in the following grades:

Grade B 11: 1.25 % chromium, 0.55 % molybdenum  
Grade B 22: 2.25 % chromium, 1.00 % molybdenum

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

[A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought](#)

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

2.2 *ASME Code*:<sup>4</sup>

[ASME Boiler and Pressure Vessel Code](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.15 on Bars.

Current edition approved March 1, 2022. Published March 2022. Originally approved in 1976. Last previous edition approved in 2016 as A739 – 90a (2016). DOI: 10.1520/A0739-90AR22.

<sup>2</sup> For *ASME Boiler and Pressure Vessel Code* applications, see related Specification SA-739 in Section II of that code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

## 3. Ordering Information

3.1 Orders for material under this specification should include the following information:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Name of material (ferritic alloy steel bars),

3.1.3 Condition (hot wrought, normalized and tempered, machine straightened and descaled),

3.1.4 Dimensions (cross-sectional shape, size, and length),

3.1.5 ASTM designation and date of issue,

3.1.6 Grade ([Table 1](#)),

3.1.7 Additions to the specification, and

3.1.8 End use.

NOTE 1—A typical description is as follows: 10 000 lb, Ferritic Alloy Steel Bars, Hot Wrought Normalized and Tempered, and Descaled, 1.000 in. diameter by 10 ft, ASTM A739 dated\_\_\_\_, Grade B11, Special Straightened, Special Machined Fittings.

## 4. Materials and Manufacture

4.1 *Melting Practice*—The steel shall be made by one or more of the following primary processes: open-hearth, basic-oxygen, or electric-furnace. The primary melting may incorporate separate degassing or refining and may be followed by secondary melting using electroslag remelting or vacuum arc remelting. Where secondary melting is employed, the heat shall be defined as all of the ingots remelted from a single primary heat.

4.2 *Condition*—Unless otherwise specified, bars shall be hot wrought, heat treated, and descaled.

4.3 *Heat Treatment*:

4.3.1 The bars shall be normalized and tempered.

4.3.2 Austenitizing temperature shall be within the range from 1700 °F to 1800 °F (927 °C to 982 °C).

4.3.3 Cooling from the austenitizing temperature may be accomplished by cooling in still air or moving air, at the producer's option. When permitted by the purchaser, cooling from the austenitizing temperature may be accelerated by spray or liquid quenching.

4.3.4 The minimum tempering temperature shall be 1200 °F (649 °C) for Grade B11 and 1250 °F (677 °C) for Grade B22.